

# AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.  
29 West 39th Street  
New York City

## AMS 5390

Issued 8-15-55

Revised

ALLOY CASTINGS, PRECISION INVESTMENT, CORROSION AND HEAT RESISTANT  
Nickel Base - 22Cr - 1.5Co - 9Mo - 0.6W - 18.5Fe

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. **APPLICATION:** Primarily for parts such as turbine shroud segments and turbine vanes requiring oxidation resistance up to 2200 F, and relatively high strength above 1500 F.
3. **COMPOSITION:** Castings shall conform to the following:

		Check Analysis	
		Under	Min or Over Max
Carbon	0.20 max	--	0.01
Manganese	1.00 max	--	0.03
Silicon	1.00 max	--	0.05
Phosphorus	0.040 max	--	0.005
Sulfur	0.030 max	--	0.005
Chromium	20.50 - 23.00	0.25	0.25
Cobalt	0.50 - 2.50	0.05	0.05
Molybdenum	8.00 - 10.00	0.10	0.10
Tungsten	0.20 - 1.00	0.04	0.04
Iron	17.00 - 20.00	0.20	0.20
Nickel	remainder	--	--

4. **CASTING:** Castings shall be poured either from remelted master heat metal or directly from a master heat. A master heat is refined metal of a single furnace charge. Gates, sprues, risers, and rejected castings shall be used only in preparation of master heats; they shall not be remelted directly, without refining, for pouring of castings. When permitted by purchaser, metal in the form of shot from more than one master heat may be uniformly blended together to form a master heat lot; the total weight of metal in a master heat lot shall not exceed 7000 pounds.
5. **TEST SPECIMENS:**
  - 5.1 **Tensile Test Specimens:** Unless otherwise specified, tensile test specimens shall be cast to represent each master heat or master heat lot of metal in castings and, when requested, shall be supplied with the castings. The specimens shall be of standard proportions with 0.25 in. diameter at the reduced parallel section, shall be cast to size in molds made of the same refractory and heated to the same temperature as the molds for castings, and shall be cooled at approximately the same rate as the castings. If the metal for castings is given any treatment such as fluxing or cooling and reheating, metal for the specimens shall be so treated.
  - 5.2 **Bend Test Specimens:** When arc melting is used for producing castings, three specimens at least 0.090 in. in diameter or thickness and approximately 2 in. in length shall be cast in each mold along with each cast part or parts.
6. **CONDITION:** As cast, unless otherwise specified.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. The use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report, in formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

## 7. TECHNICAL REQUIREMENTS:

- 7.1 Tensile Properties: Tensile test specimens produced in accordance with 5.1, heated to  $1500\text{ F} + 10$ , held at  $1500\text{ F} + 10$  for 30 min. before testing, and tested at  $1500\text{ F} + 10$  at a rate of 0.045-0.062 in. per min. shall conform to the following requirements. If supplied tensile test specimens fail to meet requirements or are not available, suitable specimens may be prepared from castings for test.

Tensile Strength, psi	35,000 min
Elongation, % in 1 in.	12 min

## 7.2 Hardness:

- 7.2.1 Castings as cast shall have hardness not higher than Rockwell B 96 or equivalent.
- 7.2.2 Castings and specimens after being heated at  $1475\text{ F} + 10$  for 50 hr and cooled to room temperature shall have hardness not higher than Rockwell C 24 or equivalent.
- 7.3 Bending: At least two of the specimens cast in each mold in accordance with 5.2 shall withstand, without cracking, bending at room temperature through an angle of 30 deg around a 0.5 in. diameter. If more than one specimen from a mold fails to pass this test, the disposition of the castings from that mold may be determined by applying a similar test to an actual casting or to specimens cut from castings, gates, or runners. Such specimens shall be not less than 0.090 in. in diameter or thickness. Failure of any such additional specimens will be cause for rejection of the castings. Unless otherwise specified, bend test shall be performed by producer of castings.

## 8. QUALITY:

- 8.1 Castings shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external defects detrimental to fabrication or to performance of parts. Castings shall have smooth surfaces and shall be well cleaned. Unless otherwise specified, metallic shot or grit shall not be used for final cleaning.
- 8.2 When castings are broken for fracture test, the fracture shall have uniform color and be substantially free from oxides and other defects.
- 8.3 Radiographic and other quality standards shall be as agreed upon by purchaser and vendor.
- 8.4 Unless otherwise specified, castings shall be produced under radiographic control. This shall consist of radiographic examination of castings until proper foundry technique, which will produce castings free from harmful internal defects, is established for each part number, and of production castings as necessary to ensure maintenance of satisfactory quality.
- 8.5 Castings shall not be repaired by plugging, welding, or other methods, without written permission from purchaser.