



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AMS 5391B
Superseding 5391A

Issued 6-30-60
Revised 1-15-76

UNS NO7713

ALLOY CASTINGS, INVESTMENT, CORROSION AND HEAT RESISTANT
73Ni - 13Cr - 4.5Mo - 2.3 (Cb+Ta) - 0.75Ti - 6.0Al - 0.010B - 0.10Zr
Vacuum Melted

1. SCOPE:

1.1 Form: This specification covers a corrosion and heat resistant nickel alloy in the form of investment castings.

1.2 Application: Primarily for parts such as turbine blades requiring high strength up to 1800° F (982° C) and oxidation resistance up to 2000° F (1093° C).

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods
AMS 2635 - Radiographic Inspection
AMS 2645 - Fluorescent Penetrant Inspection

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E8 - Tension Testing of Metallic Materials
ASTM E18 - Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials
ASTM E139 - Conducting Creep, Creep-Rupture, and Stress-Rupture Tests of
Metallic Materials
ASTM E354 - Chemical Analysis of High-Temperature, Electrical, Magnetic, and
Other Similar Iron, Nickel, and Cobalt-Base Alloys

2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS:

SAE Technical Board rules provide that: "All technical reports, including standards approved by the Board, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report, in formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

- 3.1 **Composition:** Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E354, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other approved analytical methods:

	min	max
Carbon	0.08	- 0.20
Manganese	--	0.25
Silicon	--	0.50
Sulfur	--	0.015
Chromium	12.00	- 14.00
Molybdenum	3.80	- 5.20
Columbium + Tantalum	1.80	- 2.80
Titanium	0.50	- 1.00
Aluminum	5.50	- 6.50
Boron	0.005	- 0.015
Zirconium	0.05	- 0.15
Iron	--	2.50
Copper	--	0.50
Nickel + Cobalt	remainder	
Cobalt (3.1.1)	--	1.00

- 3.1.1 Determination not required for routine acceptance.

- 3.2 **Condition:** As cast.

- 3.3 **Casting:** Castings shall be poured either from remelted metal from a master heat or directly from a master heat. The metal for castings shall be melted and poured under vacuum without loss of vacuum between melting and pouring. In either case, metal for casting shall be qualified as in

3.4. A master heat is refined metal of a single furnace charge or metal blended as in 3.3.1 melted and cast into ingot or pig under vacuum. Gates, sprues, risers, and rejected castings shall be used only in preparation of master heats; they shall not be remelted directly, without refining, for pouring of castings.

- 3.3.1 Unless prohibited by purchaser, metal from two or more master heats may be blended provided that the composition of each master heat to be blended is within the limits of 3.1 and that the total weight of metal blended does not exceed 10,000 lb (4540/kg). When two or more master heats are blended, the resultant blend shall be considered a master heat.

- 3.4 **Master Heat Qualification:** Each master heat shall be qualified by evaluation of chemical analysis and tensile test specimens conforming to 3.4.1 and 3.4.2, respectively. A master heat may be considered conditionally qualified if vendor's test results show conformance to all applicable requirements of this specification. However, except when purchaser waives confirmatory testing, final qualification shall be based on purchaser's test results. Conditional qualification of a master heat shall not be construed as a guarantee of acceptance of castings poured therefrom.

- 3.4.1 **Chemical Analysis Specimens:** Shall be of any convenient size, shape, and form for vendor's tests. When chemical analysis specimens are required by purchaser, specimens shall be cast to a size, shape, and form agreed upon by purchaser and vendor.

- 3.4.2 **Tensile Test Specimens:**

3.4.2.1 Separately-Cast Specimens: Shall be cast from remelted metal from each master heat except \emptyset that when castings are poured directly from a master heat, the tensile test specimens shall also be poured directly from the master heat. Tensile test specimens shall be of standard proportions in accordance with ASTM E8 with 0.250 in. (6.35 mm) diameter at the reduced parallel gage section. They shall be cast to size or shall be cast oversize and subsequently machined to 0.250 in. (6.35 mm) diameter. Center gating may be used.

3.4.2.2 Specimens Machined from Castings: When agreed upon by purchaser and vendor, tensile test \emptyset specimens conforming to ASTM E8 shall be machined from castings selected at random from the shipment. Size, number, and location of such specimens shall be as shown on the drawing or as agreed upon by purchaser and vendor.

3.5 Properties: Castings and separately-cast tensile test specimens shall conform to the following \emptyset requirements:

3.5.1 Hardness: 30 - 42 HRC or equivalent, determined in accordance with ASTM E18.

3.5.2 Tensile Properties: Shall be as follows, determined in accordance with ASTM E8:

Tensile Strength, min	110,000 (758 MPa)
Yield Strength at 0.2% Offset, min	100,000 (690 MPa)
Elongation in 4D, min	3%

3.5.3 Stress-Rupture Properties at 1800° F (982.2° C): Shall be as follows; tests shall be performed in accordance with ASTM E139:

3.5.3.1 A tensile test specimen as in 3.4.2.1 or 3.4.2.2, maintained at 1800° F + 3 (982.2° C + 1.7) \emptyset while a load sufficient to produce an initial axial stress of 22,000 psi (152 MPa) is applied continuously shall not rupture in less than 30 hours. The test shall be continued to rupture without change of load. Elongation after rupture, measured at room temperature, shall be not less than 5% in 4D.

3.5.3.2 The test of 3.5.3.1 may be conducted using a load higher than required to produce an initial \emptyset axial stress of 22,000 psi (152 MPa) but load shall not be changed while test is in progress. Time to rupture and elongation requirements shall be as specified in 3.5.3.1.

3.5.3.3 When permitted by purchaser, the test of 3.5.3.1 may be conducted using incremental loading. \emptyset In such case, the load required to produce an initial axial stress of 22,000 psi (152 MPa) shall be used to rupture or for 30 hr, whichever occurs first. After the 30 hr and at intervals of 8 - 16 hr, preferably 8 - 10 hr, thereafter, the stress shall be increased in increments of 5000 psi (34.5 MPa). Time to rupture and elongation requirements shall be as specified in 3.5.3.1.

3.6 Quality:

3.6.1 Castings shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts. Castings shall have smooth surfaces and shall be well cleaned. Metallic shot or grit shall not be used for final cleaning, unless otherwise permitted.

3.6.2 Castings shall be produced under radiographic control, unless otherwise specified. This \emptyset control shall consist of radiographic examination of castings in accordance with AMS 2635 until proper foundry technique, which will produce castings free from harmful internal imperfections, is established for each part number and of production castings as necessary to ensure maintenance of satisfactory quality.

- 3.6.3 When specified, castings shall be subject to fluorescent penetrant inspection in accordance with
Ø AMS 2645.
- 3.6.4 Radiographic, fluorescent penetrant, and other quality standards shall be as agreed upon by
Ø purchaser and vendor.
- 3.6.5 Castings shall not be repaired by peening, plugging, welding, or other methods without written permission from purchaser.
- 3.6.5.1 When permitted in writing by purchaser, defects in castings may be removed and the castings
Ø repaired by welding provided the weld repair area has properties comparable to those of the parent metal. Repair welds shall be subjected to the same inspection procedures and acceptance standards required of the casting and the weld repair areas shall be suitably marked to facilitate inspection. The repair welding shall be performed prior to any heat treatment and nondestructive testing specified herein.

4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of castings shall supply all samples and shall be responsible
Ø for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that the castings conform to the requirements of this specification.
- 4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this
Ø specification are classified as acceptance or routine control tests.
- 4.2.1 For direct U.S. Military procurement, qualification test material and supporting test data shall be
Ø submitted to the cognizant qualification agency as directed by the request for procurement, the procuring activity, or the contracting officer.
- 4.3 Sampling: Shall be in accordance with the following:
- 4.3.1 Two chemical analysis specimens in accordance with 3.4.1 and/or a casting from each master
Ø heat.
- 4.3.2 Six tensile test specimens in accordance with 3.4.2 from each master heat, three specimens
Ø each for tensile testing and stress-rupture testing, when requested.
- Ø 4.3.3 Two preproduction castings in accordance with 4.4.1 of each part number.
- 4.3.4 One casting from each master heat when properties of specimens machined from castings are
Ø required.
- 4.4 Approval:
- 4.4.1 Sample castings from new or reworked master patterns and the casting procedure shall be
Ø approved by purchaser before castings for production use are supplied, unless such approval be waived.
- 4.4.2 Vendor shall establish separately for tensile test specimens used for master heat qualification and
Ø for production of sample castings of each part number the control factors of processing which will produce tensile test specimens meeting master heat qualification requirements and acceptable castings. These shall constitute the approved casting procedures and shall be used for producing subsequent master heat qualification specimens and production castings. If necessary to make any change in control factors of processing, vendor shall submit for reapproval a statement of the proposed changes in processing and, when requested, sample test specimens, castings, or both. No production castings incorporating the revised operations shall be shipped prior to receipt of reapproval.