

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS5392C

Issued 5-1-46

Revised 6-1-51

ALLOY IRON CASTINGS, SAND, CORROSION RESISTANT 15Ni - 6Cu - 2Cr

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. APPLICATION: Parts requiring moderate corrosion and heat resistance at operating temperatures up to 800 F.

3. COMPOSITION:

Carbon	2.4 - 2.8
Manganese	1.0 - 1.5
Silicon	1.5 - 2.5
Phosphorus	0.30 max
Sulfur	0.12 max
Chromium	1.8 - 2.4
Nickel	14.0 - 16.0
Copper	6.0 - 7.0
Lead	0.003 max

4. CONDITION: As cast, unless otherwise specified on the drawing.

5. TECHNICAL REQUIREMENTS:

5.1 Hardness: Brinell 130-175 or Rockwell B 75-85.

5.2 Fracture Test: When castings are broken for fracture test, the fracture shall have uniform color and be substantially free from oxides and other defects.

5.3 Microstructure: Austenite matrix with uniformly distributed graphite flakes. Parts shall be capable of being cooled to -75 F without the austenite transforming to martensite; parts so cooled, after returning to room temperature, shall be sufficiently non-magnetic to prevent a small magnet from adhering to the casting.

6. QUALITY:

6.1 Castings shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external defects detrimental to fabrication or to performance of parts. Castings shall have smooth surfaces and shall be well cleaned.

6.2 Unless otherwise specified, castings shall be produced under radiographic control.

6.3 Inspection standards and procedures shall be as agreed upon by purchaser and vendor.

6.4 Castings shall not be repaired by plugging, welding or other methods, without written permission from purchaser.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform, to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."