



AEROSPACE MATERIAL

Society of Automotive Engineers, Inc. SPECIFICATION

400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AMS 5397A

Superseding AMS 5397

Issued 2-15-65
Revised 1-15-77

ALLOY CASTINGS, INVESTMENT, CORROSION AND HEAT RESISTANT
50Ni - 9.5Cr - 15Co - 3.0Mo - 4.8Ti - 5.5Al - 0.015B - 0.95V - 0.6Zr
Vacuum-Melted, Vacuum-Cast

UNS N13100

1. SCOPE:

- 1.1 Form: This specification covers a corrosion and heat resistant nickel alloy in the form of vacuum-melted, vacuum-cast investment castings.
- 1.2 Application: Primarily for small parts, such as turbine blades, requiring high strength and oxidation resistance up to 1800°F (980°C).

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods
AMS 2360 - Room Temperature Tensile Properties of Castings
AMS 2362 - Stress-Rupture Properties of Castings
AMS 2635 - Radiographic Inspection
AMS 2645 - Fluorescent Penetrant Inspection

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E8 - Tension Testing of Metallic Materials
ASTM E18 - Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials
ASTM E139 - Creep, Creep-Rupture, and Stress-Rupture Tests of Metallic Materials
ASTM E192 - Reference Radiographs of Investment Steel Castings for Aerospace Applications
ASTM E354 - Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt-Base Alloys

2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS:

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E354, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other approved analytical methods:

	min	max
Carbon	0.15	0.20
Manganese	--	0.20
Silicon	--	0.20
Sulfur	--	0.015
Chromium	8.00	11.00
Cobalt	13.00	17.00
Molybdenum	2.00	4.00
Titanium	4.50	5.00
Aluminum	5.00	6.00
Titanium + Aluminum	10.00	11.00
Boron	0.01	0.02
Vanadium	0.70	1.20
Zirconium	0.03	0.09
Iron	--	1.00
Nickel		remainder

- 3.2 Condition: As cast.

- 3.3 Casting:

3.3.1 The metal for castings shall be melted and poured under vacuum without loss of vacuum between melting and pouring. When permitted by purchaser, protective atmosphere may be used in lieu of vacuum for pouring of castings.

3.3.2 Castings shall be poured either from remelted metal from a master heat or directly from a master heat. In either case, metal for casting shall be qualified as in 3.4.

3.3.2.1 A master heat is refined metal of a single furnace charge or metal blended as in 3.3.2.2 melted and cast into ingot or pig under vacuum. Gates, sprues, risers, and rejected castings shall be used only in preparation of master heats; they shall not be remelted directly, without refining, for pouring of castings.

3.3.2.2 Unless prohibited by purchaser, metal from two or more master heats may be blended provided that the composition of each master heat to be blended is within the limits of 3.1 and that the total weight of metal blended does not exceed 10,000 lb (4540 kg). When two or more master heats are blended, the resultant blend shall be considered a master heat.

3.4 Master Heat Qualification: Each master heat shall be qualified by evaluation of chemical analysis and tensile test specimens conforming to 3.4.1 and 3.4.2, respectively. A master heat may be considered conditionally qualified if vendor's test results show conformance to all applicable requirements of this specification. However, except when purchaser waives confirmatory testing, final qualification shall be based on purchaser's test results. Conditional qualification of a master heat shall not be construed as a guarantee of acceptance of castings poured therefrom.

3.4.1 Chemical Analysis Specimens: Shall be of any convenient size, shape, and form for vendor's tests. When chemical analysis specimens are required by purchaser, specimens shall be cast to a size, shape, and form agreed upon by purchaser and vendor.

3.4.2 Tensile Test Specimens: Shall be cast from remelted metal from each master heat except when
 Ø castings are poured directly from a master heat, in which case the specimens shall also be poured directly from the master heat. Specimens shall be of standard proportions in accordance with ASTM E8 with 0.250 in. (6.35 mm) diameter at the reduced parallel gage section. They shall be cast to size or shall be cast oversize and subsequently machined to 0.250 in. (6.35 mm) diameter. Center gating may be used.

3.5 Properties: Castings and representative tensile test specimens produced in accordance with
 Ø 3.4.2 shall conform to the following requirements:

Ø 3.5.1 Separately-Cast Specimens:

3.5.1.1 Tensile Properties: Shall be as follows, determined in accordance with ASTM E8:

Ø Tensile Strength, min	115,000 psi (793 MPa)
Yield Strength at 0.2% Offset, min	95,000 psi (655 MPa)
Elongation in 1 in. (25.4 mm) or 4D, min	5%

3.5.1.2 Stress-Rupture Properties at 1800°F (982°C): Specimens, maintained at 1800°F + 3 (982°C ± 2)
 Ø while a load sufficient to produce an initial axial stress of 29,000 psi (200 MPa) is applied continuously, shall not rupture in less than 23 hours. The test shall be continued to rupture without change of load. Elongation after rupture, measured at room temperature, shall be not less than 4% in 4D. Test shall be performed in accordance with ASTM E139.

3.5.1.2.1 The test of 3.5.1.2 may be conducted using a load higher than required to produce an initial
 Ø axial stress of 29,000 psi (200 MPa) but load shall not be changed while test is in progress. Time to rupture and elongation requirements shall be as specified in 3.5.1.2.

3.5.1.2.2 When permitted by purchaser, the test of 3.5.1.2 may be conducted using incremental loading.
 Ø In such cases, the load required to produce an initial axial stress of 29,000 psi (200 MPa) shall be used to rupture or for 23 hr, whichever occurs first. After the 23 hr and at intervals of 8 - 16 hr, preferably 8 - 10 hr, thereafter, the stress shall be increased in increments of 2500 psi (17.2 MPa). Time to rupture and elongation requirements shall be as specified in 3.5.1.2.

3.5.2 Castings:

3.5.2.1 Grain Size: Shall be substantially uniform, equiaxed, non-columnar grains without pronounced
 segregation of fine and coarse grained areas. Actual grain size and method of measurement shall be as agreed upon by purchaser and vendor.

Ø 3.5.2.2 Hardness: Shall be 30 - 44 HRC or equivalent, determined in accordance with ASTM E18.

3.5.2.3 Tensile and Stress-Rupture Properties: When specified on the drawing or when agreed upon by
 Ø purchaser and vendor, tensile test specimens conforming to ASTM E8 shall be machined from castings selected at random from each master heat. Property requirements for such specimens shall be as specified on the drawing or as agreed upon by purchaser and vendor and may be defined as specified in AMS 2360 and/or AMS 2362.

3.6 Quality:

3.6.1 Castings, as received by the purchaser, shall be uniform in quality and condition, sound, and free
 Ø from foreign materials and from internal and external imperfections detrimental to usage of the castings.

- 3.6.1.1 Castings shall have smooth surfaces and shall be well cleaned. Metallic shot or grit shall not be used for final cleaning, unless otherwise permitted.
- 3.6.2 Castings shall be produced under radiographic control, unless otherwise specified. This control shall consist of radiographic examination of castings in accordance with AMS 2635 until proper foundry technique, which will produce castings free from harmful internal imperfections, is established for each part number and of production castings as necessary to ensure maintenance of satisfactory quality.
- 3.6.3 When specified, castings shall be subject to fluorescent penetrant inspection in accordance with AMS 2645.
- 3.6.4 Radiographic, fluorescent penetrant, and other quality standards shall be as agreed upon by purchaser and vendor. ASTM E192 may be used to define radiographic acceptance standards.
- 3.6.5 Castings shall not be repaired by peening, plugging, welding, or other methods without written permission from purchaser.
- 3.6.5.1 When permitted in writing by purchaser, defects in castings may be removed and the castings repaired by welding provided the weld repair area has properties comparable to those of the parent metal. Repair welds shall be subjected to the same inspection procedures and acceptance standards required of the castings. Weld repair areas shall be suitably marked to facilitate inspection. Repair welding shall be performed prior to any nondestructive testing specified herein.

4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of castings shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that the castings conform to the requirements of this specification.
- 4.2 Classification of Tests:
- 4.2.1 Acceptance Tests: Tests to determine conformance to composition (3.1), tensile properties (3.5.1.1) and stress-rupture properties (3.5.1.2) of separately-cast specimens, grain size (3.5.2.1) and hardness (3.5.2.2) of castings, and quality (3.6) requirements, and, when specified, tensile and stress-rupture properties of specimens cut from castings (3.5.2.3) are classified as acceptance tests.
- 4.2.2 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests.
- 4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.
- 4.3 Samplings: Shall be in accordance with the following:
- 4.3.1 Two chemical analysis specimens in accordance with 3.4.1 and/or a casting from each master heat.
- 4.3.2 Six tensile test specimens in accordance with 3.4.2 from each master heat.
- 4.3.3 Two preproduction castings in accordance with 4.4.1 of each part number.