



# AEROSPACE MATERIAL SPECIFICATION

## AMS 5400

Society of Automotive Engineers, Inc.  
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

Issued 1-15-79  
Revised

STEEL CASTINGS, INVESTMENT, CORROSION RESISTANT  
15Cr - 4.6Ni - 0.22(Cb + Ta) - 2.8Cu  
Solution and Precipitation Heat Treated  
170,000 psi (1172 MPa) Tensile Strength

1. SCOPE:

1.1 Form: This specification covers a corrosion-resistant steel in the form of investment castings.

1.2 Application: Primarily for parts requiring good corrosion resistance and strength up to 600°F (315°C).

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods  
AMS 2635 - Radiographic Inspection  
AMS 2640 - Magnetic Particle Inspection  
AMS 2645 - Fluorescent Penetrant Inspection  
AMS 2804 - Identification, Castings

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A370 - Mechanical Testing of Steel Products  
ASTM E192 - Reference Radiographs of Investment Steel Castings for Aerospace Applications  
ASTM E353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

# REAFFIRMED

10/91

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method No. 112, or by other approved analytical methods:

	min	max
Carbon	--	0.05
Manganese	--	0.60
Silicon	0.50 -	1.00
Phosphorus	--	0.025
Sulfur	--	0.025
Chromium	14.00 -	15.50
Nickel	4.20 -	5.00
Columbium + Tantalum	0.15 -	0.30
Copper	2.50 -	3.20
Nitrogen	--	0.05

3.2 Condition: Solution and precipitation heat treated.

3.3 Casting: Castings shall be poured either from remelted metal from a master heat or directly from a master heat. In either case, metal for casting shall be qualified as in 3.4.

3.3.1 A master heat is refined metal of a single furnace charge or metal blended as in 3.3.2. Gates, sprues, risers, and rejected castings shall be used only in preparation of master heats; they shall not be remelted directly, without refining, for pouring of castings.

3.3.2 Unless prohibited by purchaser, metal from two or more master heats may be blended provided that the composition of each master heat to be blended is within the limits of 3.1 and that the total weight of metal blended does not exceed 10,000 lb (4540 kg). Ingot and pig may be blended together, shot may be blended, but shot shall not be blended with ingot or pig. When two or more master heats are blended, the resultant blend shall be considered a master heat.

3.4 Master Heat Qualification: Each master heat shall be qualified by evaluation of chemical analysis and tensile test specimens conforming to 3.4.1 and 3.4.2, respectively. A master heat may be considered conditionally qualified if vendor's test results show conformance to all applicable requirements of this specification. However, except when purchaser waives confirmatory testing, final qualification shall be based on purchaser's test results. Conditional qualification of a master heat shall not be construed as a guarantee of acceptance of castings poured therefrom.

3.4.1 Chemical Analysis Specimens: Shall be of any convenient size, shape, and form for vendor's tests. When chemical analysis specimens are required by purchaser, specimens shall be cast to a size, shape, and form agreed upon by purchaser and vendor.

3.4.2 Tensile Test Specimens: Shall be cast from remelted metal from each master heat except when castings are poured directly from a master heat, in which case the specimens shall also be poured directly from the master heat. Specimens shall be of standard proportions in accordance with ASTM A370, with 0.250 in. (6.25 mm) diameter at the reduced parallel gage section. They shall be cast to size or shall be cast oversize and subsequently machined to 0.250 in. (6.25 mm) diameter. Center gating may be used.

3.5 Heat Treatment: Castings and representative tensile test specimens shall be heat treated as follows:

3.5.1 Homogenization Heat Treatment: Castings and representative test specimens may be given a homogenization heat treatment prior to solution heat treatment when permitted by purchaser and shall be so treated when specified by purchaser. When permitted or specified, heat to 2100°F ± 25 (1150°C ± 15), hold at heat for not less than 90 min., and cool to below 90°F (32°C) at a rate equivalent to air cool or faster.

3.5.2 Solution Heat Treatment: Heat to 1900°F ± 25 (1038°C ± 15), hold at heat for 60 min. per inch (25 mm) of maximum cross-section, and cool to below 90°F (32°C) at a rate equivalent to air cool or faster. Double solution heat treatment is acceptable except when homogenization heat treatment precedes solution heat treatment.

3.5.3 Precipitation Heat Treatment: Heat to 935°F ± 15 (502°C ± 8), hold at heat for 4 hr ± 0.25, and cool in air.

3.6 Properties: Castings and representative tensile test specimens produced in accordance with 3.4.2 shall conform to the following requirements; hardness and tensile testing shall be performed in accordance with ASTM A370; conformance to the requirements of 3.6.1.1 shall be used as basis for acceptance of castings except when purchaser specifies that the requirements of 3.6.2.1 apply:

3.6.1 Separately-Cast Test Specimens:

3.6.1.1 Tensile Properties:

Tensile Strength, min	170,000 psi (1172 MPa)
Yield Strength at 0.2% Offset, min	150,000 psi (1034 MPa)
Elongation in 4D, min	7%
Reduction of Area, min	16%

3.6.2 Castings:

3.6.2.1 Tensile Properties:

Tensile Strength, min	170,000 psi (1172 MPa)
Yield Strength at 0.2% Offset, min	150,000 psi (1034 MPa)
Elongation in 4D, min	6%
Reduction of Area, min	14%

3.6.2.2 Hardness: Should be not lower than 38 HRC or equivalent and shall be not higher than 47 HRC or equivalent, determined at essentially the same location on each casting, but castings shall not be rejected on the basis of low hardness if the tensile property requirements of 3.6.2.1 are met, determined on the casting from each heat treatment lot having the lowest hardness.

3.7 Quality:

3.7.1 Castings, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the castings.

3.7.1.1 Castings shall have smooth surfaces and shall be well cleaned. Metallic shot or grit shall not be used for final cleaning, unless otherwise permitted.

3.7.2 Castings shall be produced under radiographic control, unless otherwise specified. This control shall consist of radiographic examination of castings in accordance with AMS 2635 until proper foundry technique, which will produce castings free from harmful internal imperfections, is established for each part number and of production castings as necessary to ensure maintenance of satisfactory quality.

3.7.3 When specified, castings shall be subjected to magnetic particle inspection in accordance with AMS 2640 and/or to fluorescent penetrant inspection in accordance with AMS 2645.

3.7.4 Radiographic, magnetic particle, fluorescent penetrant, and other quality standards shall be as agreed upon by purchaser and vendor. ASTM E192 may be used to define radiographic acceptance standards.

3.7.5 Castings shall not be repaired by peening, plugging, welding, or other methods without written permission from purchaser.

3.7.5.1 When permitted in writing by purchaser, defects in castings may be removed and the castings repaired by welding provided the weld repair area has properties comparable to those of the parent metal. Repair welds shall be subjected to the same inspection procedures and acceptance standards required of the castings. Weld repair areas shall be suitably marked to facilitate inspection. Repair welding shall be performed prior to any heat treatment and nondestructive testing specified herein.

#### 4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of castings shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that the castings conform to the requirements of this specification.

#### 4.2 Classification of Tests:

4.2.1 Acceptance Tests: Except as specified in 4.2.1.1, tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed to represent each lot.

4.2.1.1 Tensile properties of specimens cut from castings shall be determined only when specified by purchaser or when separately-cast specimens are not available. Tensile properties of separately-cast specimens need not be determined when tensile properties of specimens cut from castings are determined.

4.2.2 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed on the first-article shipment of a casting to a purchaser, when a change in material or processing requires re-approval, or when purchaser deems confirmatory testing is required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling: Shall be in accordance with the following:

4.3.1 Two chemical analysis specimens in accordance with 3.4.1 and/or a casting from each master heat.

4.3.2 Three tensile test specimens in accordance with 3.4.2 from each master heat.

4.3.3 Two preproduction castings in accordance with 4.4.1 of each part number.

4.3.4 One or more castings from each day's pour from each master heat when properties of specimens machined from castings are required. Size, location, and number of specimens machined from castings shall be as specified on the drawing or as agreed upon by purchaser and vendor. When size, location, and number of specimens are not specified, not less than two tensile test specimens, one from the thickest section and one from the thinnest section, shall be cut from a casting or castings from each day's pour from each master heat.

4.3.4.1 When size of castings or other factors preclude sampling as in 4.3.4, the type and frequency of testing shall be as agreed upon by purchaser and vendor.

#### 4.4 Approval:

4.4.1 Sample castings from new or reworked master patterns and the casting procedure shall be approved by purchaser before castings for production use are supplied, unless such approval be waived.