



AEROSPACE MATERIAL SPECIFICATIONS

AMS 5501

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc.

485 Lexington Ave., New York, N. Y. 10017

Issued 11-1-67
Revised

STEEL FOIL, CORROSION RESISTANT 19Cr - 9Ni (SAE 30304) Cold Rolled, 125,000 psi

- 1. ACKNOWLEDGMENT:** A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
- 2. APPLICATION:** Primarily for liners of filament wound pressure vessels.
- 3. COMPOSITION:**

	min	max
Carbon	--	0.08
Manganese	--	2.00
Silicon	--	1.00
Phosphorous	--	0.040
Sulphur	--	0.030
Chromium	18.00 - 20.00	
Nickel	8.00 - 11.00	
Molybdenum	--	0.50
Copper	--	0.50

- 3.1 Check Analysis:** Composition variations shall meet the requirements of the latest issue of AMS 2248.
- 4. CONDITION:** Cold rolled, solution heat treated, descaled, and rerolled (No. 2 Strip Finish).

5. TECHNICAL REQUIREMENTS:

5.1 Tensile Properties:

Tensile Strength, psi	125,000 min
Yield Strength at 0.2% Offset or at 0.0098 in. in 2 in. Extension Under Load (E = 26,000,000), psi	75,000 min
Elongation, % in 2 in.	15 min

- 5.1.1** For widths 9 in. and over, tensile test specimens shall be taken with the axis perpendicular to the direction of rolling. For widths less than 9 in., tensile test specimens shall be taken with the axis parallel to the direction of rolling.
- 5.2 Bending:** Material tested with specimens 0.750 in. in width shall withstand, without cracking, bending at room temperature through the angle indicated below around a diameter equal to the bend factor times the nominal thickness of the material, with axis of bend parallel to the direction of rolling; only one bend test need be performed.

Nominal Thickness Inch	Type of Bend	Angle deg, min	Bend Factor
Up to 0.010, incl	Free Bend	180	1
Up to 0.010, incl	V-Block	135	2

Technical Board rules provide that: "All technical reports, including standards approved practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."