

# AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.  
29 West 39th Street  
New York City

## AMS 5510E

Issued 12-4-39  
Revised 2-15-52

### STEEL SHEET AND STRIP, CORROSION AND HEAT RESISTANT 18Cr - 10Ni - Ti (SAE 30321)

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. FORM: Sheet, strip, and plate.
3. APPLICATION: Primarily for parts and assemblies requiring both corrosion and heat resistance and especially where such parts and assemblies require welding during fabrication. Parts and assemblies requiring oxidation resistance up to approximately 1500 F but useful at this temperature only when stresses are low.
4. COMPOSITION:

#### Check Analysis\*

Under Min or Over Max

Carbon	0.08 max	—	0.01
Manganese	1.00 - 2.00	0.04	0.04
Silicon	1.00 max	—	0.05
Phosphorus	0.040 max	—	0.005
Sulfur	0.030 max	—	0.005
Chromium	17.00 - 19.00	0.20	0.20
Nickel	8.00 - 11.00	0.15	0.15
Titanium	6x0 - 0.70	0.05	0.05
Molybdenum	0.50 max	—	0.03
Copper	0.50 max	—	0.03

#### 5. CONDITION:

- 5.1 Sheet: Cold rolled, solution heat treated and descaled (No. 2D Finish).
- 5.2 Strip: Cold rolled, solution heat treated and descaled (No. 1 Strip Finish).
- 5.3 Plate: Hot rolled, solution heat treated and descaled.

#### 6. TECHNICAL REQUIREMENTS:

##### 6.1 Tensile Properties:

Tensile Strength, psi	100,000 max
Elongation, % in 2 in.	40 min

- 6.1.1 For widths 9 in. and over, tensile test specimens shall be taken with the axis perpendicular to the direction of rolling. For widths less than 9 in., tensile test specimens shall be taken with the axis parallel to the direction of rolling.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

- 6.2 Bending: Material shall withstand, without cracking, bending at room temperature through the angle indicated below, around a diameter equal to the nominal thickness of the material, with the axes of bends both perpendicular and parallel to the direction of rolling:

Nominal Thickness Inch	Angle Degrees, min	Bend Factor
0.249 and under	180 (135)	1 (1)
Over 0.249 to 0.749, incl	90 (135)	1 (2)

When bend is made using a V-block, figures in parentheses apply.

- 6.3 Embrittlement: Material shall be capable of meeting the following test:
- 6.3.1 Test specimens, after being heated at 1200 F + 10 for 2 hr and air cooled, shall withstand immersion for 48 hr in a boiling aqueous solution containing 100 g of  $CuSO_4 \cdot 5H_2O$  and 100 ml of  $H_2SO_4$  (sp gr 1.84) per liter of solution under a reflux condenser, without evidence of intercrystalline surface attack. After such immersion, the specimens shall withstand bending as in 6.2.
7. QUALITY: Material shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external defects detrimental to fabrication or to performance of parts.
8. TOLERANCES: Unless otherwise specified, tolerances shall conform to the latest issue of AMS 2242 as applicable and as specified below:
- 8.1 Thickness: Table I and III.
- 8.2 Flatness: Sheet and strip, Table VI.
9. REPORTS:
- 9.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report of the results of tests for chemical composition of each heat in the shipment and the results of tests on each thickness from each heat to determine conformance to the tensile and bending requirements of this specification. This report shall include the purchase order number, heat number, material specification number, thickness, size, and quantity from each heat.
- 9.2 Unless otherwise specified, the vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.