

AEROSPACE MATERIAL SPECIFICATION

SAE AMS-5516

REV

K

Issued 1940-01-23

Revised 1991-01-01

Superseding AMS-5516J

Submitted for recognition as an American National Standard

STEEL SHEET, STRIP, AND PLATE, CORROSION RESISTANT
18Cr - 9.0Ni (SAE 30302)
Solution Heat Treated

UNS S30200

1. SCOPE:

1.1 Form: This specification covers a corrosion-resistant steel in the form of sheet, strip, and plate.

1.2 Application: Primarily for formed and drawn parts requiring corrosion resistance up to 800°F (427°C).

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

2.1.1 Aerospace Material Specifications:

- AMS-2242 - Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate
- MAM-2242 - Tolerances, Metric, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate
- AMS-2248 - Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
- AMS-2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

2.2 ASTM Publications: Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM A 370 - Mechanical Testing of Steel Products
 ASTM E 353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

2.3 U.S. Government Publications: Available from Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

2.3.1 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser:

	min	max
Carbon	---	0.15
Manganese	---	2.00
Silicon	---	1.00
Phosphorus	---	0.040
Sulfur	---	0.030
Chromium	17.00 -	19.00
Nickel	8.00 -	10.00
Molybdenum	---	0.75
Copper	---	0.75

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS-2248.

3.2 Condition: The product shall be supplied in the following condition:

3.2.1 Sheet and Strip: Cold rolled, solution heat treated, and, unless solution heat treatment is performed in an atmosphere yielding a bright finish, descaled having a surface appearance conforming to 3.2.1.1 or 3.2.1.2 as applicable (See 8.2).

3.2.1.1 Sheet: No. 2D finish.

3.2.1.2 Strip: No. 1 strip finish.

3.2.1.2.1 Strip under 0.007 inch (0.18 mm) in nominal thickness shall be bright annealed.

3.2.2 Plate: Hot rolled, solution heat treated, and descaled.

3.3 Properties: The product shall conform to the following requirements; tensile and bend testing shall be performed in accordance with ASTM A 370:

3.3.1 Tensile Properties: Shall be as specified in Table I.

Ø

TABLE I

Nominal Thickness Inches	Tensile Strength psi	Yield Strength at 0.2% Offset psi	Elongation in 2 Inches or 4D %, min
0.002 to 0.003, incl	75,000 - 110,000	36,000 - 60,000	30
Over 0.003 to 0.004, incl	75,000 - 105,000	36,000 - 60,000	35
Over 0.004 to 0.176, incl	75,000 - 100,000	36,000 - 60,000	40
Over 0.176	75,000 - 100,000	30,000 min	40

TABLE I (SI)

Nominal Thickness Millimetres	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm or 4D %, min
0.05 to 0.08, incl	517 - 758	248 - 414	30
Over 0.08 to 0.10, incl	517 - 724	248 - 414	35
Over 0.10 to 4.47, incl	517 - 689	248 - 414	40
Over 4.47	517 - 689	207 min	40

3.3.2 Bending: Product 0.749 inch (19.02 mm) and under in nominal thickness shall withstand, without cracking, bending through the angle indicated below around a diameter equal to the bend factor times the nominal thickness of the product with axis of bend parallel to the direction of rolling. Only one type of test will be required in routine inspection; in case of dispute, results of tests using the V-block procedure shall govern.

Nominal Thickness		Type of Bend	Angle deg, min	Bend Factor
Inch	Millimetres			
Up to 0.249, incl	Up to 6.32, incl	Free Bend	180	1
Up to 0.249, incl	Up to 6.32, incl	V-Block	135	1
Over 0.249 to 0.749, incl	Over 6.32 to 19.02, incl	Free Bend	90	1
Over 0.249 to 0.749, incl	Over 6.32 to 19.02, incl	V-Block	135	2

3.3.2.1 Bending requirements for plate over 0.749 inch (19.02 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances: Shall conform to all applicable requirements of AMS-2242 or MAM-2242.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests for composition (3.1), tensile properties (3.3.1), and tolerances (3.5) are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests: Tests for bending (3.3.2) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing: Shall be in accordance with AMS-2371.

4.4 Reports: The vendor of the product shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and for tensile properties of each lot and, when performed, the results of tests to determine conformance to the periodic test requirements. This report shall include the purchase order number, lot number, AMS-5516K, size, and quantity.

4.5 Resampling and Retesting: Shall be in accordance with AMS-2371.

5. PREPARATION FOR DELIVERY:

5.1 Identification: Each sheet, strip, and plate shall be legibly marked on one face, in the respective location indicated below, with AMS-5516K, lot number, manufacturer's identification, and nominal thickness. The characters shall be applied using a suitable marking fluid removable in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the product or its performance and shall be sufficiently stable to withstand normal handling.

5.1.1 Flat Strip 6 Inches (152 mm) and Under in Width: Shall be marked in one or more lengthwise rows of characters recurring at intervals not greater than 3 feet (914 mm).

5.1.2 Flat Sheet, Flat Strip Over 6 Inches (152 mm) in Width, and Plate: Shall be marked in lengthwise rows of characters recurring at intervals not greater than 3 feet (914 mm), the rows being spaced not more than 6 inches (152 mm) apart and alternately staggered.

5.1.3 Coiled Sheet and Strip: Shall be marked near both the outside and inside ends of the coil; the markings shall be applied as in 5.1 or shall appear on a durable tag or label attached to the coil and marked with the information of 5.1. When the product is wound on cores, the tag or label may be attached to the core.