

**AEROSPACE
MATERIAL
SPECIFICATION**

AMS 5523F

Issued	NOV 1952
Reaffirmed	SEP 2000
Revised	SEP 2006
Superseding	AMS 5523E

Steel, Corrosion and Heat-Resistant, Sheet, Strip, and Plate
23Cr - 13.5Ni (SAE 30309S)
Solution Heat Treated

(Composition similar to UNS S30908)

RATIONALE

AMS 5523F was revised to require bend testing in accordance with ASTM E 290, and is a Five Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers a corrosion and heat-resistant steel in the form of sheet, strip, and plate.

1.2 Application

These products have been used typically for parts requiring both corrosion and heat resistance and oxidation resistance up to 2000 °F (1093 °C), but usage is not limited to such applications. Strength at elevated temperatures is similar to the room temperature strength of 18-8 type steels.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS 2242	Tolerances, Corrosion and Heat-Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate
AMS 2248	Chemical Check Analysis Limits, Wrought Corrosion and Heat-Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
AMS 2371	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS 2807	Identification, Carbon and Low Alloy Steels, Corrosion and Heat-Resistant Steels and Alloys, Sheet, Strip, Plate and Aircraft Tubing
AS4194	Sheet and Strip Surface Finish Nomenclature

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2006 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM A 370	Mechanical Testing of Steel Products
ASTM A 480/A 480M	Flat Rolled Stainless and Heat-Resisting Steel Plate, Sheet, and Strip
ASTM E 290	Bend Testing of Material for Ductility
ASTM E 353	Chemical Analysis of Stainless, Heat Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - COMPOSITION

Element	min	max
Carbon	--	0.08
Manganese	--	2.00
Silicon	--	1.00
Phosphorous	--	0.040
Sulfur	--	0.030
Chromium	22.00	24.00
Nickel	12.00	15.00
Molybdenum	--	0.75
Copper	--	0.75

3.1.1 Check Analysis

Composition variations shall meet the applicable requirements of AMS 2248.

3.2 Condition

The product shall be supplied in the following condition:

3.2.1 Sheet and Strip

Cold rolled, solution heat treated free from continuous carbide network, and, unless solution heat treatment is performed in an atmosphere yielding a bright finish, descaled having a surface appearance in accordance with ASTM A 480/A 480M and AS4194 comparable to 3.2.1.1 and 3.2.1.2 as applicable.

3.2.1.1 Sheet

No. 2D finish.

3.2.1.2 Strip

No. 1 strip finish.

3.2.2 Plate

Hot rolled, solution heat treated free from continuous carbide network, and descaled.

3.3 Properties

The product shall conform to the following requirements: tensile, hardness and bend testing shall be performed in accordance with ASTM A370:

3.3.1 Tensile Properties

Shall be as shown in Table 2.

TABLE 2A - TENSILE PROPERTIES, INCH/POUND UNITS

Nominal Thickness Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset psi, min	Elongation in 2 Inches or 4D %, min
Over 0.002 to 0.003, incl	110 max	--	20
Over 0.003 to 0.004, incl	105 max	--	30
Over 0.004	75 - 100	30.0	40

TABLE 2B - TENSILE PROPERTIES, SI UNITS

Nominal Thickness mm	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa, min	Elongation in 50.8 mm or 4D %, min
Over 0.051 to 0.076, incl	758 max	--	20
Over 0.076 to 0.102, incl	724 max	--	30
Over 0.102	517 - 689	207	40

3.3.2 Hardness

Shall not be higher than 95 HRB, or equivalent (see 8.2).

3.3.3 Bending

Product 0.749 inch (19.02 mm) and under in nominal thickness shall be tested in accordance with ASTM E 290 using a sample prepared nominally 0.75 inch (19.05 mm) in width with its axis of bending parallel to the direction of rolling and shall withstand, without cracking, bending at room temperature through the angle and bend diameter indicated in Table 3. In case of dispute, the results of tests using the guided bend test of ASTM E 290 shall govern.

TABLE 3 - BENDING REQUIREMENTS

Nominal Thickness Inch	Nominal Thickness mm	Angle deg, min	Bend Factor
Up to 0.249, incl	Up to 6.32, incl	180	1
Over 0.249 to 0.749, incl	Over 6.32 to 19.02, incl	90	1

3.4 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances

Shall conform to all applicable requirements of AMS 2242.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1), tensile properties (3.3.1), hardness (3.3.2), bending (3.3.3 - only for product 0.1874 inch (4.72 mm) and under in nominal thickness) and tolerances (3.5) are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests

Bending (3.3.3 - for product over 0.1874 inch (4.72 mm) to 0.749, incl (19.02 mm) in nominal thickness) is a periodic test and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by the purchaser.

4.3 Sampling and Testing

Shall be in accordance with AMS 2371.

4.4 Reports

The vendor of the product shall furnish with each shipment a report showing the results of tests for composition of each heat and for tensile, hardness, and applicable bending properties of each lot. This report shall include the purchase order number, heat and lot numbers, AMS 5523F, size, and quantity.

4.5 Resampling and Retesting

Shall be in accordance with AMS 2371.

5. PREPARATION FOR DELIVERY

5.1 Identification

Shall be in accordance with AMS 2807.

5.2 Packaging

5.2.1 The product shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the product to ensure carrier acceptance and safe delivery.

6. ACKNOWLEDGMENT

A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

7. REJECTIONS

Product not conforming to this specification, or to modifications authorized by purchaser, will be subject to rejection.