

# AEROSPACE MATERIAL SPECIFICATION

**SAE**

**AMS 5526H**

Issued MAR 1948  
Revised OCT 1989  
Noncurrent SEP 1994  
Reaf. Noncur. OCT 2006

Superseding AMS 5526G

Steel Sheet, Strip, and Plate, Corrosion and Heat Resistant  
19.5Cr - 9.5Ni - 1.4Mo - 1.4W - 0.42(Cb+Ta) - 0.22Ti  
Solution Heat Treated

UNS K63198

## RATIONALE

This document has been reaffirmed to comply with the SAE 5-year Review policy.

## NONCURRENT NOTICE

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of September 1994. It is recommended, therefore, that this specification not be specified for new designs.

"NONCURRENT" refers to those materials which have previously been widely used and which may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these as standard materials for future use in new designs. Each of these "NONCURRENT" specifications is available from SAE.

SAENORM.COM : Click to view the full PDF of AMS 5526H

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2006 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:** Tel: 877-606-7323 (inside USA and Canada)  
Tel: 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: CustomerService@sae.org  
http://www.sae.org

**SAE WEB ADDRESS:**

**1. SCOPE:****1.1 Form:**

This specification covers a corrosion and heat resistant steel in the form of sheet, strip, and plate.

**1.2 Application:**

Primarily for parts, such as turbine nozzles, tail pipes, and exhaust cones, requiring high strength up to 1150°F (621°C) and oxidation resistance up to 1600°F (871°C).

**2. APPLICABLE DOCUMENTS:**

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

**2.1 SAE Publications:**

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

**2.1.1 Aerospace Material Specifications:**

AMS 2242	Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate
MAM 2242	Tolerances, Metric, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate
AMS 2248	Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly Alloyed Steels, and Iron Alloys
AMS 2350	Standards and Test Methods
AMS 2371	Quality Assurance Sampling of Corrosion and Heat Resistant, Steels and Alloys, Wrought Products Except Forgings and Forging Stock

**2.2 ASTM Publications:**

Available from ASTM, 1916 Race Street, Philadelphia PA 19103.

ASTM A 370	Mechanical Testing of Steel Products
ASTM E 353	Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

**2.3 U.S. Government Publications:**

Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

## 2.3.1 Military Standards:

MIL-STD-163 Steel Mills Products, Preparation for Shipment and Storage

## 3. TECHNICAL REQUIREMENTS:

## 3.1 Composition:

Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser:

	min	max
Carbon	0.28	0.35
Manganese	0.75	1.50
Silicon	0.30	0.80
Phosphorus	-	0.040
Sulfur	-	0.030
Chromium	18.00	21.00
Nickel	8.00	11.00
Molybdenum	1.00	1.75
Tungsten	1.00	1.75
Columbium + Tantalum	0.25	0.60
Titanium	0.10	0.35
Copper	-	0.50

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

## 3.2 Condition:

The product shall be supplied in the following condition:

- 3.2.1 Sheet: Hot rolled, solution heat treated, and, unless solution heat treatment is performed in an atmosphere yielding a bright finish, descaled having a surface appearance comparable to a No. 2D finish (See 8.2).
- 3.2.2 Strip: Cold rolled, solution heat treated, and, unless solution heat treatment is performed in an atmosphere yielding a bright finish, descaled having a surface appearance comparable to a No. 1 strip finish (See 8.2).
- 3.2.3 Plate: Hot rolled, solution heat treated, and descaled.

### 3.3 Solution Heat Treatment:

The product shall be solution heat treated by heating to 1800°F ± 25 (982°C ± 14), holding at heat for a time commensurate with thickness, and cooling in air.

### 3.4 Properties:

The product shall conform to the following requirements; tensile and bend testing shall be performed in accordance with ASTM A 370:

#### 3.4.1 Tensile Properties: Shall be as follows:

Tensile Strength	95,000 - 120,000 psi (655 - 827 MPa)
Yield Strength at 0.2% Offset, minimum	45,000 psi (310 MPa)
Elongation in 2 inches (50.8 mm) or 4D, minimum	30%

#### 3.4.2 Bending: Product 0.749 inch (19.02 mm) and under in nominal thickness shall withstand, without cracking, bending through the angle indicated below around a diameter equal to the bend factor times the nominal thickness of the product with axis of bend parallel to the direction of rolling. Only one type of test will be required in routine inspection; in case of dispute, results of tests using the V-block procedure shall govern.

Nominal Thickness		Type of Bend	Angle deg, min	Bend Factor
Inch	Millimetres			
Up to 0.050, excl	Up to 1.27, excl	Free Bend	180	2
Up to 0.050, excl	Up to 1.27, excl	V-Block	135	2
0.050 to 0.749, incl	1.27 to 19.02, incl	Free Bend	90	2
0.050 to 0.749, incl	1.27 to 19.02, incl	V-Block	135	4

#### 3.4.2.1 Bending requirements for plate over 0.749 inch (19.02 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

### 3.5 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

### 3.6 Tolerances:

Shall conform to all applicable requirements of AMS 2242 or MAM 2242.

## 4. QUALITY ASSURANCE PROVISIONS:

### 4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

### 4.2 Classification of Tests:

Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each heat or lot as applicable.

### 4.3 Sampling and Testing:

Shall be in accordance with AMS 2371; the number of specimens to be sampled shall be the minimum number of specimens tested.

### 4.4 Reports:

The vendor of the product shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and for tensile and bending properties of each lot. This report shall include the purchase order number, lot number, AMS 5526H, size, and quantity.

### 4.5 Resampling and Retesting:

Shall be in accordance with AMS 2371.

## 5. PREPARATION FOR DELIVERY:

### 5.1 Identification:

Each sheet, strip, and plate shall be marked on one face, in the respective location indicated below, with AMS 5526H, heat number, manufacturer's identification, and nominal thickness. The characters shall be of such size as to be legible, shall be applied using a suitable marking fluid, and shall be removable in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the product or its performance and shall be sufficiently stable to withstand normal handling.

#### 5.1.1 Flat Strip 6 Inches (152 mm) and Under in Width: Shall be marked in one or more lengthwise rows of characters recurring at intervals not greater than 3 feet (914 mm).