

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 5530B

Issued 9-1-47

Revised 12-1-51

ALLOY SHEET, CORROSION AND HEAT RESISTANT
Nickel Base - 17Mo - 16.5Cr - 6Fe - 5W

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. APPLICATION: Primarily for parts such as welded nozzle diaphragm assemblies, burner liner parts, tail pipes, exhaust cone assemblies and other parts requiring high strength up to approximately 1500 F, and oxidation resistance up to 2000 F.
3. COMPOSITION:

Check Analysis
Under Min or Over Max

Ø	Carbon	0.15 max	--	0.01
	Manganese	1.00 max	--	0.03
	Silicon	1.00 max	--	0.05
	Phosphorus	0.040 max	--	0.005
	Sulfur	0.030 max	--	0.005
	Molybdenum	16.00 - 18.00	0.15	0.15
	Chromium	15.50 - 17.50	0.20	0.20
	Iron	4.50 - 7.00	0.15	0.15
	Tungsten	3.75 - 5.25	0.15	0.15
	Vanadium	0.20 - 0.60	0.04	0.04
	Nickel	Remainder		

4. CONDITION: Unless otherwise specified, sheet shall be hot rolled, annealed and pickled, having a surface appearance as close as possible to a commercial corrosion resistant steel No. 2D finish; actual acceptance and rejection standards shall be as agreed upon by purchaser and vendor.

5. TECHNICAL REQUIREMENTS:

5.1 Tensile Properties:

Tensile Strength, psi	100,000 - 145,000
Elongation, % in 2 in.	30 min

- 5.1.1 For widths 9 in. and over, tensile test specimens shall be taken with the axis perpendicular to the direction of rolling. For widths less than 9 in., tensile test specimens shall be taken with the axis parallel to the direction of rolling.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by any person engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to any technical report, in formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringing patents."