

ALLOY SHEET, STRIP, AND PLATE, CORROSION AND HEAT RESISTANT
47.5Ni - 22Cr - 1.5Co - 9.0Mo - 0.60W - 18.5Fe
Solution Heat Treated

UNS N06002

1. SCOPE:

1.1 Form: This specification covers a corrosion and heat resistant nickel alloy in the form of sheet, strip, and plate procured in inch/pound units. MAM 5536 is the equivalent, specified in SI (metric) units, of this AMS.

1.2 Application: Primarily for parts requiring oxidation resistance up to 2200°F and relatively high strength up to 1500°F.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2262 - Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Sheet, Strip, and Plate

AMS 2269 - Chemical Check Analysis Limits, Wrought Nickel Alloys and Cobalt Alloys

AMS 2350 - Standards and Test Methods

AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock

REAFFIRMED

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

- ASTM E8 - Tension Testing of Metallic Materials
- ASTM E112 - Determining Average Grain Size
- ASTM E139 - Conducting Creep, Creep-Rupture, and Stress-Rupture Tests of Metallic Materials
- ASTM E290 - Semi-Guided Bend Test for Ductility of Metallic Materials
- ASTM E354 - Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E354 or by spectrochemical or other analytical methods approved by purchaser:

	min	max
Carbon	0.05	0.15
Manganese	--	1.00
Silicon	--	1.00
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	20.50	23.00
Cobalt	0.50	2.50
Molybdenum	8.00	10.00
Tungsten	0.20	1.00
Iron	17.00	20.00
Aluminum (3.1.1)	--	0.50
Titanium	--	0.15
Boron (3.1.1)	--	0.010
Copper	--	0.50
Nickel	remainder	

3.1.1 Shall be present but shall not exceed the specified limit.

3.1.2 Check Analysis: Composition variations shall meet the requirements of AMS 2269.

3.2 Condition: The product shall be supplied in the following condition:

3.2.1 Sheet and Strip: Hot or cold rolled, solution heat treated, and, unless solution heat treatment is performed in an atmosphere yielding a bright finish, descaled having a surface appearance comparable to the following commercial corrosion-resistant steel finishes as applicable:

3.2.1.1 Sheet: No. 2D finish.

Ø

3.2.1.2 Strip: No. 1 strip finish.

Ø

3.2.2 Plate: Hot rolled, solution heat treated, and descaled.

3.3 Heat Treatment: The product shall be solution heat treated by heating in a suitable atmosphere to 2150°F + 25, except that sheet and strip 0.030 in. and under in nominal thickness may be heated to as low as 2100°F + 25, holding at heat for a time commensurate with product thickness, and rapidly cooling.

3.4 Properties: The product shall conform to the following requirements:

3.4.1 Tensile Properties: Shall be as specified in Table I, determined in accordance with ASTM E8.

TABLE I

Nominal Thickness Inches	Tensile Strength psi, min	Yield Strength at 0.2% Offset psi, min	Elongation in 2 in. or 4D %, min
Up to 0.010, excl	105,000	45,000	--
0.010 to 0.020, excl	105,000	45,000	29
0.020 to 0.187, incl	105,000	45,000	35
Over 0.187 to 2.000, incl	100,000	40,000	35
Over 2.000	95,000	40,000	35

3.4.2 Bending: Product 0.187 in. and under in nominal thickness shall withstand, without cracking, bending at room temperature in accordance with ASTM E290 through an angle of 180 deg around a diameter equal to the bend factor times the nominal thickness of the product with axis of bend parallel to the direction of rolling.

Nominal Thickness Inch	Bend Factor
Up to 0.050, incl	1.5
Over 0.050 to 0.187, incl	2

3.4.2.1 Bending requirements for plate over 0.187 in. in nominal thickness shall be as agreed upon by purchaser and vendor.

3.4.3 Stress-Rupture Properties at 1500°F: A tensile specimen, maintained at 1500°F \pm 3 while a load sufficient to produce an initial axial stress of 16,000 psi is applied continuously, shall not rupture in less than the time indicated below. The test shall be continued to rupture without change of load. Elongation after rupture, measured at room temperature, shall be not less than shown below. Tests shall be conducted in accordance with ASTM E139.

Nominal Thickness Inches	Time to Rupture Hours, min	Elongation % in 4D
0.010 to 0.020, excl	15	3
0.020 and over	24	8

3.4.3.1 The test of 3.4.3 may be conducted using a load higher than required to produce an initial axial stress of 16,000 psi but load shall not be changed while test is in progress. Time to rupture and elongation requirements shall be as specified in 3.4.3.

3.4.3.2 When permitted by purchaser, the test of 3.4.3 may be conducted using incremental loading. In such case, the load required to produce an initial axial stress of 16,000 psi shall be used to rupture or for 24 hr, whichever occurs first. After the 24 hr and at intervals of 8 - 16 hr, preferably 8 - 10 hr, thereafter, the stress shall be increased in increments of 2000 psi. Time to rupture and elongation requirements shall be as specified in 3.4.3.

3.4.3.2.1 The test of 3.4.3.2 applies only to product 0.020 in. and over in nominal thickness.

3.4.4 Grain Size: Sheet and strip 0.125 in. and under in nominal thickness shall have average grain size of 4 or finer, determined in accordance with ASTM E112. Grain size requirements for product over 0.125 in. in nominal thickness shall be as agreed upon by purchaser and vendor.

3.5 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.6 Tolerances: Shall conform to all applicable requirements of AMS 2262.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests: