

ALLOY SHEET, STRIP, AND PLATE, CORROSION AND HEAT RESISTANT
46Fe - 20.5Cr - 32Ni - 1.1Ti
Annealed

UNS N08801

1. SCOPE:

1.1 Form: This specification covers a corrosion and heat resistant alloy in the form of sheet, strip, and plate.

1.2 Application: Primarily for low-stressed parts requiring corrosion and oxidation resistance up to 1800°F (982°C), but useful at the higher temperatures only when stresses are low, and where such parts may require welding during fabrication.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2262 - Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Sheet, Strip, and Plate

MAM 2262 - Tolerances, Metric, Nickel, Nickel Alloy, and Cobalt Alloy Sheet, Strip, and Plate

AMS 2269 - Chemical Check Analysis Limits, Wrought Nickel Alloys and Cobalt Alloys

AMS 2350 - Standards and Test Methods

AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E8 - Tension Testing of Metallic Materials

ASTM E112 - Determining Average Grain Size

ASTM E290 - Semi-Guided Bend Test for Ductility of Metallic Materials

ASTM E354 - Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E354, by spectrochemical methods, or by other analytical methods acceptable to purchaser:

	min	max
Carbon	--	0.10
Manganese	--	1.50
Silicon	--	1.00
Sulfur	--	0.015
Chromium	19.0 -	22.0
Nickel + Cobalt	30.0 -	34.0
Titanium	0.75 -	1.5
Cobalt (3.1.1)	--	1.0
Copper	--	0.5
Iron	remainder	

3.1.1 Determination not required for routine acceptance.

3.1.2 Check Analysis: Composition variations shall meet the requirements of AMS 2269.

3.2 Condition: The product shall be supplied in the following condition:

3.2.1 Sheet and Strip: Cold rolled, annealed, and, unless annealing is performed in an atmosphere yielding a bright finish, descaled having a surface appearance comparable to a commercial corrosion-resistant steel No. 2D finish (See 8.2).

3.2.2 Plate: Hot rolled and annealed; plate shall be descaled, when so ordered.

3.3 Properties: The product shall conform to the following requirements:

3.3.1 Tensile Properties: Shall be as follows, determined in accordance with ASTM E8 on product 0.010 to 2.000 inches (0.25 to 50.80 mm) in nominal thickness:

Tensile Strength	80,000 - 105,000 psi (552 - 724 MPa)
Yield Strength at 0.2% Offset, minimum	30,000 psi (207 MPa)
Elongation in 2 Inches (50.8 mm) or 4D, minimum	30%

3.3.1.1 Tensile property requirements for product under 0.010 inch (0.25 mm) or over 2.000 inches (50.80 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

3.3.2 Bending: Product 0.010 - 0.250 inch (0.25 - 6.35 mm), incl, in nominal thickness shall withstand, without cracking, bending in accordance with ASTM E290 through an angle of 180 degrees around a diameter equal to the bend factor times the nominal thickness of the product with axis of bend parallel to the direction of rolling.

Form	Nominal Thickness		Bend Factor
	Inch	Millimetres	
Sheet and Strip	0.010 to 0.050, incl	0.25 to 1.27, incl	1
Sheet	Over 0.050 to 0.250, incl	Over 1.27 to 6.35, incl	2
Sheet	Over 0.050 to 0.125, incl	Over 1.27 to 3.18, incl	2

3.3.2.1 Bending requirements for product under 0.010 inch (0.25 mm) or over 0.250 inch (6.35 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

3.3.3 Grain Size: Shall be not larger than the following, determined in accordance with ASTM E112:

Form	Nominal Thickness		ASTM Grain Size No.
	Inch	Millimetres	
Sheet	0.010 to 0.050, incl	0.25 to 1.27, incl	4
	Over 0.050 to 0.250, incl	Over 1.27 to 6.35, incl	3
Strip	0.010 to 0.125, incl	0.25 to 3.18, incl	4

3.3.3.1 Grain size requirements for sheet and strip under 0.010 inch (0.25 mm), for strip over 0.125 inch (3.18 mm), and for plate shall be as agreed upon by purchaser and vendor.

3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances: Shall conform to all applicable requirements of AMS 2262 or MAM 2262.

4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.
- 4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each heat or lot as applicable.
- 4.3 Sampling: Shall be in accordance with AMS 2371.
- 4.4 Reports:
- 4.4.1 The vendor of the product shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and the results of tests on each lot to determine conformance to the other technical requirements of this specification. This report shall include the purchase order number, lot number, AMS 5552D, size, and quantity.
- 4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 5552D, contractor or other direct supplier of product, part number, and quantity. When product for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of product to determine conformance to the requirements of this specification and shall include in the report either a statement that the product conforms or copies of laboratory reports showing the results of tests to determine conformance.
- 4.5 Resampling and Retesting: Shall be in accordance with AMS 2371.

5. PREPARATION FOR DELIVERY:

- 5.1 Identification: Each sheet, strip, and plate shall be marked on one face, in the respective location indicated below, with AMS 5552D, heat number, manufacturer's identification, and nominal thickness. The characters shall be of such size as to be legible, shall be applied using a suitable marking fluid, and shall be removable in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the product or its performance and shall be sufficiently stable to withstand normal handling.
- 5.1.1 Flat Strip 6 Inches (152 mm) and Under in Width: Shall be marked in one or more lengthwise rows of characters recurring at intervals not greater than 3 feet (914 mm).
- 5.1.2 Flat Sheet, Flat Strip Over 6 Inches (152 mm) in Width, and Plate: Shall be marked in lengthwise rows of characters recurring at intervals not greater than 3 feet (914 mm), the rows being spaced not more than 6 inches (152 mm) apart and alternately staggered.