

Steel, Corrosion and Heat-Resistant, Seamless Tubing
16.5Cr - 4.5Ni - 2.9Mo - 0.10N
Annealed

(Composition similar to UNS S35000)

RATIONALE

AMS 5554E is a Five Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers a corrosion and heat-resistant steel in the form of thin-wall seamless tubing.

1.2 Application

This tubing has been used typically for parts, such as fluid lines, requiring high strength and oxidation resistance up to 800 °F (427 °C), but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS 2243	Tolerances, Corrosion and Heat-Resistant Steel Tubing
AMS 2248	Chemical Check Analysis Limits, Corrosion and Heat-Resistant Steels and Alloys, Maraging, and Other Highly-Alloyed Steels, and Iron Alloys
AMS 2371	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS 2634	Ultrasonic Inspection, Thin Wall Metal Tubing
AMS 2807	Identification, Carbon and Low-Alloy Steels, Corrosion and Heat-Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2006 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM E 8/E 8M	Tension Testing of Metallic Materials
ASTM E 353	Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys
ASTM E 426	Electromagnetic (Eddy-Current) Examination of Seamless and Welded Tubular Products, Austenitic Stainless Steel and Similar Alloys
ASTM E 1417	Liquid Penetrant Examination

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	0.08	0.12
Manganese	0.50	1.25
Silicon	--	0.50
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	16.00	17.00
Nickel	4.00	5.00
Molybdenum	2.50	3.25
Nitrogen	0.07	0.13

3.1.1 Check Analysis

Composition variations shall meet the applicable requirements of AMS 2248.

3.2 Condition

Cold drawn, annealed, and descaled.

3.3 Fabrication

Tubing shall be produced by a seamless process. Any surface finishing operation applied to remove objectionable pits and surface blemishes shall be performed prior to final anneal. A light polish to improve external surface appearance may be employed after solution heat treatment and, if performed, the product shall be subsequently passivated.

3.4 Heat Treatment

Tubing shall be annealed by heating to 1850 to 1975 °F (1010 to 1079 °C), holding at the selected temperature within ± 25 °F (± 14 °C) for a time commensurate with cross-sectional wall thickness, and cooling as rapidly as possible to room temperature.

3.5 Properties

Tubing shall conform to the following requirements:

3.5.1 As Received

3.5.1.1 Flarability

Specimens as in 4.3.1 from tubing 0.500 to 2.000 inches (12.70 to 50.80 mm), inclusive, in nominal OD shall withstand, without formation of cracks or other visible defects, flaring at room temperature by being forced axially with steady pressure over a hardened and polished tapered steel pin having a 74-degree included angle to produce a flare having a permanent expanded OD not less than 1.20 times the original nominal OD.

3.5.1.1.1 Flarability requirements for tubing under 0.500 inch (12.70 mm) or over 2.000 inches (50.80 mm) in nominal OD shall be as agreed upon by purchaser and vendor.

3.5.2 After Reannealing, Precipitation Hardening, and Tempering

Tubing shall have the following properties after being reannealed by heating to 1710 °F ± 25 (932 °C ± 14), holding at heat for not less than 90 minutes per inch (25 mm) of wall thickness, and cooling in air to room temperature, heating to 1375 °F ± 25 (746 °C ± 14), holding at heat for not less than 1 hour, cooling in air to room temperature, heating to 850 °F ± 25 (454 °C ± 14), holding at heat for not less than 3 hours, and cooling in air to room temperature:

3.5.2.1 Tensile Properties

Shall be as shown in Table 2, determined in accordance with ASTM E 8 or ASTM E 8M.

TABLE 2 - Minimum Tensile Properties

Property	Value
Tensile Strength	165 ksi (1138 MPa)
Yield Strength at 0.2% Offset	130 ksi (896 MPa)
Elongation in 2 inches (50.8 mm)	10%

3.6 Quality

Tubing, as received by purchaser, shall be uniform in quality and condition and shall have a finish conforming to the best practice for high quality aircraft tubing. It shall be smooth and free from heavy scale or oxide, burrs, seams, tears, grooves, laminations, slivers, pits, and other imperfections detrimental to usage of the tubing. Surface imperfections, such as handling marks, straightening marks, light mandrel and die marks, shallow pits, and scale pattern, will not be considered injurious if the imperfections are removable within the tolerances specified for wall thickness, but removal of such imperfections is not required.

3.6.1 When specified by purchaser, tubing shall be subjected to fluorescent penetrant inspection in accordance with ASTM E 1417, to ultrasonic inspection in accordance with AMS 2634, to electromagnetic (Eddy-Current) examination in accordance with ASTM E 426, or to any combination thereof. Standards for acceptance shall be as established by purchaser.

3.7 Tolerances

Shall conform to all applicable requirements of AMS 2243.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of tubing shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the tubing conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1), nondestructive inspection when specified (3.6.1), and tolerances (3.8) are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests

Flarability (3.5.1.1) and tensile properties (3.5.2.1) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing

Shall be in accordance with AMS 2371 and the following:

4.3.1 Specimens for flarability test (3.5.1.1) shall be full tubes or sections cut from a tube. The end of the specimen to be flared shall be cut square, with the cut end smooth and free from burrs, but not rounded.

4.4 Reports

The vendor of the product shall furnish with each shipment a report showing the results of tests for composition of each heat and for nondestructive inspection, when specified, and tolerances of each lot, and stating that the product conforms to the other technical requirements. This report shall include the purchase order number, heat and lot numbers, AMS 5554E, size, and quantity.

4.5 Resampling and Retesting

Shall be in accordance with AMS 2371.

5. PREPARATION FOR DELIVERY

5.1 Sizes

Except when exact lengths or multiples of exact lengths are ordered, straight tubing will be acceptable in mill lengths of 6 to 20 feet (1.8 to 6.1 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 feet (3 m).

5.2 Identification

Shall be in accordance with AMS 2807.

5.3 Packaging

Tubing shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the tubing to ensure carrier acceptance and safe delivery.