

AEROSPACE MATERIAL SPECIFICATION

SAE AMS5569

REV. B

Issued	1993-07
Reaffirmed	2006-04
Revised	2011-07
Superseding AMS5569A	

Steel, Corrosion and Heat Resistant, Seamless and Welded Hydraulic Tubing
19Cr - 9.5Ni - 0.03C max
Cold Drawn, 1/8 Hard Temper

(Composition similar to UNS S30403)

RATIONALE

AMS5569B revises referenced documents and is a Five Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers a corrosion and heat resistant steel in the form of two types of thin-wall, close-tolerance tubing 0.125 to 2.00 inches (3.18 to 50.8 mm), inclusive, in nominal OD.

1.2 Application

This tubing has been used typically in high pressure hydraulic or pneumatic systems assembled with brazed joints, but usage is not limited to such applications.

1.3 Classification

The tubing covered by this specification is classified as follows:

Class 1 - Seamless and Drawn
Class 2 - Welded and Drawn

1.3.1 Unless a specific class is ordered, either class may be supplied.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2011 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS5569B>**

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

- AMS2248 Chemical Check Analysis Limits, Corrosion and Heat-Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
- AMS2371 Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock
- AMS2700 Passivation of Corrosion Resistant Steels
- AMS2807 Identification, Carbon and Low-Alloy Steels, Corrosion and Heat-Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

- ASTM A 262 Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels
- ASTM A 370 Mechanical Testing of Steel Products
- ASTM E 112 Determining Average Grain Size
- ASTM E 353 Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys
- ASTM E 426 Electromagnetic (Eddy Current) Examination of Seamless and Welded Tubular Products, Austenitic Stainless Steel and Similar Alloys
- ASTM E 1417 Liquid Penetrant Testing

2.3 ANSI Publications

Available from American National Standards Institute, Inc., 25 West 43rd Street, New York, NY 10036-8002, Tel: 212-642-4900, www.ansi.org.

- ANSI B46.1 Surface Texture

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - COMPOSITION

Element	min	max
Carbon	--	0.03
Manganese	--	2.00
Silicon	--	1.00
Phosphorus	--	0.04
Sulfur	--	0.03
Chromium	18.0	20.0
Nickel	8.0	11.0
Molybdenum	--	0.50
Copper	--	0.75

3.1.1 Check Analysis

Composition variations shall meet the applicable requirements of AMS2248.

3.2 Condition

Solution heat treated, cold drawn, pickled as required, and passivated.

3.3 Fabrication

3.3.1 Class 1

Tubing shall be produced by a seamless process.

3.3.2 Class 2

Tubing shall be produced by the gas-metal-arc, gas-tungsten-arc, or plasma arc process and subsequently drawn. Tubing shall contain no more than one longitudinal weld and no circumferential welds. Tubing shall be processed to remove any dimensional indication of the presence of welds.

3.3.3 Tensile properties shall be obtained by cold working and not by heat treatment. A minimum reduction of 30 percent is recommended for Class 2 tubing.

3.3.4 The external and internal surface finishes shall not be rougher than 32 microinches (0.8 μm) and 63 microinches (1.6 μm) respectively, determined in accordance with ANSI B 46.1, and may be produced by any method yielding the specified surface condition that will not affect limits of wall thickness or corrosion resistance, with the exception that grinding is not acceptable. A light polish to improve surface appearance may be employed.

3.4 Properties

Tubing shall conform to the following requirements; tensile and bend testing shall be performed in accordance with ASTM A 370:

3.4.1 Tensile properties shall be as shown in Table 2 and 3.4.1.1.

TABLE 2 - TENSILE PROPERTIES

Property	Value
Tensile Strength	105 - 140 ksi (724 - 965 MPa)
Yield Strength at 0.2% Offset	75 - 100 ksi (517 - 689 MPa)
Elongation, minimum	
Full Section	20%
Strip	15%

3.4.1.1 Tubing under 0.50 inch (12.7 mm) in nominal OD, and having wall thickness of 0.02 inch (0.5 mm) or under, may have elongation as low as 16% when tested in full section.

3.4.2 Bending

Tubes shall show no evidence of cracking or splitting when bent cold around a suitable mandrel of diameter equal to the bend factor shown in Table 3 times the nominal OD. During test, flattening shall not exceed 5 percent of the minimum OD. An appropriate internal mandrel may be used. For Class 2 tubing, the weld shall be at the outside of the bend. A suitable etchant may be used to locate the weld.

TABLE 3 - BENDING PARAMETERS

Nominal OD Inches	Nominal OD Millimeters	Bend Factor
0.25 to 1.00, incl	6.4 to 25.4, incl	3
Over 1.00 to 1.75, incl	Over 25.4 to 44.5, incl	4
Over 1.75 to 2.00, incl	Over 44.5 to 50.8, incl	5

3.4.2.1 Flattening during testing is defined in Equation 1.

$$\% \text{ Flattening} = \frac{(\text{max OD} - \text{min OD})}{\text{nominal OD}} \times 100 \quad (\text{Eq. 1})$$

3.4.3 Susceptibility to Intergranular Attack

Tubing shall pass the copper-copper sulfate-sulfuric acid test of ASTM A 262, Practice E. Samples shall be taken from tubing after final annealing prior to cold working.

3.4.4 Average Grain Size

Shall be ASTM No. 6 or finer, determined in accordance with ASTM E 112. In case of dispute, the Heyn Intercept method of ASTM E 112 shall be used.

3.4.5 Passivity

Surfaces shall show no reactions indicating active surfaces when subjected to either the copper sulfate test or the potassium ferrocyanide-nitric acid test defined in AMS2700, Annex A.

3.4.6 Pressure Resistance

When specified, tubing shall withstand for not less than 1 minute, an internal hydrostatic pressure (P) as defined below, or 15.0 ksi, whichever is less. There shall not be any leaking or developing bulges, pinholes, cracks, or other defects except that a diametric permanent set not exceeding 0.002 inch/inch (0.002 mm/mm) is permissible. P shall be determined from Equation 2.

$$P = S \frac{(D^2 - d^2)}{(D^2 + d^2)} \quad (\text{Eq. 2})$$

where:

- P = Test pressure in ksi (MPa)
- S = 75 ksi (517 MPa) yield strength
- D = Nominal OD (nominal OD plus tolerance)
- d = Nominal ID (D minus twice minimum wall thickness)

3.4.7 Flarability

Tubing shall withstand flaring at room temperature, without the formation of cracks or other visible defects, by being forced axially with steady pressure over a hardened and polished tapered steel pin having a 74-degree included angle to produce a flare having a permanent expanded OD not less than shown in Table 4.

TABLE 4A - MINIMUM FLARABILITY, INCH/POUND UNITS

Nominal OD Inches	Expanded OD Inches	Nominal OD Inches	Expanded OD Inches
0.250	0.359	0.750	0.937
0.312	0.421	1.000	1.187
0.375	0.484	1.250	1.500
0.500	0.656	1.500	1.721
0.625	0.781	1.750	2.106
		2.000	2.356

TABLE 4B - MINIMUM FLARABILITY, SI UNITS

Nominal OD Millimeters	Expanded OD Millimeters	Nominal OD Millimeters	Expanded OD Millimeters
6.35	9.12	19.05	23.80
7.92	10.69	25.40	30.15
9.52	12.29	31.75	38.10
12.50	16.66	38.10	43.71
15.88	19.84	44.45	53.49
		50.80	59.84

3.4.7.1 Tubing with nominal OD between any two standard sizes given in Table 4 shall take the same percentage flare as shown for the larger of the two sizes.

3.5 Quality

Tubing, as received by purchaser, shall be uniform in quality and condition and shall have a finish conforming to the best practice for high quality aircraft tubing. It shall be smooth and free from heavy scale or oxide, burrs, seams, tears, grooves, laminations, slivers, pits, or other imperfections detrimental to usage of the tubing.

3.5.1 Mechanically-induced isolated minor surface imperfections, such as handling marks, straightening marks, light mandrel or die marks, shall not exceed the values shown in Table 5.

TABLE 5A - MAXIMUM DEPTH OF DISCONTINUITY, INCH/POUND UNITS

Nominal Wall Thickness Inch	Depth of Discontinuity Inch
Up to 0.020, incl	10% of nominal wall thickness
Over 0.020 to 0.030, incl	0.002
Over 0.030 to 0.040, incl	0.0025
Over 0.040 to 0.074, incl	0.003

TABLE 5B - MAXIMUM DEPTH OF DISCONTINUITY, SI UNITS

Nominal Wall Thickness Millimeters	Depth of Discontinuity Millimeter
Up to 0.51, incl	10% of nominal wall thickness
Over 0.51 to 0.76, incl	0.05
Over 0.76 to 1.02, incl	0.064
Over 1.02 to 1.88, incl	0.08

- 3.5.1.1 Discontinuities having large root radii plainly visible to the unaided eye, whose surfaces blend into the nominal tubing surfaces, and whose depths do not exceed the maximum depth of acceptable discontinuity or violate wall thickness tolerances, are acceptable. Other surface discontinuities shall be removed by polishing or buffing within the limits of wall thickness tolerances or maximum depth of acceptable discontinuity.
- 3.5.2 Tubing shall be free from grease or other foreign matter. Metallic flakes or particles shall not be collected by a clean white cloth or wad of cotton drawn through the length of the bore of a test sample. Discoloration of the cloth or wad of cotton, without the presence of flakes or particles, is acceptable.
- 3.5.3 When standards for acceptance are specified by purchaser, tubing shall be subjected to fluorescent penetrant testing in accordance with ASTM E 1417.
- 3.5.4 Class 1 tubing shall be eddy current inspected in accordance with ASTM E 426 using calibration notches specified in ASTM A 450 except that the standard used shall contain simulated flaws not greater than those shown in Table 5 of this specification.
- 3.5.5 Class 2 tubing shall be subjected to ultrasonic inspection in accordance with AMS2634, Class A1.

3.6 Tolerances

Shall conform to all applicable requirements of AMS2243, as applicable to half tolerances.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of tubing shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmation testing deemed necessary to ensure that the tubing conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1), surface finish (3.3.4), tensile properties (3.4.1), bending (3.4.2), average grain size (3.4.4), flarability (3.4.7), quality (3.5), eddy current inspection (3.5.4), ultrasonic inspection (3.5.5), and tolerances (3.6) are acceptance tests and shall be performed on each heat, lot, or tube as applicable.

4.2.2 Periodic Tests

Susceptibility to intergranular attack (3.4.3), passivity (3.4.5), and pressure resistance (3.4.6) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.