

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS5570B

Issued 12-4-39
~~11-1-41~~
Revised 6-1-42

SEAMLESS STEEL TUBING, CORROSION AND HEAT RESISTANT 18 Chromium - 8 Nickel

1. ACKNOWLEDGMENT: A vendor must mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. COMPOSITION:

Carbon	0.10 max
Manganese	0.20 - 2.50
Silicon	0.20 - 1.50
Copper	0.50 max
Phosphorus	0.04 max
Sulphur	0.04 max
Chromium	17.00 min
Nickel	7.00 min
Columbium	8 times C min
or	
Titanium	4 times C min

3. CONDITION: (a) Solution heat treated and pickled.

(b) Test pieces pulled at the rate of .05 inch per inch per minute shall conform to the following physical properties:

Tensile Strength, lb per sq inch	100,000 max
Elongation, % in 2 in., strip	35 min
Elongation, % in 2 in., full section	40 min

(c) The tubing shall be capable of being expanded on a hardened and polished tapered steel pin having a 60° included angle, to a diameter 35% greater than the original diameter without cracking.

4. QUALITY: (a) The material must be uniform in quality and temper free from surface and internal defects and must not reveal material defects during fabrication.

(b) The material shall be free from grease or other foreign matter and shall have a workmanlike finish.

5. EMBRITTELEMENT: The material shall be capable of meeting the following test but the actual conducting of the test is an option of the purchaser:

After being heated to 1200°F for two hours and air cooled, embrittlement test specimens shall withstand a 48 hour boiling in 10% copper sulphate, 10% sulphuric acid solution without evidence of intercrystalline surface attack. After such immersion, the specimens must withstand cold bending through an angle of 180° over a diameter equal to the thickness of the specimen without cracking.