



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
TWO PENNSYLVANIA PLAZA, NEW YORK, N. Y. 10001

AMS 5577C
Superseding AMS 5577B

Issued 2-15-52
Revised 12-1-73

STEEL TUBING, WELDED, CORROSION AND HEAT RESISTANT 25Cr - 20Ni (SAE 30310)

1. SCOPE:

- 1.1 Form: This specification covers a corrosion and heat resistant steel in the form of welded tubing.
- 1.2 Application: Primarily for parts and assemblies requiring both corrosion and heat resistance, especially when such parts and assemblies are welded during fabrication. Parts and assemblies requiring oxidation resistance up to approximately 2000°F (1093°C) but useful at that temperature only when stresses are low.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., Two Pennsylvania Plaza, New York, New York 10001.

2.1.1 Aerospace Material Specifications:

- AMS 2243 - Tolerances, Corrosion and Heat Resistant Steel Tubing
- AMS 2248 - Chemical Check Analysis Limits, Wrought Heat and Corrosion Resistant Steels and Alloys
- AMS 2350 - Standards and Test Methods
- AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Alloys, Wrought Products Except Forgings

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.

- ASTM A370 - Mechanical Testing of Steel Products
- ASTM E353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

- 2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, Pennsylvania 19120.

2.3.1 Federal Standards:

- Federal Test Method Standard No. 151 - Metals; Test Methods

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other approved analytical methods:

SAE Technical Board rules provide that: "All technical reports, including standards, app and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

	min	max
Carbon	--	0.08
Manganese	--	2.00
Silicon	--	0.75
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	24.00 -	26.00
Nickel	19.00 -	22.00
Molybdenum	--	0.75
Copper	--	0.50

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

3.2 Condition: Solution heat treated free from continuous carbide network and descaled.

3.3 Fabrication: Tubing shall be produced by the welded and drawn process. Any surface finishing operation applied to remove objectionable pits and surface blemishes shall be performed prior to final solution heat treatment. A light polish to improve surface appearance may be employed after solution heat treatment. Passivation treatment shall follow any polishing treatment.

3.4 Properties: The product shall conform to the following requirements:

3.4.1 Tensile Properties: Shall be as specified in Table I, determined in accordance with ASTM A370:

TABLE I

Nominal OD Inches	Tensile Strength psi, max	Elongation % in 2 in., min	
		Strip	Full Tube
Up to 0.312, excl	105,000	35	40
0.312 and over	100,000	35	40

TABLE I (SI)

Nominal OD Millimeters	Tensile Strength MPa, max	Elongation % in 50.8 mm, min	
		Strip	Full Tube
Up to 7.92, excl	724	35	40
7.92 and over	690	35	40

3.4.2 Flarability: Tubing shall be capable of being flared without formation of cracks or other visible defects. The specimen shall, at room temperature, be forced axially with steady pressure over a hardened and polished tapered steel pin having a 74 deg (1.29 rad) included angle, to produce a flare having the permanent expanded OD specified in Table II.

TABLE II

Nominal OD Inches	Expanded OD Inches	Nominal OD Inches	Expanded OD Inches
0.125	0.200	0.750	0.937
0.188	0.290	1.000	1.187
0.250	0.359	1.250	1.500
0.312	0.421	1.500	1.721
0.375	0.484	1.750	2.106
0.500	0.656	2.000	2.356
0.625	0.781		

TABLE II (SI)

Nominal OD Millimeters	Expanded OD Millimeters	Nominal OD Millimeters	Expanded OD Millimeters
3.18	5.08	19.04	23.80
4.78	7.36	25.40	30.15
6.35	9.11	31.75	38.10
7.93	11.70	38.10	43.71
9.54	12.29	44.45	53.49
12.70	16.68	50.80	59.74
15.88	19.82		

- 3.4.2.1 Tubing with nominal OD between any two standard sizes given in 3.4.2 shall take the same percentage flare as shown for the larger of the two sizes.
- 3.4.2.2 Tubing with nominal OD greater than 2.000 in. (50.80 mm) or less than 0.125 in. (3.180 mm) shall have flarability as agreed upon by purchaser and vendor.
- 3.4.3 Pressure Testing: Tubing shall show no bulges, leaks or other defects when subjected to an internal hydrostatic pressure, based on nominal dimensions, sufficient to cause a tensile stress of 20,000 psi (138 MPa) in the tubing wall.
- 3.5 Quality:
- 3.5.1 Tubing shall be uniform in quality and condition and shall have a workmanlike finish conforming to the best practice for high quality material. It shall be smooth, clean, and free from heavy scale or oxide, burrs, seams, tears, grooves, laminations, slivers, pits, and other injurious conditions. Surface imperfections such as handling marks, straightening marks, light mandrel and die marks, shallow pits, and scale pattern will not be considered injurious if the imperfections are removable within the tolerances specified for wall thickness. The removal of surface imperfections is not required.
- 3.5.2 If beads are present at the welds on the inner surface of the tubing, such beads shall not be thicker than 0.010 in. (0.25 mm) unless otherwise specified. The outer surfaces of the tubing shall be free from beads.
- 3.6 Sizes: Except when exact lengths or multiples of exact lengths are ordered, tubing will be acceptable in mill lengths of 6 - 20 ft (1.8 - 6.1 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 ft (3 m).
- 3.7 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of AMS 2243.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of tubing shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to assure that the tubing conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to composition (3.1), condition (3.2), tensile property (3.4.1), pressure test (3.4.3) and tolerance (3.7) requirements are classified as acceptance or routine control tests.

4.2.2 Qualification Tests: Tests to determine conformance to flarability (3.4.2) requirements are classified as qualification or periodic control tests.

4.3 Sampling: Shall be in accordance with AMS 2371 and the following:

4.3.1 Specimens for flaring may be cut from any portion of a tube or an entire tube may be used as a specimen. The end of the specimen to be flared shall be cut square, with the cut end smooth and free from burrs, but not rounded.

4.4 Reports:

4.4.1 The vendor of tubing shall furnish with each shipment three copies of a report of the results of tests for chemical composition of each heat in the shipment and for tensile properties and pressure test of each size from each heat. This report shall include the purchase order number, heat number, material specification number and its revision letter, size, and quantity from each heat.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number and its revision letter, contractor or other direct supplier of tubing, part number, and quantity. When tubing for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of tubing to determine conformance to the requirements of this specification, and shall include in the report a statement that the tubing conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.

4.5 Resampling and Retesting: If any specimen used in the above tests fails to meet the specified requirements, disposition of the tubing may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the tubing represented and no additional testing shall be permitted. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

5.1 Identification: Tubing shall be identified as follows:

5.1.1 Straight Tubes 0.029 In. (0.74 mm) and Over in Wall Thickness and 0.500 In. (12.70 mm) and Over in OD, Minor Axis, or Least Width of Flat Surface: Shall be marked in a row of characters recurring at intervals not greater than 3 ft (914 mm) with AMS 5577C, heat number, manufacturer's identification, and nominal wall thickness. The characters shall be of such size as to be clearly legible, shall be applied using a suitable marking fluid, and shall be capable of being removed in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the material or its performance and shall be sufficiently stable to withstand normal handling.

5.1.2 Straight Tubes Under 0.029 In. (0.74 mm) in Wall Thickness or Under 0.500 In. (12.70 mm) in OD, Minor Axis, or Least Width of Flat Surface: Shall be securely bundled and identified by a metal or plastic tag embossed with the above information and the nominal OD and attached to each bundle or shall be boxed and the box marked with the same information.