

AEROSPACE MATERIAL SPECIFICATION



AMS 5579C

Issued JUL 1961
Revised JAN 1987
Noncurrent JUL 1992
Reaf. Noncur. NOV 2000

Superseding AMS 5579B

Steel, Corrosion and Heat Resistant, Tubing Welded
19.5Cr - 9.5Ni - 1.4Mo - 1.4W - 0.42(Cb + Ta) - 0.22Ti
Thin Wall

UNS S63198

NONCURRENT NOTICE

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of July, 1992. It is recommended, therefore, that this specification not be specified for new designs.

"NONCURRENT" refers to those materials which have previously been widely used and which may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these as standard materials for future use in new designs. Each of these "NONCURRENT" specifications is available from SAE.

SAENORM.COM : Click to view the full PDF of AMS 5579C

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2000 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

1. SCOPE:**1.1 Form:**

This specification covers a corrosion and heat resistant steel in the form of welded tubing.

1.2 Application:

Primarily for high-pressure air ducting requiring both corrosion and heat resistance wherein the wall thickness is approximately 2% of the nominal OD or less.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2248	Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
AMS 2350	Standards and Test Methods
AMS 2371	Quality Assurance Sampling of Corrosion and Heat Resistant, Steels and Alloys, Wrought Products Except Forgings and Forging Stock
AMS 2635	Radiographic Inspection

2.2 ASTM Publications:

Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia PA 19103.

ASTM A262	Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels
ASTM A370	Mechanical Testing of Steel Products
ASTM E353	Chemical Analysis of Stainless, Heat-Resisting, Maraging and Other Similar Chromium-Nickel-Iron Alloys

2.3 U.S. Government Publications:

Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353 or by spectrographic or other analytical methods approved by purchaser:

	min	max
Carbon	0.28	0.35
Manganese	0.75	1.50
Silicon	0.30	0.80
Phosphorus	--	0.040
Sulfur		0.030
Chromium	18.00	21.00
Nickel	8.00	11.00
Molybdenum	1.00	1.75
Tungsten	1.00	1.75
Columbium + Tantalum	0.25	0.60
Titanium	0.10	0.35
Copper	--	0.50

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2248.

3.2 Condition:

As welded, descaled, and passivated. Tubing shall have been rolled only enough to ensure proper weld bead height and roundness in the weld bead area.

3.3 Fabrication:

Tubing shall be fabricated from solution heat treated sheet or strip, shall be machine fusion welded by gas-metal-arc process, shall contain not more than one longitudinal weld, and shall contain no circumferential welds. Tube ends shall be cut square and deburred. Tubing, except for the weld bead, shall have a surface appearance comparable to a commercial corrosion-resistant steel No. 2D sheet finish.

3.4 Properties:

Tubing shall conform to the following requirements; tensile and bend testing shall be performed in accordance with ASTM A370:

3.4.1 Tensile Properties: Shall be as follows:

Tensile Strength	95,000 - 125,000 psi (655 - 860 MPa)
Yield Strength at 0.2% Offset, min	45,000 psi (310 MPa)
Elongation in 2 in. (50 mm), min	
Strip (See 4.3.1)	30%
Full Section	35%

3.4.2 Bending: A specimen as in 4.3.2 shall withstand, without evidence of cracks or other imperfections when examined at 10X magnification, bending at room temperature 180 deg around a diameter equal to two times the nominal wall thickness of the tubing with axis of bend perpendicular to axis of weld and with outside of tube on inside of bend.

3.4.3 Weld Crack Susceptibility: A specimen as in 4.3.3 shall withstand, without evidence of cracks occurring in, or adjacent to, the weld bead when examined at 10X magnification, being pulled parallel to the direction of the weld bead until rupture occurs.

3.4.4 Embrittlement: Specimens of tubing taken to include the weld, after sensitization treatment, shall pass the copper/copper sulfate/sulfuric acid test performed in accordance with ASTM A262, Practice E, without evidence of intercrystalline surface attack. After exposure, specimens shall withstand, without cracking, bending at room temperature through an angle of 180 deg around a diameter equal to two times the nominal thickness of the specimen with axis of bend perpendicular to the axis of the tubing.

3.4.5 Pressure Test: After all fabricating and sizing operations, each length of tubing shall withstand for 1 min., without leakage or developing bulges, permanent set, or other imperfections which exceed the allowable tolerances for the finished tubing, a gradually applied internal hydrostatic pressure (P), calculated from the following equation:

$$P = \frac{2St}{D}$$

where,

P = Test pressure in psi (MPa)

S = 20,000 psi (140 MPa) tensile stress

t = Nominal wall thickness

D = Nominal OD

3.4.6 Weld Strength: Shall be as follows, determined in accordance with 3.4.6.1 or 3.4.6.2.

3.4.6.1 Hydrostatic Pressure Tests: A specimen as in 4.3.4 shall withstand an internal hydrostatic pressure of 95,000 psi (655 MPa) for not less than 60 sec without rupture. Hydrostatic pressure (P) shall be calculated from the equation of 3.4.5 and shall be applied gradually in 30 - 60 sec at not lower than 60°F (15°C).

3.4.6.2 Tensile Strength: Shall be not lower than 95,000 psi (655 MPa), determined on specimens as in 4.3.5.

3.5 Quality:

3.5.1 Tubing, as received by purchaser, shall be uniform in contour, quality, and condition and shall have a finish conforming to the best practice for high quality aircraft tubing. It shall be clean, sound, and free from grease, oil, and other foreign matter. It shall be free from burrs, cracks, tears, grooves, seams, laminations, dents, crimps, and other imperfections detrimental to usage of the tubing.

3.5.2 The weld in each length of tubing shall, prior to rolling, be subjected to radiographic inspection in accordance with AMS 2635 and shall conform to acceptance standards agreed upon by purchaser and vendor to guarantee against the shipment of tubing with any of the following imperfections in or adjacent to the weld: porosity, pinholes, entrapped slag, cracks, mismatches, lack of fusion, undercutting, or other imperfections which cause sharp notches or a reduction of thickness greater than 10% of parent metal wall thickness.

3.5.2.1 Metal thinning in, or adjacent to, the weld shall be permissible if not greater than 10% of parent metal wall thickness provided also that it presents only gradual transitions.

3.5.2.2 Individual lengths of tubing which contain no weld imperfections other than metal thinning in excess of 10% of parent metal wall thickness may be reinspected radiographically after rolling. If rolling has reduced the metal thinning to less than 10% of parent metal wall thickness, the thinning indicated by the first radiograph will not be cause for rejection.

3.5.2.3 Each length of tubing in a shipment shall be accompanied by its radiographs.

3.5.3 Mechanical imperfections, such as light handling marks and light tool marks, are acceptable provided they have not dented the wall of the tube and are gradual in contour to a maximum depth of 10% of parent metal wall thickness.

3.5.4 The weld flash shall not extend in height beyond the contour of the adjacent metal more than 0.0025 in. (0.062 mm) on either outside or inside of the tubing and the sum of both outside and inside weld flash heights shall not exceed 0.004 in. (0.10 mm).

3.6 Sizes:

Except when exact lengths or multiples of exact lengths are ordered, straight tubing will be acceptable in mill lengths of 6 - 20 ft (2 - 6 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 ft (3 m).

3.7 Tolerances:

Shall be as follows:

3.7.1 Diameter:

TABLE I

Nominal OD Inches	Tolerance, Inch Minus Only
1.000 to 2.500, incl	0.005
Over 2.500 to 3.500, incl	0.007
Over 3.500 to 4.500, incl	0.009
Over 4.500 to 7.000, incl	0.012

TABLE I (SI)

Nominal OD Millimetres	Tolerance, Millimetre Minus Only
25.00 to 62.50, incl	0.12
Over 62.50 to 87.50, incl	0.18
Over 87.50 to 112.50, incl	0.22
Over 112.50 to 175.00, incl	0.30

3.7.1.1 Outside diameter shall be measured using a periphery or PI tape.

3.7.2 Wall Thickness:

TABLE II

Nominal Wall Thickness Inch	Tolerance, Inch Plus and Minus
0.010 to 0.016, incl	0.002
Over 0.016 to 0.026, incl	0.003
Over 0.026 to 0.040, incl	0.004
Over 0.040 to 0.058, incl	0.005
Over 0.058 to 0.072, incl	0.006

TABLE II (SI)

Nominal Wall Thickness Millimetres	Tolerance, Millimetre Plus and Minus
0.25 to 0.40, incl	0.05
Over 0.40 to 0.65, incl	0.08
Over 0.65 to 1.00, incl	0.10
Over 1.00 to 1.45, incl	0.12
Over 1.45 to 1.80, incl	0.15

- 3.7.3 Ovality: For tubing having nominal wall thickness of 0.040 in. (1.00 mm) and under, ovality shall not exceed 6% of the nominal OD. For tubing having nominal wall thickness over 0.040 in. (1.00 mm), tolerances in Table III shall apply.

TABLE III

Nominal OD		Tolerance % of OD
Inches	Millimetres	
1.000 to 1.250, incl	25.00 to 31.25, incl	5.0
Over 1.250 to 1.500, incl	Over 31.25 to 37.50, incl	4.0
Over 1.500 to 1.750, incl	Over 37.50 to 43.75, incl	3.5
Over 1.750 to 2.000, incl	Over 43.75 to 50.00, incl	3.0
Over 2.000 to 2.500, incl	Over 50.00 to 62.50, incl	2.5
Over 2.500 to 7.000, incl	Over 62.50 to 125.00, incl	2.0

- 3.7.3.1 Ovality is obtained by dividing the difference between the maximum and minimum OD of any one station along the tube by the nominal OD and multiplying by 100.
- 3.7.4 Length: Cut-to-length tubing shall not vary from the length ordered by more than +1/8 in. (+3 mm), -0.
- 3.7.5 Straightness: When measured using a 3-ft (900-mm) straight edge touching the tube at two points, the perpendicular distance from the straight edge to the tube at any point between the two points of contact, shall not exceed $0.030 \times L/3$ in., where "L" is the distance in feet between points of contact or shall not exceed $0.83 \times L$ mm, where "L" is the distance in metres between points of contact.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of tubing shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the tubing conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1), tensile properties (3.4.1), bending (3.4.2), weld crack susceptibility (3.4.3), pressure test (3.4.5), weld strength (3.4.6), quality (3.5), and tolerances (3.7) are classified as acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests: Test to determine conformance to requirements for embrittlement (3.4.4) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling:

Shall be in accordance with AMS 2371 and the following:

4.3.1 Strip specimens for tensile testing shall be taken parallel to the tubing axis, shall have a 2 in. (50 mm) gage length, and shall not include the weld bead.

4.3.2 Specimens for bending shall be 2 in. (50 mm) square or larger cut from tubing and through the weld.

4.3.3 Specimens for weld crack susceptibility shall be cut from a tube in such a manner as to include at least 6 in. (150 mm) of weld bead and 1/4 in. (6 mm) of the tube wall on each side of the weld. The edges shall be smooth and free from burrs.

4.3.4 Specimens for weld strength hydrostatic pressure test (3.4.6.1) shall be full cross-section of the tubing, the unsupported length of which shall be not less than 2 ft (600 mm) or 6 times the nominal OD, whichever is greater.

4.3.5 Specimens for weld strength tensile test (3.4.6.2) shall be taken perpendicular to the direction of the weld and shall include the weld near the center of the gage length.

4.4 Reports:

4.4.1 The vendor of tubing shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and for tensile properties and weld strength of each lot, and stating that the tubing conforms to the other acceptance test requirements of this specification. This report shall include the purchase order number, heat number, AMS 5579C, size, and quantity.