

AEROSPACE MATERIAL SPECIFICATION



AMS 5581D

Issued JAN 1977
Revised JUN 2001

Superseding AMS 5581C

Nickel Alloy, Corrosion and Heat Resistant, Seamless or Welded Tubing
62Ni - 21.5Cr - 9.0Mo - 3.7Cb
Annealed

(Composition similar to UNS N06625)

1. SCOPE:

1.1 Form:

This specification covers a corrosion and heat resistant nickel alloy in the form of two types of tubing.

1.2 Application:

This tubing has been used typically for fluid lines requiring high strength and corrosion resistance at temperatures from cryogenic to 1800 °F (982 °C), but usage is not limited to such applications.

1.3 Classification:

The tubing covered by this specification is classified as follows:

Type 1 - Seamless and drawn

Type 2 - Welded and drawn

1.3.1 Unless a specific type is specified, either Type 1 or Type 2 may be supplied.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2001 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2263	Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Tubing
MAM 2263	Tolerance, Metric, Nickel, Nickel Alloy, and Cobalt Alloy Tubing
AMS 2269	Chemical Check Analysis Limits, Nickel, Nickel Alloys and Cobalt Alloys
AMS 2371	Quality Assurance Sampling and Testing , Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS 2807	Identification, Carbon and Low-Alloy Steels, Corrosion and Heat Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM A 370	Mechanical Testing of Steel Products
ASTM E 112	Determining Average Grain Size
ASTM E 354	Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys
ASTM E 407	Microetching Metals and Alloys

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	--	0.10
Manganese	--	0.50
Silicon	--	0.50
Phosphorus	--	0.015
Sulfur	--	0.015
Chromium	20.00	23.00
Molybdenum	8.00	10.00
Columbium	3.15	4.15
Titanium (3.1.1)	--	0.40
Aluminum (3.1.1)	--	0.40
Cobalt (3.1.2)	--	1.00
Iron	--	5.00
Nickel	remainder	

3.1.1 Shall be present but not in excess of specified maximum.

3.1.2 Determination not required for routine acceptance.

3.1.3 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2269.

3.2 Condition:

Solution heat treated, and unless solution heat treatment is performed in an atmosphere yielding a bright finish, pickled as required.

3.3 Fabrication:

Tubing shall be produced by a seamless and drawn or a welded and drawn process. A light polish to improve external surface appearance may be employed after cold drawing.

3.3.1 Welded (Type 2) tubing shall be cold reduced after welding to remove the bead and any dimensional indication of the presence of welds.

3.4 Properties:

Tubing shall conform to the following requirements:

3.4.1 Tensile Properties: Shall be as shown in Table 2, determined in accordance with ASTM A 370.

TABLE 2 - Minimum Tensile Properties

Property	Value
Tensile Strength	120 ksi (827 MPa)
Yield Strength at 0.2% Offset	60 ksi (414 MPa)
Elongation in 2 Inches (50.8 mm)	35%

3.4.2 Flarability: Specimens as in 4.3.1 shall withstand flaring at room temperature, without formation of cracks or other visible defects, by being forced axially with steady pressure over a hardened and polished tapered steel pin having a 74-degree included angle to produce a flare having a permanent expanded OD not less than specified in Table 3.

TABLE 3A - Flarability, Inch/Pound Units

Nominal OD Inch	Expanded OD Inch	Nominal OD Inches	Expanded OD Inches
0.125	0.200	0.750	0.937
0.188	0.302	1.000	1.187
0.250	0.359	1.250	1.500
0.312	0.421	1.500	1.721
0.357	0.484	1.750	2.106
0.500	0.656	2.000	2.356
0.625	0.781		

TABLE 3B - Flarability, SI Units

Nominal OD Millimeters	Expanded OD Millimeters	Nominal OD Millimeters	Expanded OD Millimeters
3.18	5.08	19.05	23.80
4.78	7.67	25.40	30.15
6.35	9.12	31.75	38.10
7.92	10.69	38.10	43.71
9.52	12.29	44.45	53.49
12.70	16.66	50.80	59.84
15.88	19.84		

3.4.2.1 Tubing with nominal OD between any two standard sizes given in Table 3 shall take the same percentage flare as shown for the larger of the two sizes.

- 3.4.3 Pressure Test: Tubing, when subjected to an internal hydrostatic pressure (P) as determined from Equation 1, shall show no bulges, leaks, pinholes, cracks, or other defects, except that a diametric permanent set of 0.002 inch per inch (0.002 mm/mm) of diameter is acceptable.

$$P = S \frac{D^2 - d^2}{D^2 + d^2} \quad (\text{Eq. 1})$$

where, P = Test pressure in ksi (MPa)
S = 60.0 ksi (414 MPa)
D = Nominal OD
d = Nominal ID

- 3.4.4 Microstructure: Tubing shall reveal no continuous intergranular carbide precipitation when suitably etched and examined microscopically at 500X magnification. The presence of some discontinuous intergranular carbide precipitation shall not be considered detrimental if the other technical requirements are met. Standards for acceptance may be as agreed upon by purchaser and vendor.
- 3.4.5 Average Grain Size: Shall be ASTM No. 5 or finer, determined by comparison of a specimen, polished and electrolytically etched in accordance with ASTM E 407, with the chart in ASTM E 112, using 100X magnification.

3.5 Quality:

Tubing, as received by purchaser, shall be uniform in quality and condition and shall have a finish conforming to the best practice for high quality aircraft tubing. It shall be smooth and free from heavy scale or oxide, burrs, seams, tears, grooves, laminations, slivers, pits, and other imperfections detrimental to usage of the tubing. Surface imperfections such as handling marks, straightening marks, light mandrel and die marks, shallow pits, and scale pattern will not be considered injurious if the imperfections are removable within the tolerances specified for wall thickness but removal of such imperfections is not required.

- 3.5.1 Tubing shall be free from grease or other foreign matter. Metallic flakes or particles shall not be collected by a clean, white cloth when it is drawn through the length of the bore of a test sample. Discoloration of the cloth, without the presence of flakes or particles, is acceptable.

3.6 Tolerances:

Shall conform to of AMS 2263 or MAM 2263.