

AEROSPACE MATERIAL SPECIFICATION



AMS 5588F

Issued FEB 1965
Revised DEC 2000
Reaffirmed APR 2006

Superseding AMS 5588E

Nickel Alloy, Corrosion and Heat Resistant, Welded Tubing
47.5Ni - 22Cr - 1.5Co - 9.0Mo - 0.60W - 18.5Fe
Solution Heat Treated

UNS N06002

1. SCOPE:

1.1 Form:

This specification covers a corrosion and heat resistant nickel alloy in the form of welded and drawn tubing.

1.2 Application:

This tubing has been used typically for fluid lines operating in service under appreciable stresses at elevated temperatures, but usage is not limited to such applications. Alloy has good strength up to 1800 °F (982 °C) and oxidation resistance up to 2200 °F (1204 °C).

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2263	Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Tubing
MAM 2263	Tolerances, Metric, Nickel, Nickel Alloy, and Cobalt Alloy Tubing
AMS 2269	Chemical Check Analysis Limits, Nickel, Nickel Alloys and Cobalt Alloys
AMS 2371	Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS 2632	Ultrasonic Inspection of Thin Materials, 0.5 Inch (13 mm) and Thinner
AMS 2807	Identification, Carbon and Low-Alloy Steels, Corrosion and Heat Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2006 SAE International

All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:

TO PLACE A DOCUMENT ORDER:

SAE WEB ADDRESS:

(724) 772-7161

(724) 776-4970

<http://www.sae.org>

FAX: (724) 776-0243

FAX: (724) 776-0790

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM E 8	Tension Testing of Metallic Materials
ASTM E 8M	Tension Testing of Metallic Materials (Metric)
ASTM E 112	Determining the Average Grain Size
ASTM E 354	Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys
ASTM E 426	Electromagnetic (Eddy-Current) Examination of Seamless and Welded Tubular Products, Austenitic Stainless Steel and Similar Alloys
ASTM E 1417	Liquid Penetrant Examination

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 -- Composition

Element	min	max
Carbon	0.05	0.15
Manganese	--	1.00
Silicon	--	1.00
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	20.50	23.00
Cobalt	0.50	2.50
Molybdenum	8.00	10.00
Tungsten	0.20	1.00
Iron	17.00	20.00
Aluminum	--	0.50
Titanium	--	0.15
Boron	--	0.010
Copper	--	0.50
Nickel	remainder	

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2269.

3.2 Condition:

Solution heat treated, and unless solution heat treatment is performed in an atmosphere yielding a bright finish, pickled as required. No specific solution heat treating instructions are specified but it is recommended that the tubing be solution heat treated by heating in a suitable protective atmosphere to 2150 °F ± 25 (1177 °C ± 14), holding at heat for a time commensurate with section thickness, and cooling rapidly. In no case shall the solution heat treatment temperature be lower than 2100 °F (1149 °C).

3.3 Fabrication:

Tubing shall be fabricated from hot or cold rolled strip, fusion welded without addition of filler metal, cold drawn, and solution heat treated. The cold drawing operation on tubing 3.0 inches (76 mm) and under in nominal OD shall result in not less than 15% reduction in wall thickness; the amount of wall thickness reduction on tubing over 3.0 inches (76 mm) in nominal OD shall be as agreed upon by purchaser and vendor.

3.4 Properties:

Tubing shall conform to the following requirements:

- 3.4.1 Tensile Properties: Shall be as shown in Table 2, determined in accordance with ASTM E 8 or ASTM E 8M on tubing having nominal OD of 0.125 inch (3.18 mm) and over with nominal wall thickness of 0.015 inch (0.38 mm) and over.

TABLE 2 - Minimum Room Temperature, Tensile Properties

Property	Value
Tensile Strength	100 ksi (689 MPa)
Yield Strength at 0.2% Offset	45.0 ksi (310 MPa)
Elongation in 2 Inches (50.8 mm)	
Strip Specimens	20%
Full-Section Specimens	25%

- 3.4.2 Average Grain Size: Shall be ASTM No. 4 or finer, determined in accordance with ASTM E 112, for tubing 0.125 inch (3.18 mm) and under in nominal wall thickness.
- 3.4.3 Flarability: Specimens as in 4.3.1 shall withstand, without formation of cracks or other visible defects, flaring at room temperature by being forced axially with steady pressure over a hardened and polished tapered steel pin having a 74-degree included angle to produce a flare having a permanent expanded OD not less than 1.2 times the original nominal diameter.

- 3.4.4 Pressure Test: Tubing shall show no bulges, leaks, pinholes, cracks, or other defects when subjected to an internal hydrostatic pressure (P), except that a diametric permanent set of 0.002 inch per inch (0.002 mm/mm) of diameter is acceptable. The hydrostatic pressure (P) shall be determined from Equation 1.

$$P = S \frac{D^2 - d^2}{D^2 + d^2} \quad (\text{Eq. 1})$$

where:

P = Test pressure in ksi (MPa)

S = 45.0 ksi (310 MPa)

D = Nominal OD in inches (mm)

d = Nominal ID in inches (mm)

3.5 Quality:

Tubing, as received by purchaser, shall be uniform in quality and condition and shall have a finish conforming to the best practice for high quality aircraft tubing. It shall be smooth and free from grease, oil and other matter, heavy scale or oxide, burrs, seams, tears, grooves, laminations, slivers, pits, and other imperfections detrimental to usage of the tubing. Surface imperfections such as handling marks, straightening marks, light mandrel and die marks, shallow pits, and scale pattern will not be considered injurious if the imperfections are removable within the tolerances specified for wall thickness, but removal of such imperfections is not required.

- 3.5.1 If beads are present at the weld on the inner surface of tubing over 3.0 inches (76 mm) in nominal OD, such weld reinforcement shall be not thicker than 0.010 inch (0.25 mm). The outer surface of all tubing and the inner surface of tubing 3.0 inches (76 mm) and under in nominal OD shall be free from weld reinforcement.

- 3.5.2 When specified by purchaser, tubing shall be subjected to fluorescent penetrant inspection in accordance with ASTM E 1417, to ultrasonic inspection in accordance with AMS 2632, to electromagnetic (eddy-current) inspection in accordance with ASTM E 426, or to any combination thereof. Standards for acceptance shall be as agreed upon by purchaser and vendor.

3.6 Tolerances:

Shall conform to all applicable requirements of AMS 2263 or MAM 2263.