

# AEROSPACE MATERIAL SPECIFICATIONS

## AMS 5592

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

Issued 7-15-63  
Revised

STEEL SHEET, STRIP, AND PLATE, HEAT RESISTANT  
18.5Cr - 35Ni - 1.15Si

1. ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. APPLICATION: Primarily for parts and assemblies requiring heat and oxidation resistance at elevated temperatures and where such assemblies may require welding during fabrication. Oxidation resistant up to 2100 F (1150 C).
3. COMPOSITION:

Carbon	0.08	max
Manganese	2.00	max
Silicon	0.75	- 1.50
Phosphorus	0.030	max
Sulphur	0.030	max
Chromium	17.00	- 20.00
Nickel	34.00	- 37.00
Copper	0.50	max
Tin	0.025	max
Lead	0.005	max

- 3.1 Check Analysis: Composition variations shall meet the requirements of the latest issue of AMS 2248.

4. CONDITION:

- 4.1 Sheet 0.050 In. and Over Thick: Hot rolled, solution heat treated free from continuous carbide network, and descaled.
- 4.2 Sheet Under 0.050 In. Thick and Strip: Cold rolled, solution heat treated free from continuous carbide network, and descaled.
- 4.3 Plate: Hot rolled, solution heat treated free from continuous carbide network, and descaled.

5. TECHNICAL REQUIREMENTS:

- 5.1 Tensile Properties:

Tensile Strength, psi	70,000	min
Elongation, % in 2 in.	30	min

- 5.1.1 Elongation requirement does not apply to sheet or strip under 0.020 in. in thickness.

- 5.2 Hardness: Shall be not higher than Rockwell B 95 or equivalent.

Section 8.3 of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and issuing technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the reports are responsible for protecting themselves against liability for infringement of patents."