

STEEL SHEET, STRIP, AND PLATE, CORROSION AND HEAT RESISTANT
18.5Cr - 35Ni - 1.15Si
Solution Heat Treated

UNS N08330

1. SCOPE:

1.1 Form: This specification covers a corrosion and heat resistant steel in the form of sheet, strip, and plate.

1.2 Application: Primarily for parts requiring heat and oxidation resistance up to 2150°F (1177°C).

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2242 - Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate

MAM 2242 - Tolerances, Metric, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate

AMS 2248 - Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys

AMS 2350 - Standards and Test Methods

AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A370 - Mechanical Testing of Steel Products

ASTM E353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, \emptyset determined by wet chemical methods in accordance with ASTM E353, by spectrochemical methods, or by other analytical methods acceptable to purchaser:

	min	max
Carbon	--	0.08
Manganese	--	2.00
Silicon	0.75 -	1.50
Phosphorus	--	0.030
Sulfur	--	0.030
Chromium	17.00 -	20.00
Nickel	34.00 -	37.00
Copper	--	0.50
Tin	--	0.025
Lead	--	0.005

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

3.2 Condition: The product shall be supplied in the following condition:

3.2.1 Sheet and Strip: Hot or cold rolled, solution heat treated, and, unless \emptyset solution heat treatment is performed in an atmosphere yielding a bright finish, descaled, having a surface appearance comparable to a commercial corrosion-resistant steel No. 2D finish (See 8.2).

3.2.2 Plate: Hot rolled, solution heat treated, and descaled.

3.3 Properties: The product shall conform to the following requirements; tensile and hardness testing shall be performed in accordance with ASTM A370:

3.3.1 Tensile Properties: Shall be as follows:

Tensile Strength, minimum	70,000 psi (483 MPa)
Yield Strength at 0.2% Offset, minimum	30,000 psi (207 MPa)
Elongation in 2 inches (50.8 mm) or 4D, minimum	30%

- 3.3.1.1 Elongation requirement does not apply to sheet or strip under 0.020 inch (0.51 mm) in nominal thickness.
- 3.3.2 Hardness: Should be not higher than 95 HRB, or equivalent, but the product shall not be rejected on the basis of hardness provided tensile properties are met.
- 3.3.3 Microstructure: Shall be free from continuous carbide networks, determined by metallographic examination.
- 3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.
- 3.5 Tolerances: Shall conform to all applicable requirements of AMS 2242 or MAM 2242.

4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.
- 4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each heat or lot as applicable.
- 4.3 Sampling: Shall be in accordance with AMS 2371.
- 4.4 Reports:
- 4.4.1 The vendor of the product shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and for tensile properties and hardness of each lot. This report shall include the purchase order number, lot number, AMS 5592B, size, and quantity.
- 4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 5592B, contractor or other direct supplier of product, part number, and quantity. When product for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of product to determine conformance to the requirements of this specification and shall include in the report either a statement that the product conforms or copies of laboratory reports showing the results of tests to determine conformance.
- 4.5 Resampling and Retesting: Shall be in accordance with AMS 2371.

5. PREPARATION FOR DELIVERY:

5.1 Identification: Each sheet, strip, and plate shall be marked on one face, in the respective location indicated below, with AMS 5592B, heat number, manufacturer's identification, and nominal thickness. The characters shall be of such size as to be legible, shall be applied using a suitable marking fluid, and shall be removable in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the product or its performance and shall be sufficiently stable to withstand normal handling.

5.1.1 Flat Strip 6 Inches (152 mm) and Under in Width: Shall be marked in one or more lengthwise rows of characters recurring at intervals not greater than 3 feet (914 mm).

5.1.2 Flat Sheet, Flat Strip Over 6 Inches (152 mm) in Width, and Plate: Shall be marked in lengthwise rows of characters recurring at intervals not greater than 3 feet (914 mm), the rows being spaced not more than 6 inches (152 mm) apart and alternately staggered.

5.1.3 Coiled Sheet and Strip: Shall be marked near both the outside and inside ends of the coil; the markings shall be applied as in 5.1 or shall appear on a durable tag or label attached to the coil and marked with the information of 5.1. When the product is wound on cores, the tag or label may be attached to the core.

5.2 Packaging:

5.2.1 The product shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the product to ensure carrier acceptance and safe delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.

5.2.2 For direct U.S. Military procurement, packaging shall be in accordance with MIL-STD-163, Level A or Level C, as specified in the request for procurement. Commercial packaging as in 5.2.1 will be acceptable if it meets the requirements of Level C.

6. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

7. REJECTIONS: Product not conforming to this specification, or to modifications authorized by purchaser, will be subject to rejection.

8. NOTES: