

AEROSPACE MATERIAL SPECIFICATION



AMS 5595F

Issued NOV 1968
Revised APR 2001
Reaffirmed APR 2006

Superseding AMS 5595E

Steel, Corrosion Resistant, Sheet, Strip, and Plate
9.0Mn - 20Cr - 6.5Ni - 0.28N
Solution Heat Treated

(Composition similar to UNS S21904)

1. SCOPE:

1.1 Form:

This specification covers a corrosion-resistant steel in the form of sheet, strip, and plate.

1.2 Application:

These products have been used typically for parts requiring high strength and corrosion resistance from -423 to +1100 °F (-253 to +593 °C), where such parts may require welding during fabrication, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2242	Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate
MAM 2242	Tolerances, Metric, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate
AMS 2248	Chemical Check Analysis Limits, Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
AMS 2371	Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS 2807	Identification, Carbon and Low-Alloy Steels, Corrosion and Heat Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2006 SAE International
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM A 262	Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels
ASTM A 370	Mechanical Testing of Steel Products
ASTM E 112	Determining Average Grain Size
ASTM E 353	Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	--	0.04
Manganese	8.00	10.00
Silicon	--	1.00
Phosphorus	--	0.060
Sulfur	--	0.030
Chromium	19.00	21.50
Nickel	5.50	7.50
Nitrogen	0.15	0.40
Molybdenum	--	0.75
Copper	--	0.75

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2248.

3.2 Condition:

The product shall be supplied in the following condition:

3.2.1 Sheet and Strip: Cold rolled, solution heat treated, and, unless solution heat treatment is performed in an atmosphere yielding a bright finish, descaled having a surface appearance comparable to 3.2.1.1 or 3.2.1.2 as applicable (See 8.2).

3.2.1.1 Sheet: No. 2D finish, except No. 2B finish may be supplied if acceptable to purchaser (See 8.4.1).

3.2.1.2 Strip: No. 1 strip finish.

3.2.2 Plate: Hot rolled, solution heat treated, and descaled.

3.3 Solution Heat Treatment:

The product shall be solution heat treated by heating to a temperature not lower than 1900 °F (1038 °C), holding at the selected temperature within ± 25 °F (± 14 °C) for a time commensurate with cross-sectional thickness and the heating equipment and procedure used, and cooling at a rate equivalent to a rapid air cool or faster.

3.4 Properties:

The product shall conform to the following requirements; tensile, hardness, and bend testing shall be performed in accordance with ASTM A 370:

3.4.1 Average Grain Size: Shall be as shown in Table 2, determined in accordance with ASTM E 112.

TABLE 2 - Average Grain Size

Inch	Millimeters	ASTM Grain Size No.
Up to 0.1875, excl	Up to 4.762, excl	7 or finer
0.1875 to 1.00 incl	4.762 to 25.4, incl	3 or finer

3.4.2 Tensile Properties: Shall be as shown in Table 3:

TABLE 3A - Minimum Tensile Properties, Inch/Pound Units

Nominal Thickness Inch	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches or 4D %
Up to 0.1875, excl	100	60	40
0.1875 and over	90	50	40

TABLE 3B - Minimum Tensile Properties, SI Units

Nominal Thickness Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm or 4D %
Up to 4.762, excl	689	414	40
4.762 and over	621	345	40

- 3.4.3 Hardness: Should be not higher than 100 HRB, or equivalent (See 8.3). Product shall not be rejected on the basis of hardness if the tensile properties are acceptable, determined on specimens taken from the same sample as that with nonconforming hardness, or another sample with similar nonconforming hardness.
- 3.4.4 Bending: Product 0.749 inch (19.02 mm) and under in nominal thickness shall withstand, without cracking, bending through the angle shown in Table 4 around a diameter equal to the bend factor times the nominal thickness of the product with axis of bend parallel to the direction of rolling. Only one type of test will be required in routine inspection; in case of dispute, results of tests using the V-block procedure shall govern.

TABLE 4 - Bending Parameters

Nominal Thickness Inch	Nominal Thickness Millimeters	Type of Bend	Angle Deg, min	Bend Factor
Up to 0.249, incl	Up to 6.32, incl	Free Bend	180	1
Up to 0.249, incl	Up to 6.32, incl	V-Block	135	1
Over 0.249 to 0.749, incl	Over 6.32 to 19.02, incl	Free Bend	90	1
Over 0.249 to 0.749, incl	Over 6.32 to 19.02, incl	V-Block	135	2

- 3.4.5 Susceptibility to Intergranular Attack: Specimens shall be sensitized by heating in air to 1250 °F ± 10 (677 °C ± 6), holding at heat for 60 minutes ± 5, and cooling in air. The sensitized specimens shall show no evidence of intergranular attack when immersed in acidified copper sulfate solution in accordance with ASTM A 262, Practice E, except that exposure time shall be 72 hours and metallic copper shall not be added. After immersion, the specimens shall withstand, without cracking, bending in accordance with ASTM A 262, Practice E.
- 3.5 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.