



AEROSPACE MATERIAL SPECIFICATION	AMS5604™	REV. K
	Issued 1968-05 Reaffirmed 2006-10 Revised 2023-02	
Superseding AMS5604J		
Steel, Corrosion Resistant, Sheet, Strip, and Plate 16.5Cr - 4.0Ni - 4.0Cu - 0.30Cb Solution Heat Treated, Precipitation Hardenable (Composition similar to UNS S17400)		

RATIONALE

AMS5604K is the result of a Five-Year Review and update of the specification. The revision clarifies the prohibition unauthorized exceptions (1.1, 3.5, 3.9, 8.4), updates composition testing and reporting (3.1, 3.1.1), clarifies heat treatment (3.3), incorporates strain rate control during tensile testing (3.4.1.1.1, 3.4.2.1.1), and provides specific acceptance requirements for hardness testing (3.4.1.2).

1. SCOPE

1.1 Form

This specification covers a corrosion-resistant steel in the form of sheet, strip, and plate 4.0 inches (102 mm) and under in nominal thickness.

1.2 Application

These products have been used typically for parts requiring corrosion resistance and high strength up to 600 °F (316 °C) and where such parts may require welding during fabrication, but usage is not limited to such applications.

1.2.1 Certain processing procedures and service conditions may cause these products to become subject to stress-corrosion cracking; ARP1110 recommends practices to minimize such conditions.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2023 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS5604K/>

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2242	Tolerances, Corrosion- and Heat-Resistant Steel, Iron Alloy, Titanium and Titanium Alloy Sheet, Strip, and Plate
AMS2248	Chemical Check Analysis Limits, Corrosion- and Heat-Resistant Steels and Alloys, Maraging and Other Highly Alloyed Steels, and Iron Alloys
AMS2315	Determination of Delta Ferrite Content
AMS2371	Quality Assurance Sampling and Testing, Corrosion- and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS2750	Pyrometry
AMS2807	Identification, Carbon and Low-Alloy Steels, Corrosion- and Heat-Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing
ARP1110	Minimizing Stress Corrosion Cracking in Wrought Forms of Steels and Corrosion-Resistant Steels and Alloys
AS4194	Sheet and Strip Surface Finish Nomenclature
AS6279	Standard Practice for Production, Distribution, and Procurement of Metal Stock
AS7766	Terms Used in Aerospace Metals Specifications

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM A370	Mechanical Testing of Steel Products
ASTM A480/A480M	Flat-Rolled Stainless and Heat-Resisting Steel Plate, Sheet, and Strip
ASTM A751	Chemical Analysis of Steel Products
ASTM E290	Bend Testing of Material for Ductility

2.3 Definitions

Terms used in AMS are defined in AS7766.

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by in accordance with ASTM A751 or by other analytical methods acceptable to purchaser.

Table 1 - Composition

Element	Min	Max
Carbon	--	0.07
Manganese	--	1.00
Silicon	--	1.00
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	15.00	17.50
Nickel	3.00	5.00
Columbium	5xC	0.45
Copper	3.00	5.00
Molybdenum	--	0.50

3.1.1 Producer may test for any element not listed in Table 1 and include this analysis in the report of 4.4. Reporting of any element not listed in the composition table is not a basis for rejection, unless limits of acceptability are specified by the purchaser.

3.1.2 Check Analysis

Composition variations shall meet the applicable requirements of AMS2248.

3.2 Condition

The product shall be supplied in the following condition:

3.2.1 Sheet and Strip

Cold rolled, solution heat treated, and, unless solution heat treatment is performed in an atmosphere yielding a bright finish, descaled having a surface appearance described in ASTM A480/A480M, AS4194, and 3.2.1.1 or 3.2.1.2, as applicable.

3.2.1.1 Sheet

No. 2D finish.

3.2.1.2 Strip

No. 1 strip finish.

3.2.2 Plate

Hot rolled, solution heat treated, and descaled.

3.3 Solution Heat Treatment

Except as specified in 3.3.1, the product shall be solution heat treated by heating in a suitable atmosphere to 1900 °F ± 25 °F (1038 °C ± 14 °C), holding at heat for a time commensurate with the thickness and the heating equipment and procedure used, and cooling to below 90 °F (32 °C). Pyrometry shall conform to AMS2750.

3.3.1 Continuous Heat Treating of Sheet and Strip

When continuous heat treating is used process parameters (e.g., furnace temperature set points, heat input, travel rate, etc.) for continuous heat-treating lines shall be established by the material producer and validated by testing of product to requirements of 3.4. Plate shall not be subjected to continuous heat treating.

3.4 Properties

The product shall conform to the following requirements; tensile, hardness, and bend testing shall be performed in accordance with ASTM A370:

3.4.1 As Solution Heat Treated

3.4.1.1 Tensile Properties

Shall be as shown in Table 2 for nominal thickness 0.015 to 0.1874 inch (0.38 to 4.760 mm), inclusive.

Table 2 - Solution treated tensile properties

Property	Value
Tensile Strength, Max	185 ksi (1276 MPa)
Yield Strength at 0.2% Offset, Max	160 ksi (1103 MPa)
Elongation in 2 Inches (50 mm), Min	3%

3.4.1.1.1 Unless otherwise specified, the strain rate shall be set at 0.005 in/in/min (0.005 mm/mm/min) and maintained within a tolerance of ± 0.002 in/in/min (± 0.002 mm/mm/min) through 0.2% offset yield strain. After the yield strain, the speed of the testing machine shall be set between 0.05 in/in and 0.5 in/in (0.05 mm/mm and 0.5 mm/mm) of the length of the reduced parallel section (or distance between the grips for specimens not having a reduced section) per minute. Alternatively, an extensometer and strain rate indicator may be used to set the strain rate between 0.05 in/in/min and 0.5 in/in/min (0.05 mm/mm/min and 0.5 mm/mm/min). The requirement for compliance becomes effective for material produced 1 year after the publication date of this document.

3.4.1.2 Hardness

Shall be not higher than 38 HRC, 352 HBW, or 392 HV. Acceptance shall be determined using one of the hardness test methods listed. Material shall not be rejected if acceptable test results are obtained by any of the hardness test methods listed.

3.4.1.3 Microstructure

The product shall contain not more than 5% ferrite, determined in accordance with AMS2315.

3.4.1.4 Bending

Product 0.109 inch (2.77 mm) and under in nominal thickness shall be tested in accordance with ASTM E290 using a sample prepared nominally 0.75 inch (19.0 mm) in width with its axis of bending parallel to the direction of rolling and shall withstand, without cracking, bending through an angle of 180 degrees around a diameter equal to 18 times the nominal thickness of the product. In case of dispute, the results of tests using the guided bend test of ASTM E290 shall govern.

3.4.2 Response to Precipitation Heat Treatment

Samples from solution heat treated product 4.0 inches (102 mm) and under in nominal thickness shall have tensile properties specified in 3.4.2.1 and hardness specified in 3.4.2.2 after being precipitation heat treated to a particular condition in accordance with the corresponding temperature and times shown in Table 3 and cooled as required. Tensile and hardness tests shall be made in only the H900 condition unless purchaser specifies another heat-treated condition.

Table 3 - Precipitation hardening conditions

Condition	Temperature	Time
H900	900 °F ± 10 °F (482 °C ± 6 °C)	60 minutes ± 5 minutes
H925	925 °F ± 10 °F (496 °C ± 6 °C)	4 hours ± 0.25 hour
H1025	1025 °F ± 10 °F (552 °C ± 6 °C)	4 hours ± 0.25 hour
H1075	1075 °F ± 10 °F (579 °C ± 6 °C)	4 hours ± 0.25 hour
H1100	1100 °F ± 10 °F (593 °C ± 6 °C)	4 hours ± 0.25 hour
H1150	1150 °F ± 10 °F (621 °C ± 6 °C)	4 hours ± 0.25 hour

3.4.2.1 Tensile Properties

Shall be as shown in Table 4.

Table 4A - Minimum tensile properties after precipitation heat treatment, inch/pound units

Condition	Nominal Thickness Inches	Tensile Strength Ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2-Inches or 4D %	Reduction of Area %
H900	Up to 0.1874, incl	190	170	5	--
	0.1875 to 0.625, incl	190	170	8	30
	Over 0.625 to 4.000, incl	190	170	10	35
H925	Up to 0.1874, incl	170	155	5	--
	0.1875 to 0.625, incl	170	155	8	30
	Over 0.625 to 4.000, incl	170	155	10	35
H1025	Up to 0.1874, incl	155	145	5	--
	0.1875 to 0.625, incl	155	145	8	35
	Over 0.625 to 4.000, incl	155	145	12	40
H1075	Up to 0.1874, incl	145	125	5	--
	0.1875 to 0.625, incl	145	125	9	35
	Over 0.625 to 4.000, incl	145	125	13	45
H1100	Up to 0.1874, incl	140	115	5	--
	0.1875 to 0.625, incl	140	115	10	35
	Over 0.625 to 4.000, incl	140	115	14	45
H1150	Up to 0.1874, incl	135	105	8	--
	0.1875 to 0.625, incl	135	105	10	40
	Over 0.625 to 4.000, incl	135	105	16	50

Table 4B - Minimum tensile properties after precipitation heat treatment, SI units

Condition	Nominal Thickness Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50 mm or 4D %	Reduction of Area %
H900	Up to 4.760, incl	1310	1172	5	--
	4.761 to 15.88, incl	1310	1172	8	30
	Over 15.88 to 101.60, incl	1310	1172	10	35
H925	Up to 4.760, incl	1172	1069	5	--
	4.761 to 15.88, incl	1172	1069	8	30
	Over 15.88 to 101.60, incl	1172	1069	10	35
H1025	Up to 4.760, incl	1069	1000	5	--
	4.761 to 15.88, incl	1069	1000	8	35
	Over 15.88 to 101.60, incl	1069	1000	12	40
H1075	Up to 4.760, incl	1000	862	5	--
	4.761 to 15.88, incl	1000	862	9	35
	Over 15.88 to 101.60, incl	1000	862	13	45
H1100	Up to 4.760, incl	965	793	5	--
	4.761 to 15.88, incl	965	793	10	35
	Over 15.88 to 101.60, incl	965	793	14	45
H1150	Up to 4.760, incl	931	724	8	--
	4.761 to 15.88, incl	931	724	10	40
	Over 15.88 to 101.60, incl	931	724	16	50

3.4.2.2 Unless otherwise specified, the strain rate shall be set at 0.005 in/in/min (0.005 mm/mm/min) and maintained within a tolerance of ± 0.002 in/in/min (± 0.002 mm/mm/min) through 0.2% offset yield strain. After the yield strain, the speed of the testing machine shall be set between 0.05 in/in and 0.5 in/in (0.05 mm/mm and 0.5 mm/mm) of the length of the reduced parallel section (or distance between the grips for specimens not having a reduced section) per minute. Alternatively, an extensometer and strain rate indicator may be used to set the strain rate between 0.05 in/in/min and 0.5 in/in/min (0.05 mm/mm/min and 0.5 mm/mm/min). The requirement for compliance becomes effective for material produced 1 year after the publication date of this document.

3.4.2.3 Hardness

Shall be within the range shown in Table 5 for the corresponding precipitation heat treatment condition.

Table 5 - Hardness

Condition	HBW	HRC	HV
H900	375 to 444	40 to 47	411 to 510
H925	352 to 415	38 to 45	392 to 473
H1025	331 to 388	35 to 42	364 to 431
H1075	311 to 363	33 to 39	344 to 401
H1100	302 to 352	32 to 38	333 to 392
H1150	269 to 341	28 to 37	280 to 383

3.5 Mechanical property requirements for product outside the range covered by 1.1 shall be agreed upon between purchaser and producer and reported per 4.4.1.

3.6 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.