



# AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.  
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

## AMS5607A

Superseding AMS 5607

Issued 5-15-71

Revised 7-16-79

UNS N10003

ALLOY SHEET, STRIP, AND PLATE, CORROSION AND HEAT RESISTANT  
73Ni - 7.0Cr - 16.5Mo

### 1. SCOPE:

1.1 Form: This specification covers a corrosion and heat resistant nickel alloy in the form of sheet, strip, and plate.

1.2 Application: Primarily for formed and drawn parts requiring moderate strength up to 1400° F (760° C) and oxidation resistance up to 1600° F (870° C), particularly where a low coefficient of expansion is desirable.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

#### 2.1.1 Aerospace Material Specifications:

AMS 2262 - Tolerances, Nickel, Nickel-Base, and Cobalt-Base Alloy Sheet, Strip, and Plate

AMS 2269 - Chemical Check Analysis Limits, Wrought Nickel Alloys and Cobalt Alloys

AMS 2350 - Standards and Test Methods

AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Alloys, Wrought Products Except Forgings

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E8 - Tension Testing of Metallic Materials

ASTM E139 - Conducting Creep, Creep-Rupture, and Stress-Rupture Tests of Metallic Materials

ASTM E290 - Semi-Guided Bend Test for Ductility of Metallic Materials

ASTM E354 - Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

#### 2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

#### 2.3.2 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

SAE Technical Board rules provide that: "All technical reports, including standards approved and published by SAE, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

### 3. TECHNICAL REQUIREMENTS:

3.1 **Composition:** Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E354, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Carbon	0.04	0.08
Manganese	--	1.00
Silicon	---	1.00
Phosphorus	--	0.015
Sulfur	--	0.020
Chromium	6.00	8.00
Molybdenum	15.75	17.25
Cobalt	--	0.20
Tungsten	--	0.50
Aluminum + Titanium	--	0.50
Boron	--	0.01
Iron	--	5.00
Copper	--	0.35
Nickel	remainder	

3.1.1 **Check Analysis:** Composition variations shall meet the requirements of AMS 2269.

3.2 **Condition:** The product shall be supplied in the following condition:

3.2.1 **Sheet and Strip:** Hot or cold rolled, solution heat treated, and descaled unless solution heat treatment is performed in an atmosphere yielding a bright finish, having a surface appearance comparable to a commercial corrosion-resistant steel No. 1 finish; standards for acceptance shall be as agreed upon by purchaser and vendor.

3.2.2 **Plate:** Hot rolled, solution heat treated, and descaled.

3.3 **Heat Treatment:** The product shall be solution heat treated by heating to  $2150^{\circ}\text{F} \pm 25$  ( $1175^{\circ}\text{C} \pm 15$ ), holding at heat for a time commensurate with section thickness but not more than 30 min., and cooling rapidly in air.

3.4 **Properties:** The product shall conform to the following requirements:

3.4.1 **Tensile Properties:** Shall be as follows, determined in accordance with ASTM E8:

Tensile Strength, min	100,000 psi (690 MPa)
Yield Strength at 0.2% Offset, min	40,000 psi (276 MPa)
Elongation in 2 in. (50 mm) or 4D, min	40%

3.4.2 **Bending:** Product 0.187 in. (4.75 mm) and under in nominal thickness shall withstand, without cracking, bending in accordance with ASTM E290 at room temperature through an angle of 180 deg around a diameter equal to the bend factor times the nominal thickness of the product with axis of bend parallel to the direction of rolling.

Nominal Thickness		Bend Factor
Inch	(Millimetres)	
Up to 0.050, incl	(Up to 1.27, incl)	1.5
Over 0.050 to 0.187, incl	(Over 1.27 to 4.75, incl)	2

- 3.4.2.1 Bending requirements for product over 0.187 in. (4.75 mm) in nominal thickness shall be as  
∅ agreed upon by purchaser and vendor.
- 3.4.3 Stress-Rupture Properties at 1500° F (816° C): A tensile test specimen, maintained at 1500° F  $\pm$  3  
(816° C  $\pm$  2) while a load sufficient to produce an initial axial stress of 13,000 psi (89.6 MPa) is applied  
continuously, shall not rupture in less than 23 hours. The test shall be continued to rupture without  
change of load. Elongation after rupture, measured at room temperature, shall be not less than 8% in  
2 in. (50 mm) or 4D. Tests shall be conducted in accordance with ASTM E139.
  - 3.4.3.1 The test of 3.4.3 may be conducted using a load higher than required to produce an initial axial stress  
of 13,000 psi (89.6 MPa) but load shall not be changed while test is in progress. Time to rupture  
and elongation requirements shall be as specified in 3.4.3.
  - 3.4.3.2 When permitted by purchaser, the test of 3.4.3 may be conducted using incremental loading. In such  
∅ case, the load required to produce an initial axial stress of 13,000 psi (89.6 MPa) shall be used to  
rupture or for 23 hr, whichever occurs first. After the 23 hr and at intervals of 8 - 16 hr, preferably  
8 - 10 hr, thereafter, the stress shall be increased in increments of 2000 psi (13.8 MPa). Time to  
rupture and elongation requirements shall be as specified in 3.4.3.
- 3.5 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free  
∅ from foreign materials and from internal and external imperfections detrimental to usage of the product.
- 3.6 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of  
AMS 2262.

4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of the product shall supply all samples and shall be responsible  
for performing all required tests. Results of such tests shall be reported to the purchaser as required by  
4.4. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure  
that the product conforms to the requirements of this specification.
- 4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification  
∅ are classified as acceptance tests and shall be performed on each lot.
- 4.3 Sampling: Shall be in accordance with AMS 2371 and the following:
  - 4.3.1 Specimens for tensile tests of widths 9 in. (229 mm) and over shall be taken with the axis of the  
specimen perpendicular to the direction of rolling; for widths less than 9 in. (229 mm), specimens  
shall be taken with the axis parallel to the direction of rolling.
- 4.4 Reports:
  - 4.4.1 The vendor of the product shall furnish with each shipment three copies of a report showing the results  
of tests for chemical composition of each heat and for tensile, bending, and stress-rupture properties  
of each size from each heat. This report shall include the purchase order number, heat number,  
material specification number and its revision letter, size, and quantity from each heat.
  - 4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report  
showing the purchase order number, material specification number and its revision letter, contractor  
or other direct supplier of material, part number, and quantity. When material for making parts is  
produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine  
conformance to the requirements of this specification, and shall include in the report a statement that  
the material conforms, or shall include copies of laboratory reports showing the results of tests to  
determine conformance.