

Issued	1971-05
Revised	2002-01
Reaffirmed	2012-07
Superseding AMS5607D	

Nickel Alloy, Corrosion and Heat-Resistant, Sheet, Strip, and Plate

73Ni - 7.0Cr - 16.5Mo
Solution Heat Treated

(Composition similar to UNS N10003)

RATIONALE

AMS5607E has been reaffirmed to comply with the SAE five-year review policy.

1. SCOPE:

1.1 Form:

This specification covers a corrosion and heat-resistant nickel alloy in the form of sheet, strip, and plate.

1.2 Application:

These products have been used typically for parts requiring moderate strength up to 1400°F (760°C) and oxidation resistance up to 1600 °F (871 °C), particularly where a low coefficient of expansion is desirable, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001 or www.sae.org.

AMS 2262	Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Sheet, Strip, and Plate
MAM 2262	Tolerances, Metric, Nickel, Nickel Alloy, and Cobalt Alloy Sheet, Strip, and Plate
AMS 2269	Chemical Check Analysis Limits, Nickel, Nickel Alloys, and Cobalt Alloys
AMS 2371	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

SAE values your input. To provide feedback on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS5607E>

2.1 (Continued):

AMS 2807 Identification, Carbon and Low-Alloy Steels, Corrosion and Heat-Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing

AS4194 Sheet and Strip Surface Finish Nomenclature

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959 or www.astm.org.

ASTM A 480/A 480M Flat-Rolled Stainless and Heat-Resisting Steel Plate, Sheet, and Strip

ASTM E 8 Tension Testing of Metallic Materials

ASTM E 8M Tension Testing of Metallic Materials (Metric)

ASTM E 139 Conducting Creep, Creep-Rupture, and Stress-Rupture Tests of Metallic Materials

ASTM E 290 Bend Testing Material for Ductility

ASTM E 354 Chemical Analysis of High-Temperature Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	0.04	0.08
Manganese	--	1.00
Silicon	--	1.00
Phosphorus	--	0.015
Sulfur	--	0.020
Chromium	6.00	8.00
Molybdenum	15.75	17.25
Cobalt	--	0.20
Tungsten	--	0.50
Aluminum + Titanium	--	0.50
Boron	--	0.01
Iron	--	5.00
Copper	--	0.35
Nickel	remainder	

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2269.

3.2 Condition:

The product shall be supplied in the following condition:

3.2.1 Sheet and Strip: Hot or cold rolled, solution heat treated, and, unless solution heat treatment is performed in an atmosphere yielding a bright finish, descaled having a surface appearance in accordance with ASTM A 480/A 480M and AS4194 comparable to 3.2.1.1 or 3.2.1.2 as applicable.

3.2.1.1 Sheet: No. 2D finish.

3.2.1.2 Strip: No. 1 strip finish.

3.2.2 Plate: Hot rolled, solution heat treated, and descaled.

3.3 Heat Treatment:

The product shall be solution heat treated by heating to $2150 \text{ }^\circ\text{F} \pm 25$ ($1177 \text{ }^\circ\text{C} \pm 14$), holding at heat for a time commensurate with section thickness but not more than 30 minutes, and cooling at a rate equivalent to an air cool or faster.

3.4 Properties:

The product shall conform to the following requirements:

3.4.1 Tensile Properties: Shall be as shown in Table 2, determined in accordance with ASTM E 8 or ASTM E 8M.

TABLE 2 - Minimum Tensile Properties

Property	Value
Tensile Strength	100 ksi (689 MPa)
Yield Strength at 0.2% Offset	40.0 ksi (276 MPa)
Elongation in 2 Inches (50.8 mm) or 4D	40%

3.4.2 Bending: Product shall withstand, without cracking, bending at room temperature in accordance with ASTM E 290 through an angle of 180 degrees around a diameter equal to the bend factor shown in Table 3 times the nominal thickness of the product, with axis of bend parallel to the direction of rolling.

TABLE 3 - Bending Parameters

Nominal Thickness Inch	Nominal Thickness Millimeters	Bend Factor
Up to 0.050, incl	Up to 1.27, incl	1.5
Over 0.050 to 0.1874, incl	Over 1.27 to 4.760, incl	2

3.4.3 Stress-Rupture Properties at 1500 °F (816 °C): A tensile specimen, maintained at 1500 °F \pm 3 (816 °C \pm 2) while a load sufficient to produce an initial axial stress of 13.0 ksi (90 MPa) or higher is applied continuously, shall not rupture in less than 23 hours. The test shall be continued to rupture without change of load. Elongation after rupture, measured at room temperature, shall be not less than 8% in 2 inches (50.8 mm) or 4D. Tests shall be conducted in accordance with ASTM E 139.

3.4.3.1 The test of 3.4.3 may be conducted using incremental loading. In such case, the load required to produce an initial axial stress of 13.0 ksi (90MPa) or higher shall be used for 23 hours or to rupture, whichever occurs first. After the 23 hours and at intervals of 8 to 16 hours, preferably 8 to 10 hours, thereafter, the stress shall be increased in increments of 2.0 ksi (14MPa). Time to rupture and elongation requirements shall be as specified in 3.4.3.

3.5 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.6 Tolerances:

Shall conform to all applicable requirements of AMS 2262 or MAM 2262.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests:

All technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling and Testing:

Shall be in accordance with AMS 2371.