

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 5616

Issued 3-1-48

Revised

STEEL, CORROSION AND MODERATE HEAT RESISTANT 13Cr - 2Ni - 3W

Page 1 of 2 pages

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. **FORM:** Bars, billets, and forgings.
3. **APPLICATION:** Parts and assemblies, such as compressor wheels and blades, requiring oxidation resistance up to 1000 F. Strength at the higher temperatures is superior to that of the standard 12 Cr type.

4. **COMPOSITION:**

		Check Analysis	
		Under Min	or Over Max
Carbon	0.12 max	--	0.01
Manganese	0.50 max	--	0.03
Silicon	0.50 max	--	0.05
Phosphorus	0.040 max	--	0.005
Sulfur	0.030 max	--	0.005
Chromium	12.00 - 14.00	0.15	0.15
Nickel	1.80 - 2.20	0.07	0.07
Tungsten	2.50 - 3.50	0.10	0.10
Molybdenum	0.50 max	--	0.03
Copper	0.50 max	--	0.03
Tin	0.05 max	--	--
Aluminum	0.15 max	--	--

5. **CONDITION:** (a) Annealed, unless otherwise specified.
(b) Unless otherwise specified, bars and rods 2.75 in. and less in diameter and all hexagons shall be cold finished.
(c) Forging stock shall be supplied as ordered by the forging manufacturer.

6. **TECHNICAL REQUIREMENTS:** (a) Hardness.- The product shall have hardness not higher than Brinell 277 or equivalent.

(b) Hardenability.- Material shall be capable of meeting the following test:

Specimens 3/8 in. thick, cut from a bar or forging, shall be heated to 1750 F \pm 10, held for 30 minutes and cooled in still air. Hardness of such specimens shall be Rockwell C 36-46.

7. **QUALITY:** The product shall be uniform in quality and condition, clean, sound and free from foreign materials and from internal and external defects detrimental to fabrication or to performance of parts.

7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any standard or recommended practice, and no commitment to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."