

# AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard



AMS 5616K

Issued MAR 1948  
Revised JAN 1999

Superseding AMS 5616J

Steel, Corrosion and Heat Resistant, Bars, Wire,  
Forgings, Tubing, and Rings  
13Cr - 2.0Ni - 3.0W  
Annealed

UNS S41800

## 1. SCOPE:

### 1.1 Form:

This specification covers a corrosion and heat resistant steel in the form of bars, wire, forgings, mechanical tubing, flash welded rings, and stock for forging, flash welded rings, or heading.

### 1.2 Application:

These products have been used typically for formed parts requiring oxidation resistance up to 1000 °F (538 °C), but usage is not limited to such applications. Strength at the higher temperature is superior to that of the standard 12Cr type steel.

## 2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1999 Society of Automotive Engineers, Inc.  
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:  
TO PLACE A DOCUMENT ORDER:  
SAE WEB ADDRESS:

(724) 772-7161  
(724) 776-4970  
<http://www.sae.org>

FAX: (724) 776-0243  
FAX: (724) 776-0790

## 2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2241	Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire
MAM 2241	Tolerances, Metric, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire
AMS 2243	Tolerances, Corrosion and Heat Resistant Steel Tubing
MAM 2243	Tolerances, Metric, Corrosion and Heat Resistant Steel Tubing
AMS 2248	Chemical Check Analysis Limits, Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
AMS 2303	Aircraft Quality Steel Cleanliness, Martensitic Corrosion-Resistant Steels, Magnetic Particle Inspection Procedure
MAM 2303	Aircraft Quality Steel Cleanliness, Martensitic Corrosion-Resistant Steels, Magnetic Particle Inspection Procedure, Metric (SI) Measurement
AMS 2371	Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS 2374	Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steel and Alloy Forgings
AMS 2806	Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat Resistant Steels and Alloys
AMS 2808	Identification, Forgings
AMS 7493	Rings, Flash Welded, Ferritic and Martensitic, Corrosion-Resistant Steels
AS1182	Standard Machining Allowance, Aircraft-Quality and Premium Aircraft-Quality Steel Bars and Mechanical Tubing

## 2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM A 370	Mechanical Testing of Steel Products
ASTM E 112	Determining the Average Grain Size
ASTM E 353	Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

## 3. TECHNICAL REQUIREMENTS:

## 3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	0.15	0.20
Manganese	-	0.50
Silicon	-	0.50
Phosphorus	-	0.040
Sulfur	-	0.030
Chromium	12.00	14.00
Nickel	1.80	2.20
Tungsten	2.50	3.50
Molybdenum	-	0.50
Aluminum	-	0.15
Copper	-	0.50
Tin	-	0.05
Nitrogen	-	0.08

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

### 3.2 Condition:

The product shall be supplied in the following condition; hardness and tensile strength shall be determined in accordance with ASTM A 370.

3.2.1 Bars: Annealed having hardness not greater than 311 HB, or equivalent (See 8.2).

3.2.1.1 Bars over 0.500 to 2.750 inches (12.70 to 69.85 mm), inclusive, in nominal diameter or least distance between parallel sides and all hexagons shall be cold finished.

3.2.1.2 Bars, other than hexagons, over 2.750 inches (69.85 mm) in nominal diameter or least distance between parallel sides shall be hot finished.

3.2.2 Wire: Annealed and cold finished having tensile strength not higher than 155 ksi (1069 MPa) or equivalent hardness (See 8.3).

3.2.3 Forgings: Annealed having hardness not higher than 311 HB, or equivalent (See 8.2).

3.2.4 Mechanical Tubing: Annealed and cold finished having hardness not higher than 311 HB, or equivalent (See 8.2).

3.2.5 Flash Welded Rings: Annealed having hardness not higher than 311 HB, or equivalent (See 8.2).

3.2.5.1 Flash welded rings shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, rings shall be manufactured in accordance with AMS 7493.

3.2.6 Stock for Forging, Flash Welded Rings, or Heading: As ordered by the forging, flash welded ring, or heading manufacturer.

### 3.3 Properties:

The product shall conform to the following requirements:

3.3.1 Response to Heat Treatment: Product 0.375 inch (9.52 mm) and under in nominal thickness and 0.375 inch  $\pm$  0.010 (9.52 mm  $\pm$  0.25) thick specimens cut from larger product shall have hardness not lower than 45 HRC, or equivalent (See 8.2), determined in accordance with ASTM A 370, after being heated to 1750 °F  $\pm$  10 (954 °C  $\pm$  6), held at heat for 25 to 30 minutes, and quenched in commercial paraffin oil [(approximately 100 SUS at 100 °F (38 °C))] at room temperature.

3.3.2 Average Grain Size: Bars 2 inches (51 mm) and under in nominal diameter or least distance between parallel sides shall have an average grain size of ASTM No. 5 or finer, determined in accordance with ASTM E 112 (See 8.4).

### 3.4 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.4.1 Steel shall be aircraft quality and, when specified, shall conform to AMS 2303 or MAM 2303.

3.4.2 Bars ordered hot rolled or cold drawn, or ground, turned, or polished, shall, after removal of the standard machining allowance in accordance with AS1182, be free from seams, laps, tears, and cracks open to the ground, turned, or polished surface.

3.4.3 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of re-entrant grain flow.

### 3.5 Tolerances:

Shall conform to all applicable requirements of the following:

3.5.1 Bars and Wire: AMS 2241 or MAM 2241.

3.5.2 Mechanical Tubing: AMS 2243 or MAM 2243.

#### 4. QUALITY ASSURANCE PROVISIONS:

##### 4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

##### 4.2 Classification of Tests:

4.2.1 Acceptance Tests: Composition (3.1), condition (3.2), response to heat treatment (3.3.1), average grain sizes of bars 2.00 inches (51 mm) and under in nominal diameter or least distance between parallel sides (3.3.2), frequency-severity cleanliness rating when specified (3.4.1), and tolerances (3.5) are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests: Grain flow of die forgings is a periodic test and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

##### 4.3 Sampling and Testing:

Shall be in accordance with the following:

4.3.1 Bars, Wire, Mechanical Tubing, Flash Welded Rings, and Stock for Forging, Flash Welded Rings, or Heading: AMS 2371.

4.3.2 Forgings: AMS 2374.

##### 4.4 Reports:

The vendor of the product shall furnish with each shipment a report showing the results of tests for chemical composition and, when specified, frequency-severity cleanliness rating of each heat and for average grain size of bars 2.00 inches (51 mm) and under in nominal diameter or least distance between parallel sides and response to heat treatment of each lot, and stating that the product conforms to the other technical requirements. This report shall include the purchase order number, heat and lot numbers, AMS 5616K, size, and quantity. If forgings are supplied, the part number and the size and melt source of stock used to make the forgings shall also be included.

##### 4.5 Resampling and Retesting:

Shall be in accordance with the following:

4.5.1 Bars, Wire, Mechanical Tubing, Flash Welded Rings, and Stock for Forging, Flashing Welded Rings, or Heading: AMS 2371.

4.5.2 Forgings: AMS 2374.