



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AMS 5620C

Superseding AMS 5620 B

Issued 7-1-45

Revised 7-1-76

STEEL BARS AND FORGINGS, CORROSION AND MODERATE HEAT RESISTANT
13Cr (0.30 - 0.40C) (SAE 51420F)
Free-Machining

UNS S42020 (Type II)
S42023 (Type I)

1. SCOPE:

- 1.1 Form: This specification covers two types of free-machining, corrosion and moderate heat resistant steel in the form of bars, wire, forgings, and forging stock.
- 1.2 Application: Primarily for parts on which the amount of machining warrants use of a free-machining grade of steel and requiring hardness within the range of 40 - 50 HRC with corrosion resistance and oxidation resistance up to 1000°F (538°C), but useful at the higher temperatures only when stresses are moderately low. Certain design and processing procedures may cause this material to be susceptible to stress-corrosion cracking. ARP 1110 recommends practices to minimize such conditions.
- 1.3 Classification: The steel compositions covered by this specification are classified as follows:
Type I - 13Cr - 0.26Se (0.30 - 0.40C)
Type II - 13Cr - 0.25S (0.30 - 0.40C)

1.3.1 Unless a specific type is ordered, either Type I or Type II may be supplied.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS), Aerospace Standards (AS), and Aerospace Recommended Practices (ARP) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

- AMS 2241 - Tolerances, Corrosion and Heat Resistant Steel Bars and Wire and Titanium and Titanium Alloy Bars and Wire
- AMS 2248 - Chemical Check Analysis Limits, Wrought Heat and Corrosion Resistant Steels and Alloys
- AMS 2350 - Standards and Test Methods
- AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Alloys, Wrought Products Except Forgings
- AMS 2806 - Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Heat and Corrosion Resistant Steels and Alloys
- AMS 2808 - Identification, Forgings

2.1.2 Aerospace Standards:

- AS 1182 - Standard Machining Allowance, Aircraft Quality and Premium Quality Steel Products

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

2.1.3 Aerospace Recommended Practices:

ARP 1110 - Minimizing Stress Corrosion Cracking in Heat Treatable Wrought Low Alloy and Martensitic Corrosion Resistant Steels

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A370 - Mechanical Testing of Steel Products

ASTM E340 - Macroetching Metals and Alloys

ASTM E353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other approved analytical methods:

	Type I		Type II	
	min	max	min	max
Carbon	0.30	0.40	0.30	0.40
Manganese	--	1.25	--	1.25
Silicon	--	1.00	--	1.00
Phosphorus	--	0.060	--	0.060
Sulfur	--	0.030	0.15	0.35
Chromium	12.00	14.00	12.00	14.00
Selenium	0.18	0.35	--	--
Nickel	--	0.50	--	0.50
Molybdenum or Zirconium	--	0.60	--	0.60

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

3.2 Condition: The product shall be supplied in the following condition; hardness and tensile strength shall be determined in accordance with ASTM A370:

3.2.1 Bars:

3.2.1.1 Bars over 0.500 to 2.750 in. (12.70 to 69.85 mm), incl, in nominal diameter or distance between parallel sides and all hexagons shall be cold finished, unless otherwise ordered, having hardness not higher than 241 HB or equivalent.

- 3.2.1.2 Bars, other than hexagons, over 2.750 in. (69.85 mm) in nominal diameter or distance between parallel sides shall be hot finished having hardness not higher than 241 HB or equivalent.
- 3.2.2 Wire: Cold finished having tensile strength not higher than 125,000 psi (862 MPa) or equivalent hardness.
- 3.2.3 Forgings: As ordered.
- 3.2.4 Forging Stock: As ordered by the forging manufacturer.
- 3.3 Properties: The product shall conform to the following requirements; hardness testing shall be performed in accordance with ASTM A370:
- 3.3.1 Macrostructure: Visual examination of transverse sections from bars, billets, and forging stock, etched in accordance with ASTM E340 in hot hydrochloric acid (1:1) at 160° - 180°F (71.1° - 82.2°C) for sufficient time to develop a well-defined macrostructure, shall show no imperfections, such as pipe, cracks, porosity, segregation, and inclusions, detrimental to fabrication or to performance of parts. Macrostructure standards shall be as agreed upon by purchaser and vendor.
- 3.3.2 Decarburization:
- 3.3.2.1 Bars and wire ordered ground, turned, or polished shall be free from decarburization on the ground, turned or polished surfaces.
- 3.3.2.2 Allowable decarburization of bars, wire, and billets ordered for redrawing or forging or to specified microstructural requirements shall be as agreed upon by purchaser and vendor.
- 3.3.2.3 Decarburization of bars and wire to which 3.3.2.1 or 3.3.2.2 is not applicable shall be not greater than shown in Table I.

TABLE I

Nominal Diameter or Distance Between Parallel Sides Inches	Depth of Decarburization Inch
Up to 0.375, incl	0.010
Over 0.375 to 0.500, incl	0.012
Over 0.500 to 0.625, incl	0.014
Over 0.625 to 1.000, incl	0.017
Over 1.000 to 1.500, incl	0.020
Over 1.500 to 2.000, incl	0.025
Over 2.000 to 2.500, incl	0.030
Over 2.500 to 3.000, incl	0.035
Over 3.000 to 4.000, incl	0.045

TABLE I (SI)

Nominal Diameter or Distance Between Parallel Sides Millimetres	Depth of Decarburization Millimetres
Up to 9.52, incl	0.25
Over 9.52 to 12.70, incl	0.30
Over 12.70 to 15.88, incl	0.36
Over 15.88 to 25.40, incl	0.43
Over 25.40 to 38.10, incl	0.51
Over 38.10 to 50.80, incl	0.64
Over 50.80 to 63.50, incl	0.76
Over 63.50 to 76.20, incl	0.89
Over 76.20 to 101.60, incl	1.14

- 3.3.2.3.1 Limits for depth of decarburization of bars over 4.000 in. (101.60 mm) in nominal diameter or distance between parallel sides shall be as agreed upon by purchaser and vendor.
- 3.3.2.4 Decarburization shall be measured by the microscopic method or by Rockwell Superficial 30-N scale or equivalent hardness testing method on hardened but untempered specimens protected during heat treatment to prevent changes in surface carbon content. Depth of decarburization, when measured by a hardness method, is defined as the perpendicular distance from the surface to the depth under that surface below which there is no further increase in hardness. Such measurements shall be far enough away from any adjacent surface to be uninfluenced by any decarburization or lack of decarburization thereon.
- 3.3.2.4.1 When determining the depth of decarburization, it is permissible to disregard local areas provided the decarburization of such areas does not exceed the above limits by more than 0.005 in. (0.13 mm) and the width is 0.065 in. (1.65 mm) or less.
- 3.3.3 Response to Heat Treatment: Product 0.500 in. (12.70 mm) and under in nominal thickness and 0.500-in. ± 0.010 (12.70-mm ± 0.25) thick specimens cut from larger bars and forgings hardness not lower than 50 HRC or equivalent after being heated to 1825°F ± 10 (996.1°C ± 5.6), held at heat for 25 - 30 min., and cooled in still air to room temperature.
- 3.4 Quality: The product, as received by the purchaser, shall be uniform in quality and condition, sound, and consistent with the type of steel involved, free from foreign materials and from internal and external imperfections detrimental to usage of the product.
- 3.4.1 Bars ordered ground, turned, or polished shall be free from seams, laps, tears, and cracks open to the ground, turned, or polished surfaces.
- 3.4.2 Product ordered to surface conditions other than ground, turned, or polished shall, after removal of the standard machining allowance, be free from seams, laps, tears, cracks, and other defects exposed to the machined surfaces. Standard machining allowance shall be in accordance with AS 1182.
- 3.5 Sizes: Except when exact lengths or multiples of exact lengths are ordered, straight bars and wire will be acceptable in mill lengths of 6 - 20 ft (1.8 - 6.1 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 ft (3 m).
- 3.6 Tolerances: Unless otherwise specified, tolerances for bars and wire shall conform to all applicable requirements of AMS 2241.