

An American National Standard

Issued 1 NOV 1952
Revised 1 OCT 1991
Superseding AMS 5621C

STEEL, CORROSION RESISTANT, BARS, WIRE, AND FORGINGS
13Cr (0.30-0.40C (SAE 51420)
Annealed

UNS S42000

1. SCOPE:

1.1 Form:

This specification covers a corrosion-resistant steel in the form of bars, wire, forgings, and forging stock.

1.2 Application:

These products have been used typically for parts requiring corrosion resistance and oxidation resistance up to 800 °F (427 °C) and hardness at room temperature within the range 40 - 50 HRC when heat treated, but usage is not limited to such applications.

- 1.2.1 Certain design and processing procedures may cause these products to become susceptible to stress-corrosion cracking; ARP1110 recommends practices to minimize such conditions.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

- AMS 2241 Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire
- MAM 2241 Tolerances, Metric, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire
- AMS 2248 Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
- AMS 2371 Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock
- AMS 2374 Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steel and Alloy Forgings
- AMS 2806 Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels, and Corrosion and Heat Resistant Steels and Alloys
- AMS 2808 Identification, Forgings
- ARPI110 Minimizing Stress Corrosion Cracking in Heat Treatable Wrought Low Alloy and Martensitic Corrosion Resistant Steels
- AS1182 Standard Machining Allowance, Aircraft Quality and Premium Quality Steel Bars and Mechanical Tubing

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

- ASTM A 370 Mechanical Testing of Steel Products
- ASTM E 353 Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

2.3 U.S. Government Publications:

Available from Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

- MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

(R)

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	0.30	0.40
Manganese	--	1.00
Silicon	--	1.00
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	12.00	14.00
Nickel	--	0.50
Molybdenum	--	0.50
Copper	--	0.50
Aluminum	--	0.05
Tin	--	0.05

3.1.1 Check Analysis Composition variations shall meet the requirements of AMS 2248.

3.2 Condition:

The product shall be supplied in the following condition; hardness and tensile strength shall be determined in accordance with ASTM A 370:

3.2.1 Bars: Annealed having hardness not higher than 241 HB, or equivalent.

3.2.1.1 Bars 2.750 inches (69.85 mm) and under in nominal diameter or distance between parallel sides and all hexagons shall be cold finished.

3.2.1.2 Bars, other than hexagons, over 2.750 inches (69.85 mm) in nominal diameter or distance between parallel sides shall be hot finished.

3.2.2 Wire: Cold drawn and annealed having tensile strength not higher than (R) 115 ksi (793 MPa).

3.2.3 Forgings: As ordered.

3.2.4 Forging Stock: As ordered by the forging manufacturer.

3.3 Properties:

The product shall conform to the following requirements; hardness testing shall be performed in accordance with ASTM A 370:

- 3.3.1 Response to Heat Treatment: Product 0.500 inch (12.10 mm) and under in nominal thickness and 0.500 inch \pm 0.100 (12.70 mm \pm 2.54) thick specimens cut from larger bars and forgings shall have hardness not lower than 50 HRC, or equivalent, after being heated to 1825 °F \pm 25 (996 °C \pm 14), held at heat for 30 minutes \pm 3, and cooled in still air.
- 3.3.2 Decarburization:
- 3.3.2.1 Bars and wire ordered ground, turned, or polished shall be free from decarburization on the ground, turned, or polished surfaces.
- 3.3.2.2 Allowable decarburization of bars and billets ordered for redrawing or forging or to specified microstructural requirements shall be as agreed upon by purchaser and vendor.
- 3.3.2.3 Decarburization of bars and wire to which 3.3.2.1 or 3.3.2.2 is not applicable shall be not greater than shown in Table 2.

TABLE 2A - Maximum Decarburization, Inches

Nominal Diameter or Distance Between Parallel Sides	Depth of Decarburization
Up to 0.375, incl	0.010
Over 0.375 to 0.500, incl	0.012
Over 0.500 to 0.625, incl	0.014
Over 0.625 to 1.000, incl	0.017
Over 1.000 to 1.500, incl	0.020
Over 1.500 to 2.000, incl	0.025
Over 2.000 to 2.500, incl	0.030
Over 2.500 to 3.000, incl	0.035
Over 3.000 to 4.000, incl	0.045

TABLE 2B - Maximum Decarburization, Millimeters

Nominal Diameter or Distance Between Parallel Sides		Depth of Decarburization
	Up to 9.52, incl	0.25
Over	9.52 to 12.70, incl	0.30
Over	12.70 to 15.88, incl	0.36
Over	15.88 to 25.40, incl	0.43
Over	25.40 to 38.10, incl	0.51
Over	38.10 to 50.80, incl	0.64
Over	50.80 to 63.50, incl	0.76
Over	63.50 to 76.20, incl	0.89
Over	76.20 to 101.60, incl	1.14

3.3.2.3.1 Limits for depth of decarburization of bars over 4.000 inches (101.60 mm) in nominal diameter or distance between parallel sides shall be as agreed upon by purchaser and vendor.

3.3.2.4 Decarburization shall be measured by the microscopic method or by Rockwell Superficial 30-N scale or equivalent hardness testing method on hardened but untempered specimens protected during heat treatment to prevent changes in surface carbon content. Depth of decarburization, when measured by a hardness method, is defined as the perpendicular distance from the surface to the depth under that surface below which there is no further increase in hardness. Such measurements shall be far enough away from any adjacent surface to be uninfluenced by any decarburization or lack of decarburization thereon.

3.3.2.4.1 When determining the depth of decarburization, it is permissible to disregard local areas provided the decarburization of such areas does not exceed the limits of Table 2 by more than 0.005 inch (0.13 mm) and the width is 0.065 inch (1.65 mm) or less.

3.4 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.4.1 Bars and wire ordered hot rolled or cold drawn or ground, turned, or polished shall after removal of the standard machining allowance in accordance with AS1182, be free from seams, laps, tears, and cracks open to the ground, turned, or polished surfaces.

3.4.2 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of re-entrant grain flow.

3.5 Tolerances:

Bars and wire shall conform to all applicable requirements of AMS 2241 or MAM 2241.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

Test for all technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling and Testing:

(R)

Shall be in accordance with the following:

4.3.1 Bars, Wire, and Forging Stock: AMS 2371.

4.3.2 Forgings: AMS 2374.

4.4 Reports:

4.4.1 The vendor of bars, wire, and forgings shall furnish with each shipment a (R) report showing the results of tests for chemical composition of each heat and the results of tests for response to heat treatment of each lot. This report shall include the purchase order number, heat and lot number, AMS 5621D, size, and quantity. If forgings are supplied, the part number and the size and melt source of stock, if not the same as the forge shop, used to make the forgings shall also be included.

4.4.2 The vendor of forging stock shall furnish with each shipment a report showing the results of tests for chemical composition of each heat. This report shall include the purchase order number, heat number, AMS 5621D, size, and quantity.

4.5 Resampling and Retesting:

Shall be in accordance with the following:

4.5.1 Bars, Wire, and Forging Stock: AMS 2371.