

**AEROSPACE
MATERIAL
SPECIFICATION**

Submitted for recognition as an American National Standard

SAE AMS 5638B

Issued 1-15-63
Revised 10-1-86

Superseding AMS 5638A

STEEL BARS AND FORGINGS, CORROSION RESISTANT
0.14S - 18Cr - 9.5Ni - 0.50Mo - 0.80Al
Free-Machining; Swaging or Upsetting
Solution Heat Treated

UNS S30345

1. SCOPE:

1.1 Form: This specification covers one type of free-machining, corrosion-resistant steel in the form of bars, forgings, and forging stock.

1.2 Application: Primarily for parts on which the amount of machining warrants use of a free-machining grade of steel requiring corrosion resistance similar to the 18-8 type of steel but not subjected to temperatures exceeding 700°F (370°C) during fabrication or in service.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2241 - Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire

MAM 2241 - Tolerances, Metric, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire

AMS 2248 - Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys

AMS 2350 - Standards and Test Methods

AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.1.1 (Cont'd.):

AMS 2374 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Forgings and Forging Stock

AMS 2806 - Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Heat and Corrosion Resistant Steels and Alloys

AMS 2808 - Identification, Forgings

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E10 - Brinell Hardness of Metallic Materials

ASTM E353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.2.3.1 Military Specifications:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353 or by spectrographic or other analytical methods approved by purchaser:

	min	max
Carbon	--	0.15
Manganese	--	2.00
Silicon	--	1.00
Phosphorus	--	0.040
Sulfur	0.11 -	0.16
Chromium	17.00 -	19.00
Nickel	8.50 -	10.50
Molybdenum	0.40 -	0.60
Aluminum	0.60 -	1.00
Copper	--	0.50

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2248.3.2 Condition: The product shall be supplied in the following condition:3.2.1 Bars and Forgings: Solution heat treated, descaled, and free from continuous carbide network.

3.2.1.1 All hexagons and other bars 2.75 in. (70 mm) and under in nominal diameter or distance between parallel sides shall be cold finished.

- 3.2.1.2 Bars, other than hexagons, over 2.75 in. (70 mm) in nominal diameter or distance between parallel sides shall be hot finished.
- 3.2.2 Forging Stock: As ordered by the forging manufacturer.
- 3.3 Heat Treatment: Bars and forgings shall be solution heat treated by heating \emptyset to a temperature not lower than 1900°F (1040°C), holding at the selected temperature within +25°F (+15°C) for not less than 15 min., and cooling rapidly in air.
- 3.4 Properties: The product shall conform to the following requirements; hardness testing shall be performed in accordance with ASTM E10:

3.4.1 Hardness:

- 3.4.1.1 Bars: Shall be as follows, or equivalent, determined at approximate mid-radius or quarter thickness:

Nominal Diameter or Distance Between Parallel Sides		Hardness
Inches	Millimetres	
Up to 0.75, incl	Up to 19.0, incl	170 - 255 HB
Over 0.75	Over 19.0	140 - 241 HB

- 3.4.1.2 Forgings: Shall have hardness not higher than 187 HB, or equivalent.
- 3.5 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound and, consistent with the type of steel involved, free from foreign materials and from imperfections detrimental to usage of the product.
- 3.6 Sizes: Except when exact lengths or multiples of exact lengths are ordered, straight bars will be acceptable in mill lengths of 6 - 20 ft (2 - 6 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 ft (3 m).
- 3.7 Tolerances: Shall conform to all applicable requirements of AMS 2241 or MAM 2241.

4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of the product shall supply all \emptyset samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.
- 4.2 Classification of Tests: Tests to determine conformance to all technical \emptyset requirements of this specification are classified as acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling: Shall be in accordance with the following:

4.3.1 Bars: AMS 2371.

4.3.2 Forgings and Forging Stock: AMS 2374.

4.4 Reports:

4.4.1 The vendor of the product shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and for hardness of each lot and stating that the product conforms to the other technical requirements of this specification. This report shall include the purchase order number, heat number, AMS 5638B, size, and quantity. If forgings are supplied, the part number and the size and melt source of stock used to make the forgings shall also be included.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 5638B, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification and shall include in the report either a statement that the material conforms or copies of laboratory reports showing the results of tests to determine conformance.

4.5 Resampling and Retesting: Shall be in accordance with the following:

4.5.1 Bars: AMS 2371.

4.5.2 Forgings and Forging Stock: AMS 2374.

5. PREPARATION FOR DELIVERY:

5.1 Identification: The product shall be identified as follows:

5.1.1 Bars: In accordance with AMS 2806.

5.1.2 Forgings: In accordance with AMS 2808.

5.1.3 Forging Stock: As agreed upon by purchaser and vendor.

5.2 Packaging:

5.2.1 The product shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the product to ensure carrier acceptance and safe delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.

5.2.2 For direct U.S. Military procurement, packaging shall be in accordance with MIL-STD-163, Level A or Level C, as specified in the request for procurement. Commercial packaging as in 5.3.1 will be acceptable if it meets the requirements of Level C.