

**AEROSPACE
MATERIAL
SPECIFICATION**

SAE AMS 5652E

Issued 9-1-47
Revised 10-1-86

Superseding AMS 5652D

Submitted for recognition as an American National Standard

STEEL BARS, FORGINGS, TUBING, AND RINGS, CORROSION AND HEAT RESISTANT
25Cr - 20Ni - 2Si (SAE 30314)
Solution Heat Treated

UNS S31400

1. SCOPE:

1.1 Form: This specification covers a corrosion and heat resistant steel in the form of bars, wire, forgings, mechanical tubing, flash welded rings, and stock for forging or flash welded rings.

1.2 Application: Primarily for parts requiring good corrosion resistance and which will be subjected to elevated temperatures during fabrication or in service. For parts requiring oxidation resistance up to 2000°F (1095°C) but useful at the higher temperatures only when stresses are low. Strength at elevated temperatures is similar to that of the 18-8 type steels. The specified silicon content improves oxidation resistance with some sacrifice of weldability and ductility.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2241 - Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire

MAM 2241 - Tolerances, Metric, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire

AMS 2243 - Tolerances, Corrosion and Heat Resistant Steel Tubing

MAM 2243 - Tolerances, Metric, Corrosion and Heat Resistant Steel Tubing

AMS 2248 - Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.1.1 (Continued):

- AMS 2350 - Standards and Test Methods
- AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock
- AMS 2374 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Forgings and Forging Stock
- AMS 2375 - Control of Forgings Requiring First Article Approval
- AMS 2806 - Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Heat and Corrosion Resistant Steels and Alloys
- AMS 2808 - Identification, Forgings
- AMS 7490 - Rings, Flash Welded, Corrosion and Heat Resistant Austenitic Steels and Austenitic-Type Alloys

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

- ASTM A370 - Mechanical Testing of Steel Products
- ASTM E353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.2.3.1 Military Standards:

- MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:3.1 Composition: Shall conform to the following percentages by weight, \emptyset determined by wet chemical methods in accordance with ASTM E353 or by spectrographic or other analytical methods approved by purchaser:

	min	max
Carbon	--	0.18
Manganese	1.00 -	2.00
Silicon	1.50 -	2.30
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	23.00 -	25.00
Nickel	19.00 -	22.00
Molybdenum	--	0.75
Copper	--	0.75

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.3.2 Condition: The product shall be supplied in the following condition:

- 3.2.1 Bars, Wire, Forgings, Mechanical Tubing, and Flash Welded Rings: Solution heat treated free from continuous carbide network.
- 3.2.1.1 Bars and Wire:
- 3.2.1.1.1 All hexagons, other bars 2.75 in. (70 mm) and under in nominal diameter or distance between parallel sides, and wire shall be cold finished.
- 3.2.1.1.2 Bars, other than hexagons, over 2.75 in. (70 mm) in nominal diameter or distance between parallel sides shall be hot finished and descaled.
- 3.2.1.2 Mechanical Tubing: Shall be cold finished.
- 3.2.1.3 Flash Welded Rings: Shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, they shall be manufactured in accordance with AMS 7490.
- 3.2.2 Stock for Forging or Flash Welded Rings: As ordered by the forging or flash welded ring manufacturer.
- 3.3 Properties: The product shall conform to the following requirements; hardness and tensile testing shall be performed in accordance with ASTM A370:
- 3.3.1 Hardness:
- 3.3.1.1 Bars: Not higher than 187 HB, or equivalent, determined approximately midway between surface and center, except that if supplied cold finished, hardness may be as high as 229 HB or equivalent.
- 3.3.1.2 Forgings and Flash Welded Rings: Not higher than 187 HB or equivalent.
- 3.3.1.3 Mechanical Tubing: Not higher than 90 HRB, or equivalent, determined approximately midway between outer and inner surfaces.
- 3.3.2 Tensile Properties: Wire shall have tensile strength not higher than 125,000 psi (860 MPa) or equivalent hardness.
- 3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.
- 3.5 Sizes: Except when exact lengths or multiples of exact lengths are ordered, straight bars, wire, and mechanical tubing will be acceptable in mill lengths of 6 - 20 ft (2 - 6 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 ft (3 m).
- 3.6 Tolerances: Shall conform to all applicable requirements of the following:
- 3.6.1 Bars and Wire: AMS 2241 or MAM 2241.
- 3.6.2 Mechanical Tubing: AMS 2243 or MAM 2243.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all ~~samples for vendor's tests~~ and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Preproduction Tests: Tests of forgings to determine conformance to all applicable technical requirements of this specification when AMS 2375 is specified are classified as preproduction tests and shall be performed prior to or on the first-article shipment of a forging to a purchaser, when a change in material, processing, or both requires reapproval as in 4.4, and when purchaser deems confirmatory testing to be required.

4.2.2. For direct U.S. Military procurement, substantiating test data and, when requested, preproduction forgings shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.

4.3 Sampling: Shall be in accordance with the following:

4.3.1 Bars, Wire, Mechanical Tubing, Flash Welded Rings, and Stock for Flash Welded Rings: AMS 2371.

4.3.2 Forgings and Forging Stock: AMS 2374.

4.4 Approval: When specified, approval and control of forgings shall be in accordance with AMS 2375.

4.5 Reports:

4.5.1 The vendor of the product shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and for tensile properties or hardness, as applicable, of each lot. This report shall include the purchase order number, heat number, AMS 5652E, size, and quantity. If forgings are supplied, the part number and the size and melt source of stock used to make the forgings shall also be included.