



AEROSPACE MATERIAL SPECIFICATION	AMS5654™	REV. G
	Issued	1967-11
	Revised	2018-07
Superseding AMS5654F		
Steel, Corrosion and Heat Resistant, Bars, Wire, Forgings, Mechanical Tubing, and Rings 18Cr - 11Ni - 0.60Cb (Nb) (347) Premium Aircraft Quality, Consumable Electrode Melted Solution Heat Treated UNS S34700		

RATIONALE

AMS5654G introduces Exceptions (3.7), revises Title, composition analysis standards (3.1), Composition (Table 1), Condition (3.3.), Properties (3.4.1.2), Reports (4.4), and Identification (5.2.4), and is a Five-Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers a corrosion and heat resistant steel in the form of bars, wire, forgings, mechanical tubing, flash welded rings, and stock for forging or flash welded rings over 0.50 inch (12.7 mm) in nominal diameter or least distance between parallel sides (see 8.6).

1.2 Application

These products have been used typically for parts requiring corrosion and heat resistance and subject to very rigid inspection standards, especially when such parts are welded during fabrication, for parts requiring oxidation resistance up to 1500 °F (816 °C) but useful at that temperature only when stresses are low, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2241 Tolerances, Corrosion and Heat-Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire

AMS2243 Tolerances Corrosion and Heat-Resistant Steel Tubing

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2018 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

SAE values your input. To provide feedback
on this Technical Report, please visit
<http://standards.sae.org/AMS5654G>

AMS2248	Chemical Check Analysis Limits Corrosion and Heat-Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
AMS2371	Quality Assurance Sampling and Testing Corrosion and Heat-Resistant Steels and Alloys Wrought Products and Forging Stock
AMS2374	Quality Assurance Sampling and Testing Corrosion and Heat-Resistant Steel and Alloy Forgings
AMS2806	Identification Bars, Wire, Mechanical Tubing, and Extrusions Carbon and Alloy Steels and Corrosion and Heat-Resistant Steels and Alloys
AMS2808	Identification Forgings
AMS7490	Rings, Flash Welded Corrosion and Heat-Resistant Austenitic Steels, Austenitic-Type Iron, Nickel, or Cobalt Alloys, or Precipitation-Hardenable Alloys
ARP1917	Clarification of Terms Used in Aerospace Metals Specifications

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM A262	Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels
ASTM A276	Stainless Steel Bars and Shapes
ASTM A370	Mechanical Testing of Steel Products
ASTM A751	Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products
ASTM E45	Determining the Inclusion Content of Steel
ASTM E140	Conversion Tables for Metals Relationship Among Brinell Hardness, Vickers Hardness, Rockwell Hardness, Superficial Hardness, Knoop Hardness, Scleroscope Hardness, and Leeb Hardness

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM A751, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

Table 1 - Composition

Element	Min	Max
Carbon	--	0.08
Manganese	--	2.00
Silicon	--	1.00
Phosphorus	--	0.020
Sulfur	--	0.020
Chromium	17.00	19.00
Nickel	9.00	13.00
Columbium (Niobium)	10xC	1.10
Molybdenum	--	0.75
Copper	--	0.75

3.1.1 Check Analysis

Composition variations shall meet the requirements of AMS2248.

3.2 Melting Practice

Product shall be multiple melted using consumable electrode practice in the remelt cycle.

3.3 Condition

The product shall be supplied in the following condition:

3.3.1 Bars, Wire, Forgings, Mechanical Tubing, and Flash Welded Rings

Solution heat treated.

3.3.1.1 Bars and Wire

3.3.1.1.1 All hexagons, other bars 2.75 inches (69.8 mm) and under in nominal diameter or least distance between parallel sides, and wire shall be cold finished.

3.3.1.1.2 Bars, other than hexagons, over 2.75 inches (69.8 mm) in nominal diameter or least distance between parallel sides, shall be hot finished or cold finished.

3.3.1.1.3 Bars shall not be cut from plate (also see 4.4.1.1).

3.3.1.2 Mechanical Tubing

Shall be cold finished.

3.3.1.3 Flash Welded Rings

Shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, rings shall be manufactured in accordance with AMS7490.

3.3.2 Stock for Forging or Flash Welded Rings

As ordered by the forging or flash welded ring manufacturer.

3.4 Properties

The product shall conform to the following requirements; hardness and tensile testing shall be performed in accordance with ASTM A370:

3.4.1 Tensile Properties

3.4.1.1 Bars and Forgings Over 0.50 Inch (12.7 mm) in Nominal Diameter or Least Distance Between Parallel Sides

Shall be as Shown in Table 2.

Table 2 - Minimum tensile properties

Property	Value
Tensile Strength	75 ksi (517 MPa)
Yield Strength at 0.2% Offset	30.0 ksi (206.8 MPa)
Elongation in 4D	30%
Reduction of Area	40%

NOTE: Minimum tensile properties for bars and forgings have been taken directly from ASTM A276 (see 8.5).

3.4.1.2 Mechanical property requirements for product outside the size range covered by 3.4.1.1 shall be agreed upon between purchaser and producer.

3.4.1.3 Wire shall have tensile strength not higher than 125 ksi (862 MPa).

3.4.2 Hardness

3.4.2.1 Bars

Shall be as shown in Table 3, or equivalent (see 8.2), determined approximately at mid-radius or quarter thickness.

Table 3 - Hardness, HB

Nominal Diameter or Least Distance Between Parallel Sides Inches	Nominal Diameter or Least Distance Between Parallel Sides Millimeters	Min	Max
Up to 2.00, incl	Up to 50.8, incl	140	255
Over 2.00	Over 50.8	--	255

3.4.2.2 Mechanical Tubing

Shall be not higher than 90 HRB, or equivalent (see 8.2), determined approximately midway between outer and inner surfaces.

3.4.2.3 Forgings and Flash Welded Rings

Shall be not higher than 187 HB, or equivalent (see 8.2).

3.4.3 Susceptibility to Intergranular Attack

The product, after sensitizing treatment, shall pass the intergranular corrosion test performed in accordance with ASTM A262, Practice E.

3.4.4 Micro-Inclusion Rating

No specimen shall exceed the limits shown in Table 4, determined in accordance with ASTM E45, Method D, except that the length of any inclusion shall be not greater than 0.015 inch (0.38 mm).

Table 4 - Micro-inclusion rating limits

Type	A	B	C	D
Thin	2.0	1.5	1.5	1.5
Heavy	1.0	1.0	1.0	1.5

3.5 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5.1 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of re-entrant grain flow.

3.6 Tolerances

Shall be as follows:

3.6.1 Bars and Wire

In accordance with AMS2241.

3.6.2 Mechanical Tubing

In accordance with AMS2243.

3.7 Exceptions

Any exceptions shall be authorized by purchaser and reported as in 4.4.2.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The producer of the product shall supply all samples for producer's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

The following requirements are acceptance tests and shall be performed on each heat or lot as applicable:

4.2.1.1 Composition (3.1) and micro-inclusion rating (3.4.4) of each heat.

4.2.1.2 Tensile properties (3.4.1) of each lot of bars, forgings, and wire.

4.2.1.3 Hardness (3.4.2) of each lot of bars, mechanical tubing, forgings, and flash welded rings.

4.2.1.4 Tolerances (3.6) of bars, wire, and mechanical tubing.

4.2.2 Periodic Tests

Susceptibility to intergranular attack (3.3.3), and grain flow of die forgings (3.5.1) are periodic tests and shall be performed at a frequency selected by the producer unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing

Shall be as follows:

4.3.1 Bars, Wire, Mechanical Tubing, Flash Welded Rings, and Stock for Forging or Flash Welded Rings

In accordance with AMS2371.

4.3.2 Forgings

In accordance with AMS2374.

4.4 Reports

4.4.1 The producer of bars, forgings, mechanical tubing, and flash welded rings shall furnish with each shipment a report showing the producer's name and country where the metal was melted (e.g., final melt in the case of metal processed by multiple melting operations) and the results of tests for composition and micro-inclusion rating of each heat and for tensile properties or hardness of each lot and stating that the product conforms to the other technical requirements. This report shall include the purchase order number, heat and lot numbers, AMS5654G, product form, size, and quantity. If forgings are supplied, the part number and the size and melt source of stock used to make the forgings shall also be included.

4.4.1.1 If the ship size/shape is cut from a larger cross section, report the nominal metallurgically worked size (also see 3.3.1.1.3).

4.4.1.2 When material produced to this specification is beyond the sizes allowed in the scope or tables, or other exceptions are taken to the technical requirements listed in Section 3 (see 5.2.4), the report shall contain a statement "This material is certified as AMS5654G(EXC) because of the following exceptions:" and the specific exceptions shall be listed.