

AEROSPACE MATERIAL SPECIFICATION

SAE AMS5657

REV. C

Issued	1960-06
Cancelled	2007-02
Noncurrent	2007-08
Reaf Nonc	2012-10
Superseding AMS5657B	

Steel Bars and Forgings, Corrosion and Moderate Heat-Resistant
15Cr - 7.1Ni - 2.5Mo - 1.1Al

(Composition similar to UNS S15700)

RATIONALE

AMS5657C has been reaffirmed to comply with the SAE five-year review policy.

NONCURRENT NOTICE

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of August, 2007. It is recommended, therefore, that this specification not be specified for new designs.

"NONCURRENT" refers to those materials which have previously been widely used and which may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these as standard materials for future use in new designs. Each of these "NONCURRENT" specifications is available from SAE.

SAENORM.COM : Click to view the full PDF of AMS5657C

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS5657C>**

CANCELLATION NOTICE

This specification has been declared "CANCELLED" by the Aerospace Materials Division, SAE, as of February 2007. By this action, this document will remain listed in the Numerical Section of the Index of Aerospace Material Specifications indicating that it has been "CANCELLED".

Cancelled specifications are available from SAE.

SAENORM.COM : Click to view the full PDF of ams5657c

1. ACKNOWLEDGMENT:

A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.

2. FORM:

Bars, forgings, and forging stock.

3. APPLICATION:

Primarily for parts requiring high strength and oxidation resistance up to 700 F, and where such parts may require welding during fabrication.

4. COMPOSITION:

Carbon	0.09 max
Manganese	1.00 max
Silicon	1.00 max
Phosphorus	0.040 max
Sulfur	0.030 max
Chromium	14.00 - 16.00
Nickel	6.50 - 7.75
Molybdenum	2.00 - 3.00
Aluminum	0.75 - 1.50

4.1 Check Analysis:

Unless otherwise specified, composition variations shall meet the requirements of the latest issue of AMS 2248.

5. CONDITION:

5.1 Bars:

Solution heat treated at 1950 F \pm 25 and water quenched, having hardness as indicated below when tested midway between center and surface.

5.1.1 Rounds: Ground, turned, or polished, having hardness not higher than Brinell 269 or equivalent.

5.1.2 Hexagons: Cold drawn for size after solution treatment, having hardness not higher than Brinell 321 or equivalent.

5.1.3 Flats: Hot finished, solution heat treated, and descaled, having hardness not higher than Brinell 269 or equivalent.

5.2 Forgings:

Unless otherwise specified, solution treated at 1950 F \pm 25 and water quenched, having hardness not higher than Brinell 321 or equivalent.

5.3 Forging Stock:

As ordered by the forging manufacturer.

6. TECHNICAL REQUIREMENTS:

6.1 Properties After Transformation and Precipitation Hardening:

Material shall conform to the following requirements after heating to 1400 F \pm 25, holding at heat 90 min., cooling to 55 F \pm 5 within 1 hr, holding at this temperature for not less than 30 min., heating to 1050 F \pm 10, holding at heat for 90 min., and cooling in air.

6.1.1 Bars:

6.1.1.1 Tensile Properties: Applicable to sizes 6 in. and under in diameter or distance between parallel sides.

Tensile Strength, psi	180,000 min
Yield Strength at 0.2% Offset or at 0.0150 in. in 2 in. Extension Under Load (E = 29,000,000), psi	160,000 min
Elongation, % in 4D	8 min
Reduction of Area, %	25 min

6.1.1.1.1 Tensile test specimens shall be taken parallel to the direction of rolling and midway between center and surface where size permits.

6.1.1.2 Hardness: Not lower than Brinell 375 or equivalent.

6.1.2 Forgings:

6.1.2.1 Hardness: Not lower than Brinell 375 or equivalent.