

Issued	1967-11
Reaffirmed	2012-07
Revised	2013-06
Superseding AMS5666F	

Nickel Alloy, Corrosion and Heat-Resistant, Bars, Forgings, Extrusions, and Rings
62Ni - 21.5Cr - 9.0Mo - 3.65 Cb (Nb)
Annealed

(Compositions similar to UNS N06625)

RATIONALE

AMS5666G clarifies that grain size is to be tested and reported only for the applicable product sizes (4.2.1, 4.4.1) and is a Five Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers a corrosion and heat-resistant nickel alloy in the form of bars, forgings, extrusions, flash welded rings, and stock for forging, extruding, or flash welded rings.

1.2 Application

These products have been used typically for parts requiring both corrosion and oxidation resistance up to 2000 °F (1093 °C) and where such parts may require welding during fabrication, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS2261 Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Bars, Rods, and Wire

AMS2269 Chemical Check Analysis Limits, Nickel, Nickel Alloys, and Cobalt Alloys

AMS2371 Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2013 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS5666G>**

AMS2374	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steel and Alloy Forgings
AMS2806	Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat-Resistant Steels and Alloys
AMS2808	Identification, Forgings
AMS7490	Rings, Flash Welded, Corrosion and Heat-Resistant Austenitic Steels, Austenitic-Type Iron, Nickel, or Cobalt Alloys, or Precipitation-Hardenable Alloys

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM A 370	Mechanical Testing of Steel Products
ASTM E 10	Brinell Hardness of Metallic Materials
ASTM E 112	Determining Average Grain Size
ASTM E 354	Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - COMPOSITION

Element	min	max
Carbon	--	0.10
Manganese	--	0.50
Silicon	--	0.50
Phosphorus	--	0.015
Sulfur	--	0.015
Chromium	20.00	23.00
Molybdenum	8.00	10.00
Columbium (Niobium)	3.15	4.15
Tantalum	--	0.05
Cobalt	--	1.00
Titanium	--	0.40
Aluminum	--	0.40
Iron	--	5.00
Nickel	remainder	

3.1.1 Check Analysis

Composition variations shall meet the applicable requirements of AMS2269.

3.2 Condition

The product shall be supplied in the following condition:

3.2.1 Bars

Hot finished and annealed; round bars shall be ground or turned.

3.2.2 Forgings, Extrusions, and Flash Welded Rings

Annealed.

3.2.2.1 Flash welded rings shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, rings shall be manufactured in accordance with AMS7490.

3.2.3 Stock for Forging, Extruding, or Flash Welded Rings

As ordered by the forging, extrusion, or flash welded ring manufacturer.

3.3 Properties

The product shall conform to the following requirements:

3.3.1 Bars, Forgings, and Flash Welded Rings

3.3.1.1 Tensile Properties

Shall be as shown in Table 2, determined in accordance with ASTM A 370 on specimens taken from product under 4 inches (101.6 mm) in least cross-sectional dimension:

TABLE 2 - MINIMUM TENSILE PROPERTIES

Property	Value
Tensile Strength	120.0 ksi (827 MPa)
Yield Strength at 0.2% Offset	60.0 ksi (414 MPa)
Elongation in 4D	30%

3.3.1.2 Hardness

Shall be not higher than 287 HB, or equivalent (See 8.2), determined in accordance with ASTM E 10.

3.3.1.3 Average Grain Size

Shall be ASTM No. 5 or finer, determined in accordance with ASTM E 112, for product with a least cross-section dimension under 2-1/2 inches (63.5 mm).

3.3.2 Extrusions and Stock for Forging, Extruding, and Flash Welded Rings

Shall have properties as agreed upon by purchaser and vendor.

3.4 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.4.1 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of reentrant grain flow.

3.5 Tolerances

Bars shall conform to all applicable requirements of AMS2261.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1), tensile properties (3.3.1.1), hardness (3.3.1.2), average grain size (3.3.1.3) when applicable, and tolerances (3.5) are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests

Grain flow of die forgings (3.4.1) is a periodic test and shall be performed at a frequency selected by the vendor unless frequency of test is specified by purchaser.

4.3 Sampling and Testing

Shall be as follows:

4.3.1 Bars, Flash Welded Rings, Extrusions, and Stock for Forging, Extruding, or Flash Welded Rings

In accordance with AMS2371.

4.3.2 Forgings

In accordance with AMS2374.

4.4 Reports

4.4.1 The vendor of product shall furnish with each shipment a report of the composition of each heat and the condition, hardness, tensile properties, and average grain size when applicable, of each lot, and stating that the product conforms to the other technical requirements. The report shall include the purchase order number, heat and lot numbers, AMS5666G, size and quantity. If forgings are supplied, the size and melt source of stock used to make the forgings shall also be included.

4.4.2 The vendor of forging stock shall furnish with each shipment a report showing the results of tests for composition of each heat and the results of any additional property requirements imposed by the purchase order (See 8.5). The report shall include the purchase order number, heat number, AMS5666G, size, and quantity.

4.5 Resampling and Retesting

Shall be as follows:

4.5.1 Bars, Flash Welded Rings, Extrusions, and Stock for Forging, Extruding, or Flash Welded Rings

In accordance with AMS2371.

4.5.2 Forgings

In accordance with AMS2374.