

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS5683A

Issued 10-15-40

Revised 7-1-48

ALLOY WIRE, CORROSION AND HEAT RESISTANT Cold Drawn

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. APPLICATION: Primarily for welding rod.

3. COMPOSITION:

| | |
|-----------------------|---------------|
| Carbon | 0.15 max |
| Manganese | 1.00 max |
| Silicon | 0.50 max |
| Chromium | 14.00 - 17.00 |
| Nickel + Cobalt | 72.00 min |
| Cobalt, if determined | 1.00 max |
| Iron | 6.00 - 10.00 |
| Copper | 0.50 max |

4. CONDITION: Cold-drawn, unless otherwise specified.

5. TECHNICAL REQUIREMENTS: Wire, melted during welding, shall flow smoothly and evenly, and shall be capable of producing acceptable welds.

6. QUALITY: Wire shall be uniform in quality and condition, clean, sound, smooth, and free from foreign materials and from internal and external defects detrimental to its use for welding purposes.

7. TOLERANCES: Unless otherwise specified, diameter of the wire shall vary not more than plus 0.001 in. and minus 0.003 in. from the diameter ordered.

8. REPORTS: Unless otherwise specified, the vendor of wire shall furnish with each shipment three copies of a notarized report of the results of tests for chemical composition of each heat in the shipment. This report shall include the purchase order number, heat number, material specification number, size, and quantity from each heat.

9. IDENTIFICATION:

9.1 Packaging shall be accomplished in such a manner as to ensure that the wire, during shipment and storage, will be protected against mechanical injury and exposure to moisture.

9.2 Each bundle or container shall be permanently and legibly marked with the following information:

ALLOY WIRE, CORROSION AND HEAT RESISTANT
AMS 5683A
SIZE _____
QUANTITY _____
HEAT NUMBER _____
PURCHASE ORDER NUMBER _____
MANUFACTURER'S IDENTIFICATION _____

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards, approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment is made by the Board and its Committees will not investigate or consider any matter which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."