

Issued	1940-10
Revised	1990-04
Noncurrent	2000-03
Reaf Nonc	2012-04
Superseding AMS5683E	

Alloy Welding Wire, Corrosion and Heat Resistant  
75Ni - 15.5Cr - 8.0Fe

#### RATIONALE

AMS5683F has been reaffirmed to comply with the SAE five-year review policy.

#### NONCURRENT NOTICE

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of March 2000. It is recommended, therefore, that this specification not be specified for new designs.

"NONCURRENT" refers to those materials which have previously been widely used and which may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these as standard materials for future use in new designs. Each of these "NONCURRENT" specifications is available from SAE upon request.

SAENORM.COM : Click to view the full PDF of AMS5683f

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:** Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: CustomerService@sae.org  
http://www.sae.org

**SAE WEB ADDRESS:**

**SAE values your input. To provide feedback  
on this Technical Report, please visit  
<http://www.sae.org/technical/standards/AMS5683F>**

## 1. SCOPE:

### 1.1 Form:

This specification covers a corrosion and heat resistant nickel alloy in the form of welding wire.

### 1.2 Application:

Primarily for use as filler metal for oxyacetylene welding.

## 2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

### 2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

#### 2.1.1 Aerospace Material Specifications:

AMS 2269	Chemical Check Analysis Limits, Wrought Nickel Alloys and Cobalt Alloys
AMS 2350	Standards and Test Methods
AMS 2371	Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock
AMS 2813	Packaging of Welding Wire, Standard Method
AMS 2815	Identification, Welding Wire, Line Code System
AMS 2816	Identification, Welding Wire, Color Code System

### 2.2 ASTM Publications:

Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E354 Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

### 2.3 U.S. Government Publications:

Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

#### 2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

### 3. TECHNICAL REQUIREMENTS:

#### 3.1 Composition:

Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E354, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Carbon	--	0.10
Manganese	--	1.00
Silicon	--	0.50
Sulfur	--	0.015
Chromium	14.00	17.00
Iron	6.00	10.00
Cobalt (3.1.1)	--	1.00
Copper	--	0.50
Nickel + Cobalt	72.00	--

3.1.1 Determination not required for routine acceptance.

3.1.2 Check Analysis: Composition variations shall meet the requirements of AMS 2269.

#### 3.2 Condition:

Cold finished in a temper which will provide proper feeding of the wire in machine welding equipment.

3.2.1 Wire shall be furnished on disposable spools for machine welding or in cut lengths for manual welding, as ordered.

3.2.2 In-process annealing between cold rolling or drawing operations shall be performed in a suitable protective atmosphere.

3.2.3 Drawing compounds, oxides, and dirt shall be removed by cleaning processes which will result neither in pitting nor cause gas absorption by the wire or deposition of substances harmful to welding operations.

#### 3.3 Properties:

Wire shall conform to the following requirements:

3.3.1 Weldability: Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds, determined by a procedure agreed upon by purchaser and vendor.

3.3.2 Spooled Wire: Shall conform to 3.3.2.1 and 3.3.2.2, unless otherwise agreed upon by purchaser and vendor:

3.3.2.1 Cast: Wire wound on standard 12-in. (300 mm) diameter spools shall have imparted to it a curvature such that a specimen sufficient in length, 4 - 8 ft (1200 - 2400 mm), to form one loop, when cut from the spool and laid on a flat surface, shall form a circle not less than 15 in. (375 mm) and not greater than 30 in. (750 mm) in diameter.

3.3.2.2 Helix: The specimen on which cast was determined, when laid on a flat surface and measured between adjacent turns, shall show a vertical separation not greater than 1 in. (25 mm).

3.4 Quality:

Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

3.5 Sizes and Tolerances:

Wire shall be supplied in the sizes and to the tolerances shown in 3.5.1 and 3.5.2, unless otherwise specified.

3.5.1 Diameter:

TABLE I

Form	Nominal Diameter	Tolerance Inch	
	Inch	plus	minus
Cut lengths	0.062, 0.094, 0.125, 0.156	0.003	0.003
Spools	0.035, 0.045	0.001	0.002
Spools	0.062, 0.094	0.002	0.002

TABLE I (SI)

Form	Nominal Diameter	Tolerance, Millimetre	
	Millimetres	plus	minus
Cut lengths	1.55, 2.35, 3.10, 4.00	0.08	0.08
Spools	0.90, 1.15	0.03	0.05
Spools	1.55, 2.35	0.05	0.05

3.5.2 Length: Cut lengths shall be furnished in 18, 27, or 36 in. (450, 675, or 900 mm) lengths, as ordered, and shall not vary more than +0, -0.5 in. (-13 mm) from the length ordered.

#### 4. QUALITY ASSURANCE PROVISIONS:

##### 4.1 Responsibility for Inspection:

The vendor of wire shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to the requirements of this specification.

##### 4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1) and tolerances (3.5) are classified as acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests: Tests to determine conformance to requirements for weldability (3.3.1), cast (3.3.2.1), and helix (3.3.2.2) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

##### 4.3 Sampling:

Shall be in accordance with AMS 2371 and as specified herein.

##### 4.4 Reports:

4.4.1 The vendor of wire shall furnish with each shipment three copies of a report showing the results of tests for chemical composition of each heat and stating that the wire conforms to the other technical requirements of this specification. This report shall include the purchase order number, heat number, AMS 5683F, nominal size, and quantity from each heat.

4.4.2 When parts made of this wire or assemblies requiring use of this welding wire are supplied, the part or assembly manufacturer shall inspect each lot of wire to determine conformance to the technical requirements of this specification and shall furnish with each shipment three copies of a report stating that the wire conforms. This report shall include the purchase order number, AMS 5683F, part or assembly number, and quantity.

##### 4.5 Resampling and Retesting:

Shall be in accordance with AMS 2371.