

**AEROSPACE
MATERIAL
SPECIFICATION**

SAE AMS 5685L

Issued DEC 1939
Revised MAR 2001
Cancelled AUG 2007

Superseded by AS5685

Steel, Corrosion Resistant, Safety Wire,
18Cr - 11.5Ni (SAE 30305)
Solution Heat Treated, Cold Finished

(Composition similar to UNS S30500)

RATIONALE

AMS 5685K has been designated cancelled and superseded since equivalent technical requirements are contained in AS5685.

CANCELLATION NOTICE

This specification has been declared "CANCELLED" by the Aerospace Materials Division, SAE, as of August, 2007 and has been superseded by AS5685. The requirements of the latest issue of AS5685 shall be fulfilled whenever reference is made to the cancelled AMS 5685K. By this action, this document will remain listed in the Numerical Section of the Index of Aerospace Material Specifications indicating that it has been "CANCELLED".

Cancelled specifications are available from SAE.

SAENORM.COM : Click to view the full PDF of ams5685L

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2007 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

SAENORM.COM : Click to view the full PDF of ams56851

AEROSPACE MATERIAL SPECIFICATION

Issued DEC 1939
Revised MAR 2001
Cancelled AUG 2007

Superseded by AS5685

Steel, Corrosion Resistant, Safety Wire,
18Cr - 11.5Ni (SAE 30305)
Solution Heat Treated, Cold Finished
(Composition similar to UNS S30500)

1. SCOPE:

1.1 Form:

This specification covers a corrosion-resistant steel in the form of wire.

1.2 Application:

This product has typically been used for safety wire, but usage is not limited to that application.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

- | | |
|----------|---|
| AMS 2241 | Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire |
| MAM 2241 | Tolerances, Metric, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire |
| AMS 2248 | Chemical Check Analysis Limits, Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys |
| AMS 2371 | Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock |

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2007 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: http://www.sae.org

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19248-2959.

ASTM B 117 Operating Salt Spray Fog Apparatus

ASTM E 8 Tension Testing of Metallic Materials

ASTM E 8M Tension Testing of Metallic Materials (Metric)

ASTM E 353 Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Wire shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	--	0.08
Manganese	--	2.00
Silicon	--	1.00
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	17.00	19.00
Nickel	10.00	13.00
Molybdenum	--	0.75
Copper	--	0.75

3.1.1 Chemical analysis of initial ingot, bar, or rod stock before drawing is acceptable provided the processes used for drawing or rolling, annealing, and cleaning, are controlled to ensure continued conformance to chemical composition requirements.

3.1.2 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2248.

3.2 Condition:

Solution heat treated and cold finished.

3.3 Properties:

Wire shall conform to the following requirements:

- 3.3.1 Tensile Properties: Shall be as shown in Table 2, determined in accordance with ASTM E 8 or ASTM E 8M.

TABLE 2 - Maximum Tensile Strength

Property	Value
Coiled Wire	110 ksi (758 MPa)
Straight Lengths	120 ksi (827 MPa)

- 3.3.2 Bending: Wire shall withstand, without cracking, bending at room temperature flat on itself.
- 3.3.3 Wire shall exhibit no evidence of corrosion when exposed for not less than two hours to the conditions of ASTM B 117.

3.4 Quality:

Wire, as received by purchaser, shall be uniform in quality and condition, cylindrical, and free from kinks, twists, scrapes, splits, cold shuts, and other imperfections detrimental to usage of the wire. The surface shall have a bright, smooth finish free from pits, abrasions, and other defects.

3.5 Tolerances:

Shall conform to AMS 2241 or MAM 2241.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of wire shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to specified requirements.

4.2 Classification of Tests:

- 4.2.1 Acceptance Tests: Composition (3.1), tensile properties (3.3.1), and bending (3.3.2) are acceptance tests and shall be performed on each heat or lot as applicable.
- 4.2.2 Periodic Test: Resistance to corrosion (3.3.3) is a periodic test and shall be performed at a frequency selected by the vendor unless a frequency of testing is specified by purchaser.

4.3 Sampling and Testing:

Shall be in accordance with AMS 2371.