

AEROSPACE

AMS 5687D

MATERIAL SPECIFICATIONS

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

Issued 7-1-48
Revised 2-15-65

ALLOY WIRE, CORROSION AND HEAT RESISTANT Nickel Base - 15.5Cr - 8.0Fe Annealed

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **APPLICATION:** Primarily for lock wire and wire cloth requiring oxidation resistance superior to that of the 18-8 type of steel.
3. **COMPOSITION:**

	min	max
Ø Carbon	--	0.06
Manganese	--	1.00
Silicon	--	0.50
Sulfur	--	0.015
Chromium	14.00 - 17.00	
Nickel + Cobalt	72.00	--
Cobalt (1)	--	1.00
Iron	6.00	10.00
Columbium + Tantalum (1)	--	1.00
Titanium (1)	--	0.50
Aluminum (1)	--	0.35
Copper	--	0.50

(1) Determination not required for routine acceptance.

- 3.1 **Check Analysis:** Composition variations shall meet the requirements of the latest issue of AMS 2269.
4. **CONDITION:** Cold-drawn from hot finished wire or rod, and annealed, and descaled if necessary, unless otherwise specified.

4.1 Wire shall be supplied in coils or on spools, unless otherwise ordered.

5. **TECHNICAL REQUIREMENTS:**

5.1 **Tensile Properties:**

Nominal Diameter Inch	Tensile Strength, psi, min	
	Coils or Spools	Straight Lengths
0.002 to 0.015, incl	130,000	--
Over 0.015 to 0.040, incl	115,000	--
Over 0.040	110,000	125,000

- 5.2 **Wrapping:** Wire shall withstand, without cracking, wrapping at room temperature five full, closely spaced turns around a diameter equal to the diameter of the wire.
6. **QUALITY:** Wire shall be uniform in quality and condition, clean, sound, smooth, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.

Section 8.3 of the SAE Technical Board rules provides that: "All technical reports including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no obligation to conform to or be guided by any technical report. In formulating and applying technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the reports are responsible for protecting themselves against liability for infringement of patents."