

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 5690E

Issued 12-4-39

Revised 2-1-56

STEEL WIRE, CORROSION AND HEAT RESISTANT 17Cr - 12Ni - 2.5Mo (SAE 30316)

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **APPLICATION:** Primarily for use in woven wire screening, and as bare wire filler metal for welding.
3. **COMPOSITION:**

		Check Analysis	
		Under Min	or Over Max

	Carbon	0.08 max	--	0.01
	Manganese	2.00 max	--	0.04
	Silicon	1.00 max	--	0.05
	Phosphorus	0.040 max	--	0.005
∅	Sulfur	0.030 max	--	0.005
	Chromium	17.00 - 20.00	0.20	0.20
	Nickel	12.00 - 14.00	0.15	0.15
	Molybdenum	2.00 - 3.00	0.10	0.10
	Copper	0.50 max	--	0.03

4. **CONDITION:** Solution heat treated free from continuous carbide network and bright finished.

5. **TECHNICAL REQUIREMENTS:**

- 5.1 **Bending:** Wire shall be capable of being bent at room temperature flat on itself without breaking or cracking of the surface.
- 5.2 **Melting:** When used for welding, melted wire shall flow smoothly and evenly and shall be capable of producing acceptable welds.

6. **QUALITY:**

- 6.1 Wire shall be uniform in quality and condition, cylindrical, clean, and free from kinks, twists, scrapes, splits, cold shuts, and other injurious defects.
- 6.2 The surface shall have a bright, smooth, cold-drawn finish, free from pits, abrasions, and other surface imperfections.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."