

ALLOY WIRE, CORROSION AND HEAT RESISTANT
72Ni - 15.5Cr - 0.95(Cb+Ta) - 2.5Ti - 0.70Al - 7.0Fe
No. 1 Temper

UNS N07750

1. SCOPE:

1.1 Form: This specification covers a corrosion and heat resistant nickel alloy in the form of round, square, and flat wire.

1.2 Application: Primarily for helical springs requiring optimum resistance to relaxation up to 1000°F (540°C) with moderate or relatively low stresses.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2269 - Chemical Check Analysis Limits, Wrought Nickel Alloys and Cobalt Alloys

AMS 2350 - Standards and Test Methods

AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E8 - Tension Testing of Metallic Materials

ASTM E354 - Chemical Analysis of High-Temperature, Electrical, Magnetic, and other Similar Iron, Nickel, and Cobalt Alloys

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

AMS 5698D

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.3 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E354, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Carbon	--	0.08
Manganese	--	1.00
Silicon	--	0.50
Sulfur	--	0.010
Chromium	14.00 -	17.00
Nickel + Cobalt	70.00	--
Columbium + Tantalum	0.70 -	1.20
Titanium	2.25 -	2.75
Aluminum	0.40 -	1.00
Iron	5.00 -	9.00
Cobalt (3.1.1)	--	1.00
Copper	--	0.50

3.1.1 Determination not required for routine acceptance.

3.1.2 Check Analysis: Composition variations shall meet the requirements of AMS 2269.

3.2 Condition: Cold finished from hot finished wire or rod which has been previously ground or has had surface preparation, other than by pickling, for removal of seams and other injurious surface imperfections and solution heat treated.

3.2.1 Wire over 0.025 in. (0.65 mm) in nominal diameter or thickness shall be copper coated and cold reduced approximately 15% following solution heat treatment.

3.3 Heat Treatment: Wire shall be solution heat treated by heating to a temperature not lower than 2100°F (1150°C), holding at heat for not more than 15 min., and cooling as required.

3.4 Properties: Wire shall conform to the following requirements; tensile testing shall be performed in accordance with ASTM E8:

3.4.1 As Received:

3.4.1.1 Tensile Properties: Shall be as specified in Table I.

TABLE I

Nominal Diameter or Thickness Inch	Tensile Strength psi	
	min	max
Up to 0.025, incl	--	150,000
Over 0.025 to 0.500, incl	130,000	165,000

TABLE I (SI)

Nominal Diameter or Thickness Millimetres	Tensile Strength MPa	
	min	max
Up to 0.65, incl	--	1035
Over 0.65 to 12.50, incl	895	1140

3.4.1.2 Wrapping: Wire shall withstand, without cracking, wrapping at room temperature five full, closely-spaced turns around a diameter equal to the following:

Wire Shape	Wrapping Diameter
Round	Nominal diameter of wire
Square	Nominal diagonal of wire
Flat	Nominal width of wire

3.4.2 After Precipitation Heat Treatment: Wire shall have tensile properties as specified in Table II after being precipitation heat treated by heating to 1350°F \pm 25 (730°C \pm 15), holding at heat for 16 hr \pm 0.5, and cooling in air.

TABLE II

Nominal Diameter or Thickness Inch	Tensile Strength psi, min
Up to 0.025, incl	155,000
Over 0.025 to 0.500, incl	165,000

TABLE II (SI)

Nominal Diameter or Thickness Millimetres	Tensile Strength MPa, min
Up to 0.65, incl	1070
Over 0.65 to 12.50, incl	1140

3.5 Quality: Wire, as received by purchaser, shall be uniform in quality and condition and free from kinks, twists, scrapes, splits, cold shuts, and other imperfections detrimental to usage of the wire. The surface shall have a bright, smooth finish free from pits, abrasions, and other defects.

3.6 Tolerances: Unless otherwise specified, tolerances shall be as follows:

3.6.1 Round Wire and Square Wire:

TABLE III

Nominal Diameter or Thickness Inch	Tolerance, Inch plus and minus
0.003 to 0.005, excl	0.0001
0.005 to 0.008, excl	0.0002
0.008 to 0.012, excl	0.0003
0.012 to 0.024, excl	0.0004
0.024 to 0.033, excl	0.0005
0.033 to 0.044, excl	0.0008
0.044 to 0.312, excl	0.0010
0.312 to 0.500, incl	0.0015

TABLE III (SI)

Nominal Diameter or Thickness Millimetres	Tolerance, Millimetre plus and minus
0.08 to 0.12, excl	0.003
0.12 to 0.20, excl	0.005
0.20 to 0.30, excl	0.008
0.30 to 0.60, excl	0.010
0.60 to 0.85, excl	0.013
0.85 to 1.15, excl	0.020
1.15 to 7.90, excl	0.025
7.90 to 12.50, incl	0.038

3.6.2 Out-of-Roundness: Round wire shall not be out-of-round by more than one-half the total permissible tolerance in 3.5.1.

3.6.3 Flat Wire 0.062 to 0.375 in. (1.57 to 9.52 mm), Incl, in Nominal Width:

TABLE IV

Nominal Thickness Inch	Tolerance, Inch plus and minus	
	Thickness	Width
Up to 0.029, excl	0.0010	0.0005
0.029 to 0.035, excl	0.0015	0.0005
0.035 to 0.3125, incl	0.0020	0.0005

TABLE IV (SI)

Nominal Thickness Millimetres	Tolerance, Millimetre plus and minus	
	Thickness	Width
Up to 0.75, excl	0.025	0.12
0.75 to 0.90, excl	0.038	0.12
0.90 to 8.000, incl	0.050	0.12

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of wire shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to the requirements of this specification.

4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling: Shall be in accordance with AMS 2371.

4.4 Reports:

4.4.1 The vendor of wire shall furnish with each shipment three copies of a report showing the results of tests for chemical composition of each heat and for tensile properties and wrapping requirements of each lot. This report shall include the purchase order number, heat number, AMS 5698D, size, and quantity from each heat.