



# AEROSPACE MATERIAL SPECIFICATION

AMS5698

REV. G

Issued 1953-06  
Revised 2003-01  
Reaffirmed 2013-12

Superseding AMS5698F

Nickel Alloy, Corrosion and Heat-Resistant, Wire  
72Ni - 15.5Cr - 0.95Cb - 2.5Ti - 0.70Al - 7.0Fe  
No. 1 Temper, Precipitation Hardenable  
(Composition similar to UNS N07750)

## RATIONALE

AMS5698G has been reaffirmed to comply with the SAE five-year review policy.

### 1. SCOPE:

#### 1.1 Form:

This specification covers a corrosion and heat-resistant nickel alloy in the form of round, square, and flat wire 0.500 inch (12.70 mm) and under in nominal diameter or thickness.

#### 1.2 Application:

This wire has been used typically for helical springs requiring optimum resistance to relaxation up to 1000 °F (538 °C) with moderate or relatively low stresses, but usage is not limited to such applications.

### 2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

#### 2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001 or [www.sae.org](http://www.sae.org).

AMS 2269 Chemical Check Analysis Limits, Nickel, Nickel Alloys and Cobalt Alloys  
AMS 2371 Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2013 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: [CustomerService@sae.org](mailto:CustomerService@sae.org)  
http://www.sae.org

SAE values your input. To provide feedback on this Technical Report, please visit <http://www.sae.org/technical/standards/AMS5698G>

SAE WEB ADDRESS:

## 2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959 or [www.astm.org](http://www.astm.org).

ASTM E 8	Tension Testing of Metallic Materials
ASTM E 8M	Tension Testing of Metallic Materials (Metric)
ASTM E 354	Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

## 3. TECHNICAL REQUIREMENTS:

### 3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	--	0.08
Manganese	--	1.00
Silicon	--	0.50
Sulfur	--	0.010
Chromium	14.00	17.00
Nickel	70.00	--
Columbium	0.70	1.20
Titanium	2.25	2.75
Aluminum	0.40	1.00
Iron	5.00	9.00
Cobalt	--	1.00
Tantalum	--	0.05
Copper	--	0.50

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2269.

### 3.2 Condition:

Cold drawn from hot finished wire or rod which has had suitable surface preparation for removal of scale, seams, and other injurious surface imperfections. Wire shall be solution heat treated by heating within the range 2000 to 2200 °F (1093 to 1204 °C) before reducing to the size ordered.

3.2.1 Wire in the size range 0.025 to 0.500 inch (0.64 to 12.70 mm) in nominal diameter or thickness shall be cold reduced approximately 15% following solution heat treatment.

3.2.2 All traces of lubricant shall be removed after cold reduction.

### 3.3 Properties:

Wire shall conform to the following requirements; tensile testing shall be performed in accordance with ASTM E 8 or ASTM E 8M:

#### 3.3.1 As Received:

##### 3.3.1.1 Tensile Properties: Shall be as shown in Table 2.

TABLE 2A - Tensile Strength, Inch/Pound Units

Nominal Diameter or Thickness Inch	Tensile Strength ksi, min	Tensile Strength ksi, max
Up to 0.025, incl	--	150
Over 0.025 to 0.500, incl	130	165

TABLE 2B - Tensile Strength, SI Units

Nominal Diameter or Thickness Millimeters	Tensile Strength MPa, min	Tensile Strength MPa, max
Up to 0.64, incl	--	1034
Over 0.64 to 12.70, incl	896	1138

##### 3.3.1.2 Wrapping: Wire shall withstand, without cracking, wrapping at room temperature five full, closely-spaced turns around a diameter as shown in Table 3.

TABLE 3 - Wrapping Parameters

Wire Shape	Wrapping Diameter
Round	Nominal diameter of wire
Square	Nominal diagonal of wire
Flat	Nominal width of wire

##### 3.3.2 After Precipitation Heat Treatment: Wire shall have tensile properties as shown in Table 4 after being precipitation heat treated by heating to 1350 °F ± 25 (732 °C ± 14), holding at heat for 16 hours ± 0.5, and cooling at a rate equivalent to air cooling.

TABLE 4A - Minimum Tensile Strength, Inch/Pound Units

Nominal Diameter or Thickness Inch	Tensile Strength ksi
Up to 0.025, incl	155
Over 0.025 to 0.500, incl	165

TABLE 4B - Minimum Tensile Strength, SI Units

Nominal Diameter or Thickness Millimeters	Tensile Strength MPa
Up to 0.64, incl	1069
Over 0.64 to 12.70, incl	1138

## 3.4 Quality:

Wire, as received by purchaser, shall be uniform in quality and condition and free from kinks, twists, scrapes, splits, cold shuts, and other imperfections detrimental to usage of the wire. The surface of the wire shall be free from lubricant and have a bright, smooth finish free from pits, abrasions, and other defects.

## 3.5 Tolerances:

Shall be as follows:

## 3.5.1 Round Wire and Square Wire: Shall be as shown in Table 5.

TABLE 5A - Round and Square Wire Tolerance, Inch/Pound Units

Nominal Diameter or Thickness Inch	Tolerance Inch Plus and Minus
0.003 to 0.005, excl	0.0001
0.005 to 0.008, excl	0.0002
0.008 to 0.012, excl	0.0003
0.012 to 0.024, excl	0.0004
0.024 to 0.033, excl	0.0005
0.033 to 0.044, excl	0.0008
0.044 to 0.312, excl	0.0010
0.312 to 0.500, incl	0.0015

TABLE 5B - Round and Square Wire Tolerance, SI Units

Nominal Diameter or Thickness Millimeters	Tolerance Millimeters Plus and Minus
0.08 to 0.13, excl	0.003
0.13 to 0.20, excl	0.005
0.20 to 0.30, excl	0.008
0.30 to 0.61, excl	0.010
0.61 to 0.84, excl	0.013
0.84 to 1.12, excl	0.020
1.12 to 7.92, excl	0.025
7.92 to 12.70, incl	0.038

- 3.5.2 Out-of-Roundness: Round wire shall not be out-of-round by more than one-half the total permissible tolerance in 3.5.1.
- 3.5.3 Flat Wire 0.062 to 0.375 inch (1.57 to 9.52 mm), Inclusive, in Nominal Width: Shall be as shown in Table 6.

TABLE 6A - Flat Wire Tolerances, Inch/Pound Units

Nominal Thickness Inch	Tolerance Inch	Tolerance Inch
	Plus and Minus Thickness	Plus and Minus Width
Up to 0.029, excl	0.0010	0.005
0.029 to 0.035, excl	0.0015	0.005
0.035 to 0.3125, incl	0.0020	0.005

TABLE 6B - Flat Wire Tolerances, SI Units

Nominal Thickness Millimeters	Tolerance Millimeter	Tolerance Millimeter
	Plus and Minus Thickness	Plus and Minus Width
Up to 0.74, excl	0.025	0.13
0.74 to 0.89, excl	0.038	0.13
0.89 to 7.938, incl	0.051	0.13

#### 4. QUALITY ASSURANCE PROVISIONS:

##### 4.1 Responsibility for Inspection:

The vendor of wire shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to specified requirements.

##### 4.2 Classification of Tests:

All technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

##### 4.3 Sampling and Testing:

Shall be in accordance with AMS 2371.