

Issued 1971-11
Revised 2006-09
Reaffirmed 2012-02

Superseding AMS5703C

Nickel Alloy, Corrosion and Heat-Resistant, Bars, Forgings, and Rings
41.5Ni - 16Cr - 37Fe - 2.9Cb - 1.8Ti
Consumable Electrode or Vacuum Induction Melted
1750 °F (954 °C) Solution, Stabilization, and Precipitation Heat Treated
(Composition similar to UNS N09706)

RATIONALE

AMS5703D has been reaffirmed to comply with the SAE five-year review policy.

1. SCOPE

1.1 Form

This specification covers a corrosion and heat-resistant nickel alloy in the form of bars, forgings, flash welded rings, and stock for forging or flash welded rings.

1.2 Application

These products have been used primarily for parts requiring a combination of resistance to creep and stress-rupture up to 1300 °F (704 °C), oxidation resistance up to 1800 °F (982 °C), and good machinability, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), or www.sae.org.

AMS 2261	Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Bars, Rods, and Wire
AMS 2269	Chemical Check Analysis Limits, Nickel, Nickel Alloys and Cobalt Alloys
AMS 2371	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS 2374	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steel and Alloy Forgings
AMS 2750	Pyrometry
AMS 2806	Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat-Resistant Steels and Alloys

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

SAE values your input. To provide feedback on this Technical Report, please visit <http://www.sae.org/technical/standards/AMS5703D>

AMS 2808 Identification, Forgings
 AMS 7490 Rings, Flash Welded, Corrosion and Heat-Resistant Austenitic Steels, Austenitic-Type Iron, Nickel, or Cobalt Alloys or Precipitation Hardenable Alloys

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, or www.astm.org.

ASTM E 8 Tension Testing of Metallic Materials
 ASTM E 8M Tension Testing of Metallic Materials (Metric)
 ASTM E 10 Brinell Hardness of Metallic Materials
 ASTM E 112 Determining Average Grain Size
 ASTM E 139 Conducting Creep, Creep-Rupture, and Stress-Rupture Tests of Metallic Materials
 ASTM E 292 Conducting Time-for-Rupture Notch Tension Tests of Materials
 ASTM E 354 Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - COMPOSITION

Element	min	max
Carbon	--	0.06
Manganese	--	0.35
Silicon	--	0.35
Phosphorus	--	0.020
Sulfur	--	0.015
Chromium	14.50	17.50
Nickel	39.00	44.00
Columbium	2.50	3.30
Titanium	1.50	2.00
Aluminum	--	0.40
Boron	--	0.006
Tantalum	--	0.05
Copper	--	0.30
Iron	remainder	

3.1.1 Check Analysis

Composition variations shall meet the applicable requirements of AMS 2269.

3.2 Melting Practice

Alloy shall be produced by multiple melting using consumable electrode practice in the remelt cycle or shall be induction melted under vacuum. If consumable electrode remelting is not performed in vacuum, electrodes which have been produced by vacuum induction melting shall be used.

3.3 Condition

The product shall be supplied in the following condition:

3.3.1 Bars, Forgings, and Flash Welded Rings

Solution, stabilization, and precipitation heat treated and descaled.

3.3.1.1 Bars shall be hot finished; round bars shall be turned or ground.

3.3.1.2 Flash welded rings shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, rings shall be manufactured in accordance with AMS 7490.

3.3.2 Stock for Forging or Flash Welded Rings

As ordered by the forging or flash welded ring manufacturer.

3.4 Heat Treatment

Bars, forgings, and flash welded rings shall be heat treated as follows; pyrometry shall be in accordance with AMS 2750:

3.4.1 Solution Heat Treatment

3.4.1.1 Bars

Shall be solution heat treated by heating to a temperature within the range 1700 to 1800 °F (927 to 982 °C), holding at the selected temperature within ± 25 °F (± 14 °C) for a time commensurate with cross-sectional thickness, and cooling as required.

3.4.1.2 Forgings and Flash Welded Rings

Shall be solution heat treated by heating within the range 1700 to 1800 °F (927 to 982 °C), holding at the selected temperature within ± 25 °F (± 14 °C) for not less than 30 minutes, and cooling as required.

3.4.2 Stabilization Heat Treatment

Heat to 1550 °F ± 25 (843 °C ± 14), hold at heat for 3 hours ± 0.25 , and cool to room temperature at a rate equivalent to air cooling.

3.4.3 Precipitation Heat Treatment

Heat to 1325 °F ± 15 (718 °C ± 8), hold at heat for 8 hours ± 0.25 , furnace cool at a rate not faster than 100 °F (56 °C) degrees per hour to 1150 °F ± 15 (621 °C ± 8), hold at 1150 °F ± 15 (621 °C ± 8) for 8 hours ± 0.25 , and cool at a rate equivalent to air cooling. Instead of the 100 °F (56 °C) per hour cooling rate to 1150 °F ± 15 (621 °C ± 8), the furnace cooling may be at any rate provided the time at 1150 °F ± 15 (621 °C ± 8) is adjusted to give a total precipitation heat treatment time of 18 hours.

3.5 Properties

The product shall conform to the following requirements:

3.5.1 Bars, Forgings, and Flash Welded Rings

3.5.1.1 Tensile Properties

Shall be as specified in Table 2, determined in accordance with ASTM E 8 or ASTM E 8M.

TABLE 2A - MINIMUM TENSILE PROPERTIES, INCH/POUND UNITS

Nominal Diameter or Least Distance Between Parallel Sides Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 4D %	Reduction of Area %
Up to 2.50, excl	170	130	12	15
2.50 to 4.00, incl	165	130	12	15

TABLE 2B - MINIMUM TENSILE PROPERTIES, SI UNITS

Nominal Diameter or Least Distance Between Parallel Sides Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 4D %	Reduction of Area %
Up to 63.5, excl	1172	896	12	15
63.5 to 101.6, incl	1138	896	12	15

3.5.1.2 Hardness

Shall be not lower than 285 HB, or equivalent (See 8.2), determined in accordance with ASTM E 10.

3.5.1.3 Average Grain Size

Shall be as follows, determined in accordance with ASTM E 112 or, in case of disagreement, by the intercept (Heyn) method:

3.5.1.3.1 Shall be 5 or finer in bars and flash welded rings 9 square inches (58 cm²) and under in cross-sectional area.

3.5.1.3.2 Shall be ASTM No. 4 or finer in bars and flash welded rings over 9 square inches (58 cm²) in cross-sectional area and in all forgings.

3.5.1.4 Stress-Rupture Properties at 1200 °F (649 °C)

Shall be as follows; testing of notched specimens and of combination smooth-and-notched specimens shall be performed in accordance with ASTM E 292 and of smooth specimens in accordance with ASTM E 139:

3.5.1.4.1 A standard cylindrical combination smooth-and-notched specimen conforming to ASTM E 292, maintained at 1200 °F ± 3 (649 °C ± 2) while a load sufficient to produce an initial axial stress of 100 ksi (689 MPa) is applied continuously, shall not rupture in less than 23 hours. The test shall be continued to rupture without change of load. Rupture shall occur in the smooth section and elongation of this section after rupture, measured at room temperature, shall be not lower than 4% in 4D for product 4.00 inches (101.6 mm) and under in nominal diameter or least distance between parallel sides.

3.5.1.4.2 As an alternate procedure, separate smooth and notched specimens, machined from adjacent sections of the same piece, with gage sections conforming to the respective dimensions shown in ASTM E 292 may be tested individually under the conditions of 3.5.1.4.1. The smooth specimen shall not rupture in less than 23 hours and elongation after rupture, measured at room temperature, shall be as specified in 3.5.1.4.1. The notched specimen shall not rupture in less time than the companion smooth specimen but need not be tested to rupture.

3.5.1.4.3 The tests of 3.5.1.4.1 and 3.5.1.4.2 may be conducted using a load higher than required to produce an initial axial stress of 100 ksi (689 MPa) but load shall not be changed while test is in progress. Time to rupture, rupture location, and elongation requirements shall be as specified in 3.5.1.4.1.

3.5.1.4.4 The tests of 3.5.1.4.1 and 3.5.1.4.2 may be conducted using incremental loading. In such case, the load required to produce an initial axial stress of 100 ksi (689 MPa) shall be used to rupture or for 23 hours, whichever occurs first. After the 23 hours and at intervals of 8 to 16 hours, preferably 8 to 10 hours, thereafter, the stress shall be increased in increments of 5.0 ksi (34.5 MPa). Time to rupture, rupture location, and elongation requirements shall be as specified in 3.5.1.4.1.

3.5.2 Forging Stock

When a sample of stock is forged to a test coupon, solution heat treated as in 3.4.1.2, stabilization heat treated as in 3.4.2, and precipitation heat treated as in 3.4.3, specimens taken from the heat treated coupon shall conform to the requirements of 3.5.1.1, 3.5.1.2, 3.5.1.3, and 3.5.1.4. If specimens taken from the stock after heat treatment as specified above conform to the requirements of 3.5.1.1, 3.5.1.2, 3.5.1.3, and 3.5.1.4, the tests shall be accepted as equivalent to tests of a forged coupon.

3.5.3 Stock for Flash Welded Rings

Specimens taken from the stock after heat treatment as in 3.4 shall conform to the requirements of 3.5.1.1, 3.5.1.2, 3.5.1.3, and 3.5.1.4.

3.6 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.6.1 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of reentrant grain flow.

3.7 Tolerances

Bars shall conform to all applicable requirements of AMS 2261.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

The following requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.1.1 Composition (3.1) of each heat.

4.2.1.2 Tensile properties (3.5.1.1), hardness (3.5.1.2), average grain size (3.5.1.3), and stress-rupture properties (3.5.1.4) of each lot of bars, forgings, and flash welded rings.

4.2.1.3 Tolerances (3.7) of bars.

4.2.2 Periodic Tests

Forging stock (3.5.2) and stock for flash welded rings (3.5.3) to demonstrate ability to develop required properties, and grain flow of die forgings (3.6.1) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.