



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AMS 5705B

Superseding AMS 5705A

Issued 1-1-42

Revised 1-15-81

UNS K63005

STEEL BARS AND FORGINGS, CORROSION AND HEAT RESISTANT
2.5Si - 12.8Cr - 8.0Ni

1. SCOPE:

- 1.1 Form: This specification covers a corrosion and heat resistant steel in the form of bars, forgings, and forging stock.
- 1.2 Application: Primarily for parts, such as intake valves, requiring resistance to corrosion by combustion products at operating temperatures.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

- AMS 2241 - Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire
- AMS 2248 - Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steels and Alloys
- AMS 2350 - Standards and Test Methods
- AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock
- AMS 2374 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Forgings and Forging Stock
- AMS 2806 - Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Heat and Corrosion Resistant Steels and Alloys
- AMS 2808 - Identification, Forgings

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

- ASTM E10 - Brinell Hardness of Metallic Materials
- ASTM E353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

2.3 U. S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

- Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Standards:

- MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Carbon	0.25	0.40
Manganese	--	0.65
Silicon	2.00	3.00
Phosphorus	--	0.030
Sulfur	--	0.030
Chromium	11.50	14.00
Nickel	7.00	9.00
Molybdenum	--	0.50
Copper	--	0.50

- 3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

- 3.2 Condition: The product shall be supplied in the following condition:

- 3.2.1 Bars and Forgings: Annealed having a uniform refined structure. Standards for acceptance shall be as agreed upon by purchaser and vendor.

- 3.2.1.1 Bars 2.75 In. (70 mm) and Under in Nominal Diameter or Distance Between Parallel Sides and All Hexagons: Cold finished.

- 3.2.1.2 Bars, Other than Hexagons, Over 2.75 In. (70 mm) in Nominal Diameter or Distance Between Parallel Sides: Hot finished.

- 3.2.2 Forging Stock: As ordered by the forging manufacturer.

- 3.3 Heat Treatment: Bars and forgings shall be annealed by heating to $1600^{\circ}\text{F} \pm 25$ ($870^{\circ}\text{C} \pm 15$), holding at heat for 4 - 6 hr, and cooling in air.

- 3.4 Properties: The product shall conform to the following requirements:

- 3.4.1 Hardness: Bars and forgings shall have hardness not higher than 285 HB or equivalent, determined in accordance with ASTM E10.

- 3.5 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the product.

- 3.6 Sizes: Except when exact lengths or multiples of exact lengths are ordered, straight bars will be acceptable in mill lengths of 6 - 20 ft (1.8 - 6.1 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 ft (3 m).

- 3.7 Tolerances: Unless otherwise specified, tolerances for bars shall conform to all applicable requirements of AMS 2241.

4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform such confirmatory testing as he deems necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Preproduction Tests: Tests of forgings to determine conformance to all applicable technical requirements of this specification when AMS 2375 is specified are classified as preproduction tests and shall be performed on the first-article shipment of a forging to a purchaser, when a change in material or processing requires reapproval as in 4.4, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement of forgings, substantiating test data and, when requested, preproduction forgings shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling: Shall be in accordance with the following:

4.3.1 Bars: AMS 2371.

4.3.2 Forgings and Forging Stock: AMS 2374.

4.4 Approval: When specified, approval and control of forgings shall be in accordance with AMS 2375.

4.5 Reports:

4.5.1 The vendor of the product shall furnish with each shipment three copies of a report showing the results of tests for chemical composition of each heat and the results of tests on each lot to determine conformance to the other technical requirements of this specification. This report shall include the purchase order number, heat number, AMS 5705B, size, and quantity from each heat. If forgings are supplied, the part number and the size and melt source of stock used to make the forgings shall also be included.

4.5.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, AMS 5705B, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.

4.6 Resampling and Retesting: Shall be in accordance with the following:

4.6.1 Bars: AMS 2371.

4.6.2 Forgings and Forging Stock: AMS 2374.

5. PREPARATION FOR DELIVERY:

5.1 Identification: The product shall be identified as follows:

5.1.1 Bars: In accordance with AMS 2806.

5.1.2 Forgings: In accordance with AMS 2808.

5.1.3 Forging Stock: As agreed upon by purchaser and vendor.

5.2 Packaging: