



AEROSPACE MATERIAL SPECIFICATION

AMS 5709A

Superseding AMS 5709

Society of Automotive Engineers, Inc.
TWO PENNSYLVANIA PLAZA, NEW YORK, N. Y. 10001

Issued 7-15-63
Revised 5-1-70

ALLOY BARS AND FORGINGS, CORROSION AND HEAT RESISTANT

Nickel Base - 19.5Cr - 13.5Co - 4.3Mo - 3.0Ti - 1.4Al

Consumable Electrode or Vacuum Induction Melted

1975 F (1079.4 C) Solution, Stabilization, and Precipitation Heat Treated

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **FORM:** Bars, forgings, and forging stock.
3. **APPLICATION:** Primarily for parts, such as pins, nuts, and turbine blades or buckets, requiring high strength up to 1500 F (816 C) and oxidation resistance up to 1750 F (954 C).
4. **COMPOSITION:**

		min	max
Ø	Carbon	0.03	- 0.10
	Manganese	--	0.10
	Silicon	--	0.15
	Phosphorus	--	0.015
	Sulfur	--	0.015
	Chromium	18.00	- 21.00
	Cobalt	12.00	- 15.00
	Molybdenum	3.50	- 5.00
	Titanium	2.75	- 3.25
	Aluminum	1.20	- 1.60
	Zirconium	0.02	- 0.08
	Boron	0.003	- 0.010
	Iron	--	2.00
	Copper	--	0.10
	Nickel	remainder	

4.1 **Check Analysis:** Composition variations shall meet the requirements of the latest issue of AMS 2269; check analysis limits for zirconium shall be 0.01 under min or over maximum.

5. **CONDITION:** Unless otherwise ordered, the product shall be supplied in the following condition:

5.1 **Bars and Forgings:** Solution, stabilization, and precipitation heat treated, and descaled.

5.1.1 Bars shall be hot rolled or extruded; round bars shall be ground or turned.

5.2 **Forging Stock:** As ordered by the forging manufacturer.

6. **TECHNICAL REQUIREMENTS:**

6.1 **Bars and Forgings:**

6.1.1 **Heat Treatment:** Unless otherwise specified, the product shall be heat treated as follows:

6.1.1.1 **Solution Heat Treatment:** Heat to 1975 F \pm 25 (1079.4 C \pm 14), hold at heat for approximately 4 hr, and cool at a rate equivalent to air cool or faster.

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

- 6.1.1.2 Stabilization Heat Treatment: Heat to 1550 F \pm 15 (843.3 C \pm 8.3), hold at heat for 4 hr, except that blade or bucket forgings shall be held at heat for 24 hr, and cool in air.
- 6.1.1.3 Precipitation Heat Treatment: Heat to 1400 F \pm 15 (760 C \pm 8.3), hold at heat for approximately 16 hr, and cool in air.
- 6.1.2 Hardness: Shall be Rockwell C 32 - 42 or equivalent.
- 6.1.3 Grain Size: Shall be substantially uniform without pronounced segregation of fine and coarse grain areas, in accordance with standards agreed upon by purchaser and vendor. Clusters of large germinated grains will be cause for rejection.
- 6.1.4 Stress Rupture Test at 1500 F (815.6 C): A tensile test specimen, maintained at 1500 F \pm 5 (815.6 C \pm 2.8) while a load sufficient to produce an initial axial stress of 47,500 psi is applied continuously, shall not rupture in less than 23 hours. The test shall be continued to rupture. Elongation after rupture, measured at room temperature, shall be not less than 8% in 4D. Tests shall be conducted in accordance with the issue of ASTM E139 listed in the latest issue of AMS 2350.
- 6.1.4.1 The test of 6.1.4 may be conducted using a load sufficient to produce an initial axial stress higher than 47,500 psi but load shall not be changed while test is in process, unless otherwise specified or allowed. Time to rupture and elongation requirements shall be as specified in 6.1.4.
- 6.2 Forging Stock: When a sample of stock is forged to a test coupon and heat treated as in 6.1.1, specimens taken from the heat treated coupon shall conform to the requirements of 6.1.2, 6.1.3, and 6.1.4. If specimens taken from the stock after heat treatment as in 6.1.1 conform to the requirements of 6.1.2, 6.1.3, and 6.1.4, the tests shall be accepted as equivalent to tests of the forged coupon.
7. QUALITY: Material shall be produced by multiple melting using consumable electrode process in the remelt cycle or shall be induction melted under vacuum, unless otherwise permitted. The product shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts. Forgings shall have substantially uniform macrostructure and grainflow.
8. SAMPLING: Bars shall be sampled in accordance with applicable requirements of the latest issue of AMS 2371 and as specified herein. Forgings and forging stock shall be sampled as agreed upon by purchaser and vendor.
9. TOLERANCES: Unless otherwise specified, tolerances for bars and forging stock shall conform to all applicable requirements of the latest issue of AMS 2261.
10. REPORTS:
- 10.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report of the results of tests for chemical composition of each heat in the shipment and the results of tests on each size from each heat to determine conformance to the technical requirements of this specification. When consumable electrode remelted alloy is supplied, a heat shall be the consumable electrode remelted ingots produced from alloy originally melted as a single furnace charge. This report shall include the purchase order number, material specification number and its revision letter, heat number, size, and quantity from each heat. If forgings are supplied, the part number and size of stock used to make the forgings shall also be included.
- 10.2 Unless otherwise specified, the vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number and its revision letter, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.