

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard



AMS 5717G

Issued JAN 1964
Revised JAN 1999

Superseding AMS 5717F

Nickel Alloy, Corrosion and Heat Resistant, Bars, Forgings, and Rings
45.5Ni - 25.5Cr - 3.2Co - 3.2Mo - 3.2W - 18.5Fe
Solution Heat Treated

UNS N06333

1. SCOPE:

1.1 Form:

This specification covers a corrosion and heat resistant nickel alloy in the form of bars, forgings, flash welded rings, and stock for forging or flash welded rings.

1.2 Application:

These products have been used typically for parts requiring heat and oxidation resistance up to 2150 °F (1177 °C), particularly where such parts may require welding during fabrication, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1999 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

- AMS 2241 Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire
- MAM 2241 Tolerances, Metric, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire
- AMS 2248 Chemical Check Analysis Limits, Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
- AMS 2371 Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock
- AMS 2374 Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steel and Alloy Forgings
- AMS 2806 Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat Resistant Steels and Alloys
- AMS 2808 Identification, Forgings
- AMS 7490 Rings, Flash Welded, Corrosion and Heat Resistant Austenitic Steels, and Austenitic-Type Alloys or Precipitation-Hardenable Alloys

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

- ASTM E 8 Tension Testing of Metallic Materials
- ASTM E 8M Tension Testing of Metallic Materials (Metric)
- ASTM E 18 Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials
- ASTM E 354 Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	-	0.08
Manganese	-	2.00
Silicon	0.75	1.50
Phosphorus	-	0.030
Sulfur	-	0.030
Chromium	24.00	27.00
Nickel	44.00	47.00
Cobalt	2.50	4.00
Molybdenum	2.50	4.00
Tungsten	2.50	4.00
Copper	-	0.50
Tin	-	0.025
Lead	-	0.025
Iron	remainder	

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

3.2 Condition:

The product shall be supplied in the following condition:

3.2.1 Bars, Forgings, and Flash Welded Rings: Solution heat treated.

3.2.1.1 Bars shall be hot finished, except that bars under 0.250 inch (6.35 mm) in nominal diameter or distance between parallel sides may be cold finished.

3.2.1.2 Flash welded rings shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, rings shall be manufactured in accordance with AMS 7490.

3.2.2 Stock for Forging or Flash Welded Rings: As ordered by the forging or flash welded ring manufacturer.

3.3 Heat Treatment:

No specific heat treating instructions are specified, but bars, forgings, and flash welded rings shall be solution heat treated to produce the properties specified in 3.4.1.1 and 3.4.1.2. Recommended solution heat treatment is presented in 3.3.1.

3.3.1 Bars, forgings, and flash welded rings should be solution heat treated by heating to a temperature not lower than 1950 °F (1066 °C), holding at the selected temperature within ± 25 °F (± 14 °C) for a time commensurate with cross-sectional thickness, and cooling at a rate equivalent to an air cool or faster.

3.4 Properties:

The product shall conform to the following requirements:

3.4.1 Bars, Forgings, and Flash Welded Rings:

3.4.1.1 Tensile Properties: Shall be as shown in Table 2, determined in accordance with ASTM E 8 or ASTM E 8M:

TABLE 2 - Tensile Properties

Property	Value
Tensile Strength, maximum	120 ksi (827 MPa)
Yield Strength at 0.2% Offset, minimum	35.0 ksi (241 MPa)
Elongation in 4D, minimum	30%

3.4.1.2 Hardness: Shall be not higher than 95 HRB, or equivalent (See 8.2), determined in accordance with ASTM E 18.

3.4.2 Stock for Forging or Flash Welded Rings: As agreed upon by purchaser and vendor.

3.5 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5.1 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of re-entrant grain flow.

3.6 Tolerances:

Bars shall conform to all applicable requirements of AMS 2241 or MAM 2241.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Composition (3.1), tensile properties (3.4.1.1), hardness (3.4.1.2), and tolerances (3.6) are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests: Grain flow of die forgings (3.5.1) is a periodic test and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing:

Shall be in accordance with the following:

4.3.1 Bars, Flash Welded Rings, and Stock for Forging or Flash Welded Rings: AMS 2371.

4.3.2 Forgings: AMS 2374.

4.4 Reports:

The vendor of the product shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and for tensile properties and hardness requirements of each lot, and stating that the product conforms to the other technical requirements. This report shall include the purchase order number, heat and lot numbers, AMS 5717G, specific heat treating cycles used to obtain reported properties, size, and quantity. If forgings are supplied, the part number and the size and melt source of stock used to make the forgings shall also be included.

4.5 Resampling and Retesting:

Shall be in accordance with the following:

4.5.1 Bars, Flash Welded Rings, and Stock for Forging or Flash Welded Rings: AMS 2371.

4.5.2 Forgings: AMS 2374.