



AEROSPACE MATERIAL SPECIFICATION

AMS5717

REV. H

Issued 1964-01
Revised 2003-07
Reaffirmed 2014-10

Superseding AMS5717G

Nickel Alloy, Corrosion and Heat-Resistant, Bars, Forgings, and Rings
45.5Ni - 25.5Cr - 3.2Co - 3.2Mo - 3.2W - 18.5Fe
Solution Heat Treated
(Composition similar to UNS N06333)

RATIONALE

AMS5717H has been reaffirmed to comply with the SAE five year review policy.

1. SCOPE:

1.1 Form:

This specification covers a corrosion and heat-resistant nickel alloy in the form of bars, forgings, flash welded rings, and stock for forging or flash welded rings.

1.2 Application:

These products have been used typically for parts requiring heat and oxidation resistance up to 2150 °F (1177 °C), particularly where such parts may require welding during fabrication, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2014 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS5717H>

SAE WEB ADDRESS:

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001 or www.sae.org.

| | |
|----------|---|
| AMS 2241 | Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire |
| AMS 2248 | Chemical Check Analysis Limits, Corrosion and Heat-Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys |
| AMS 2371 | Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock |
| AMS 2374 | Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steel and Alloy Forgings |
| AMS 2806 | Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat-Resistant Steels and Alloys |
| AMS 2808 | Identification, Forgings |
| AMS 7490 | Rings, Flash Welded, Corrosion and Heat-Resistant Austenitic Steels, and Austenitic-Type Alloys or Precipitation-Hardenable-Alloys |

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959 or www.astm.org.

| | |
|------------|--|
| ASTM E 8 | Tension Testing of Metallic Materials |
| ASTM E 8M | Tension Testing of Metallic Materials (Metric) |
| ASTM E 18 | Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials |
| ASTM E 354 | Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys |

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

| Element | min | max |
|------------|-----------|-------|
| Carbon | - | 0.08 |
| Manganese | - | 2.00 |
| Silicon | 0.75 | 1.50 |
| Phosphorus | - | 0.030 |
| Sulfur | - | 0.030 |
| Chromium | 24.00 | 27.00 |
| Nickel | 44.00 | 47.00 |
| Cobalt | 2.50 | 4.00 |
| Molybdenum | 2.50 | 4.00 |
| Tungsten | 2.50 | 4.00 |
| Copper | - | 0.50 |
| Tin | - | 0.025 |
| Lead | - | 0.025 |
| Iron | remainder | |

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2248.

3.2 Condition:

The product shall be supplied in the following condition:

3.2.1 Bars, Forgings, and Flash Welded Rings: Solution heat treated.

3.2.1.1 Bars shall be hot finished, except that bars under 0.250 inch (6.35 mm) in nominal diameter or distance between parallel sides may be cold finished.

3.2.1.2 Flash welded rings shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, rings shall be manufactured in accordance with AMS 7490.

3.2.2 Stock for Forging or Flash Welded Rings: As ordered by the forging or flash welded ring manufacturer.

3.3 Heat Treatment:

No specific heat treating instructions are specified, but bars, forgings, and flash welded rings shall be solution heat treated to produce the properties specified in 3.4.1.1 and 3.4.1.2. Recommended solution heat treatment is presented in 3.3.1.

3.3.1 Bars, forgings, and flash welded rings should be solution heat treated by heating to a temperature not lower than 1950 °F (1066 °C), holding at the selected temperature within ± 25 °F (± 14 °C) for a time commensurate with cross-sectional thickness, and cooling at a rate equivalent to an air cool or faster.

3.4 Properties:

The product shall conform to the following requirements:

3.4.1 Bars, Forgings, and Flash Welded Rings:

3.4.1.1 Tensile Properties: Shall be as shown in Table 2, determined in accordance with ASTM E 8 or ASTM E 8M:

TABLE 2 - Tensile Properties

| Property | Value |
|--|--------------------|
| Tensile Strength, maximum | 120 ksi (827 MPa) |
| Yield Strength at 0.2% Offset, minimum | 35.0 ksi (241 MPa) |
| Elongation in 4D, minimum | 30% |

3.4.1.2 Hardness: Shall be not higher than 95 HRB, or equivalent (See 8.2), determined in accordance with ASTM E 18.

3.4.2 Stock for Forging or Flash Welded Rings: As agreed upon by purchaser and vendor.

3.5 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5.1 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of reentrant grain flow.

3.6 Tolerances:

Bars shall conform to all applicable requirements of AMS 2241.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.