



AEROSPACE MATERIAL

Society of Automotive Engineers, Inc.

SPECIFICATION

400 COMMONWEALTH DRIVE, WARRENDALE, PA 15096

AMS 5747

Issued 7-15-77

Revised

UNS N07750

ALLOY BARS, FORGINGS, AND RINGS, CORROSION AND HEAT RESISTANT

72Ni - 15.5Cr - 0.95(Cb+Ta) - 2.5Ti - 0.70Al - 7.0Fe

1. SCOPE:

1.1 Form: This specification covers a corrosion and heat resistant nickel alloy in the form of bars, forgings, flash welded rings, and stock for forging, or flash welded rings.

1.2 Application: Primarily for parts, such as flanges, cases, and turbine rotors, requiring high strength in the range 800° - 1100° F (425° - 595° C).

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2261 - Tolerances, Nickel, Nickel Base, and Cobalt Base Alloy Bars and Forging Stock

AMS 2269 - Chemical Check Analysis Limits, Wrought Nickel Alloys and Cobalt Alloys

AMS 2350 - Standards and Test Methods

AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Alloys, Wrought Products Except Forgings

AMS 2374 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Forgings and Forging Stock

AMS 2375 - Approval and Control of Critical Forgings

AMS 2806 - Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Heat and Corrosion Resistant Steels and Alloys

AMS 2808 - Identification, Forgings

AMS 7490 - Rings, Flash Welded, Corrosion and Heat Resistant, Austenitic Steels and Austenitic-Type Alloys

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E8 - Tension Testing of Metallic Materials

ASTM E10 - Brinell Hardness of Metallic Materials

ASTM E354 - Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt-Base Alloys

2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

2.3.2 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E354, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other approved analytical methods:

	min	max
Carbon	--	0.08
Manganese	--	1.00
Silicon	--	0.50
Phosphorus (3.1.1)	--	0.015
Sulfur	--	0.010
Chromium	14.00 - 17.00	
Nickel + Cobalt	70.00	--
Columbium + Tantalum	0.70 - 1.20	
Titanium	2.25 - 2.75	
Aluminum	0.40 - 1.00	
Iron	5.00 - 9.00	
Cobalt (3.1.1)	--	1.00
Copper	--	0.50

3.1.1 Determination not required for routine acceptance.

3.1.2 Check Analysis: Composition variations shall meet the requirements of AMS 2269.

3.2 Condition: The product shall be supplied in the following condition:

3.2.1 Bars: Hot finished, solution heat treated, and descaled.

3.2.1.1 Round bars shall be ground or turned, except that bars under 0.50 in. (12.7 mm) in nominal diameter shall be cold drawn when so ordered.

3.2.2 Forgings and Flash Welded Rings: Solution heat treated.

3.2.2.1 Flash welded rings shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, they shall be manufactured in accordance with AMS 7490.

3.2.3 Stock for Forging or Flash Welded Rings: As ordered by the forging or flash welded ring manufacturer.

3.3 Heat Treatment: Bars, forgings, and flash welded rings shall be solution treated by heating to 1800° F \pm 25 (982° C \pm 15), holding at heat for not less than 15 min., and cooling at a rate equivalent to air cool or faster.

3.4 Properties: The product shall conform to the following requirements:

3.4.1 Bars, Forgings, and Flash Welded Rings:

3.4.1.1 As Solution Heat Treated:

3.4.1.1.1 Hardness: Shall be not higher than 320 HB or equivalent, determined in accordance with ASTM E10.

3.4.1.2 After Precipitation Heat Treatment: The product shall have the following properties after being precipitation heat treated by heating to 1350° F \pm 15 (732° C \pm 8), holding at heat for 8 hr \pm 0.5, cooling at a rate of 100 F \pm 15 (56 C \pm 8) deg per hr to 1150° F \pm 15 (621° C \pm 8), holding at 1150° F \pm 15 (621° C \pm 8) for 8 hr \pm 1, and cooling in air. Instead of the 100 F (56 C) deg per hr cooling rate to 1150° F \pm 15 (621° C \pm 8), the product may be furnace cooled at any rate provided the time at 1150° F \pm 15 (621° C \pm 8) is adjusted to give a total precipitation heat treatment time of 18 hours.

3.4.1.2.1 Tensile Properties: Shall be as specified in Table I, determined in accordance with ASTM E8:

TABLE I

Nominal Diameter or Distance Between Parallel Sides Inches	Tensile Strength psi, min	Yield Strength at 0.2% Offset psi, min	Elongation in 2 in. or 4D % , min	Reduction of Area % , min
Up to 2.50, excl	170,000	115,000	18	18
2.50 to 4.00, excl	170,000	115,000	15	15

TABLE I (SI)

Nominal Diameter or Distance Between Parallel Sides Millimetres	Tensile Strength MPa, min	Yield Strength at 0.2% Offset MPa, min	Elongation in 50.8 mm or 4D % , min	Reduction of Area % , min
Up to 63.5, excl	1172	793	18	18
63.5 to 101.6, excl	1172	793	15	15

3.4.1.2.1.1 Tensile property requirements for bars 4.00 in. (101.6 mm) and over in nominal diameter or distance between parallel sides, for forgings 4.00 in. (101.6 mm) and over in nominal thickness, and for flash welded rings 4.00 in. (101.6 mm) and over in nominal radial thickness shall be as agreed upon by purchaser and vendor.

3.4.1.2.1.2 The requirements of 3.4.1.2.1 apply to specimens taken with the axis approximately parallel to the grain flow and to specimens taken in the radial direction and in the tangential direction at the rim of disc forgings.

3.4.1.2.1.3 Specific locations of specimens from forgings shall be as agreed upon by purchaser and vendor.

3.4.1.2.2 Hardness: Should be 298 - 382 HB or equivalent, determined in accordance with ASTM E10, but the product shall not be rejected on the basis of hardness if the tensile property requirements are met.

3.4.2 Stock for Forging or Flash Welded Rings: When a sample of stock is forged to a test coupon and heat treated as in 3.3, and 3.4.1.2, specimens taken from the heat treated coupon shall conform to the requirements of 3.4.1.2.1 and 3.4.1.2.2. If specimens taken from the stock after heat treatment as in 3.3 and 3.4.1.2 conform to the requirements of 3.4.1.2.1 and 3.4.1.2.2, the tests shall be accepted as equivalent to tests of a forged coupon.

3.5 Quality: The product, as received by the purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the product.

- 3.6 Sizes: Except when exact lengths or multiples of exact lengths are ordered, straight bars will be acceptable in mill lengths of 6 - 24 ft (1.8 - 7.3 m) but not more than 25% of any shipment shall be supplied in lengths of 6 - 9 ft (1.8 - 2.7 m) except that for bars weighing over 25 lb per ft (37.2 kg/m), short lengths down to 2 ft (610 mm) may be supplied.
- 3.7 Tolerances: Unless otherwise specified, tolerances for bars and forging stock shall conform to all applicable requirements of AMS 2261.
4. QUALITY ASSURANCE PROVISIONS:
- 4.1 Responsibility for Inspection: The vendor of the product shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that the product conforms to the requirements of this specification.
- 4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and as preproduction tests.
- 4.2.1 For direct U.S. Military procurement of forgings, substantiating test data and, when requested, preproduction forgings shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.
- 4.3 Sampling: Shall be in accordance with the following:
- 4.3.1 Bars, Flash Welded Rings, and Stock for Flash Welded Rings: AMS 2371.
- 4.3.2 Forgings and Forging Stock: AMS 2374.
- 4.4 Approval: When specified, approval and control of forgings shall be in accordance with AMS 2375.
- 4.5 Reports:
- 4.5.1 The vendor of the product shall furnish with each shipment three copies of a report showing the results of tests for chemical composition of each heat and the results of tests on each size from each heat to determine conformance to the other technical requirements of this specification. This report shall include the purchase order number, material specification number, heat number, size, and quantity from each heat. If forgings are supplied, the part number and the size and melt source of stock used to make the forgings shall also be included.
- 4.5.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.
- 4.6 Resampling and Retesting: Shall be in accordance with the following:
- 4.6.1 Bars, Flash Welded Rings, and Stock for Flash Welded Rings: AMS 2371.
- 4.6.2 Forgings and Forging Stock: AMS 2374.