

# AEROSPACE MATERIAL SPECIFICATION

**SAE** AMS5751

REV. E

Issued	1960-06
Revised	1982-01
Noncurrent	1987-10
Reaf Nonc	2012-04
Superseding AMS5751D	

Alloy Bars, Forgings, and Rings, Corrosion and Heat Resistant  
54Ni - 17.5Cr - 16.5Co - 4.0Mo - 2.9Ti - 2.9Al - 0.006B  
Solution, Stabilization, and Precipitation Heat Treated  
Consumable Electrode or Vacuum Induction Melted

UNS N07500

## RATIONALE

AMS5751E has been reaffirmed to comply with the SAE five-year review policy.

## NONCURRENT NOTICE

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of 16 October 1987. It is recommended, therefore, that this specification not be specified for new designs.

"NONCURRENT" refers to those materials which have previously been widely used and which may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these as standard materials for future use in new designs. Each of these "NONCURRENT" specifications is available from SAE upon request.

SAENORM.COM : Click to view the full PDF of ams5751e

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: CustomerService@sae.org  
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback  
on this Technical Report, please visit  
<http://www.sae.org/technical/standards/AMS5751E>**

## 1. SCOPE:

### 1.1 Form:

This specification covers a corrosion and heat resistant nickel alloy in the form of bars, forgings, flash welded rings, and stock for forging or flash welded rings.

### 1.2 Application:

Primarily for parts, such as turbine components, requiring high strength up to 1600°F (870°C) and oxidation resistance up to 1800°F (980°C).

## 2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

### 2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

#### 2.1.1 Aerospace Material Specifications:

AMS 2261	Tolerances, Nickel, Nickel Alloy and Cobalt Alloy Bars and Forging Stock
AMS 2269	Chemical Check Analysis Limits, Wrought Nickel Alloys and Cobalt Alloys
AMS 2350	Standards and Test Methods
AMS 2371	Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock
AMS 2374	Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Forgings and Forging Stock
AMS 2375	Control of Forgings Requiring First Article Approval
AMS 2806	Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Heat and Corrosion Resistance Steels and Alloys
AMS 2808	Identification, Forgings
AMS 7490	Rings, Flash Welded, Corrosion and Heat Resistant Austenitic Steels and Austenitic-Type Alloys

## 2.2 ASTM Publications:

Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E10	Brinell Hardness of Metallic Materials
ASTM E21	Elevated Temperature Tension Tests of Metallic Materials
ASTM E112	Estimating the Average Grain Size of Metals
ASTM E139	Conducting Creep, Creep-Rupture, and Stress-Rupture Tests of Metallic Materials
ASTM E354	Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

## 2.3 Government Publications:

Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

### 2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

### 2.3.2 Military Standards:

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

## 3. TECHNICAL REQUIREMENTS:

### 3.1 Composition:

Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E354, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Carbon	--	0.15
Manganese	--	0.75
Silicon	--	0.75
Sulfur	--	0.015
Chromium	15.00	- 20.00
Cobalt	13.00	- 20.00
Molybdenum	3.00	- 5.00
Titanium	2.50	- 3.25
Aluminum	2.50	- 3.25
Boron	0.003	- 0.010
Iron	--	4.00
Copper	--	0.15
Nickel	remainder	

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2269.

3.2 Condition:

The product shall be supplied in the following condition:

3.2.1 Bars, Forgings, and Flash Welded Rings: Solution, stabilization, and precipitation heat treated.

3.2.1.1 Bars shall be hot finished; round bars shall be ground or turned, except that bars under 0.50 in. (12.5 mm) in nominal diameter shall be cold drawn when so ordered.

3.2.1.2 Flash welded rings shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, they shall be manufactured in accordance with AMS 7490.

3.2.2 Stock for Forging or Flash Welded Rings: As ordered by the forging or flash welded ring manufacturer.

3.3 Heat Treatment:

Bars, forgings, and flash welded rings shall be solution heat treated by heating to 1975°F ± 25 (1080°C ± 15), holding at heat for 4 hr ± 0.25 and cooling at a rate equivalent to air cool or faster; stabilization heat treated by heating to 1550°F ± 25 (845°C ± 15), holding at heat for 24 hr ± 1, and cooling in air; and precipitation heat treated by heating to 1400°F ± 25 (760°C ± 15), holding at heat for 16 hr ± 1, and cooling in air.

3.4 Properties:

The product shall conform to the following requirements:

3.4.1 Bars, Forgings, and Flash Welded Rings:

3.4.1.1 Tensile Properties at 1200°F (649°C): Shall be as follows, determined in accordance with ASTM E21 on specimens heated to 1200°F ± 5 (649°C ± 3), held at heat for 20 - 30 min. before testing, and tested at 1200°F ± 5 (649°C ± 3):

Tensile Strength, min	170,000 psi (1170 MPa)
Yield Strength at 0.2% Offset, min	110,000 psi ( 760 MPa)
Elongation in 4D, min	6%
Reduction of Area, min	10%

3.4.1.2 Hardness: Should be not lower than 285 HB or equivalent, determined in accordance with ASTM E10, but the product shall not be rejected on the basis of hardness if the tensile property requirements are met.

- 3.4.1.3 Stress Rupture Properties at 1650°F (899°C): A tensile test specimen, maintained at 1650°F ± 3 (899°C ± 2) while a load sufficient to produce an initial axial stress at 25,000 psi (170 MPa) is applied continuously, shall not rupture in less than 24 hours. The test shall be continued to rupture without change of load. Elongation after rupture, measured at room temperature, shall be not less than 5% in 4D. Tests shall be conducted in accordance with ASTM E139.
- 3.4.1.3.1 The test of 3.4.1.3 may be conducted using a load higher than required to produce an initial axial stress of 25,000 psi (170 MPa) but load shall not be changed while test is in progress. Time to rupture and elongation requirements shall be as specified in 3.4.1.3.
- 3.4.1.3.2 When permitted by purchaser, the test of 3.4.1.3 may be conducted using incremental loading. In such case, the load required to produce an initial axial stress of 25,000 psi (170 MPa) shall be used to rupture or for 24 hr, whichever occurs first. After the 24 hr and at intervals of 8 - 16 hr, preferably 8 - 10 hr, thereafter, the stress shall be increased in increments of 2000 psi (14 MPa). Time to rupture and elongation requirements shall be as specified in 3.4.1.3.
- 3.4.1.4 Grain Size: Shall be predominantly 2 or finer with occasional grains as large as 1 permissible, determined by comparison of a polished and etched specimen with the chart in ASTM E112.
- 3.4.2 Stock for Forging or Flash Welded Rings: When a sample of stock is forged to a test coupon and heat treated as in 3.3, specimens taken from the heat treated coupon shall conform to the requirements of 3.4.1.1, 3.4.1.2, 3.4.1.3, and 3.4.1.4. If specimens taken from the stock after heat treatment as in 3.3 conform to the requirements of 3.4.1.1, 3.4.1.2, 3.4.1.3, and 3.4.1.4, the tests shall be accepted as equivalent to tests of a forged coupon.
- 3.5 Quality:
- 3.5.1 Alloy shall be produced by multiple melting using consumable electrode practice in the remelt cycle or shall be induction melted under vacuum, unless otherwise permitted.
- 3.5.2 The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the product.
- 3.6 Sizes:
- Except when exact lengths or multiples of exact lengths are ordered, straight bars will be acceptable in mill lengths of 6 - 24 ft (2 - 7.5 m) but not more than 25% of any shipment shall be supplied in lengths of 6 - 9 ft (2 - 3 m) except that for bars weighing over 25 lb per ft (37 kg/m), short lengths down to 2 ft (600 mm) may be supplied.
- 3.7 Tolerances:
- Unless otherwise specified, tolerances for bars and forging stock shall conform to all applicable requirements of AMS 2261.

#### 4. QUALITY ASSURANCE PROVISIONS:

##### 4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

##### 4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to the following requirements are classified as acceptance tests and shall be performed on each heat or lot as applicable.

4.2.1.1 Composition (3.1) of each heat.

4.2.1.2 Tensile properties (3.4.1.1), hardness (3.4.1.2), and grain size (3.4.1.4) of bars, forgings, and flash welded rings.

4.2.1.3 Tolerances (3.7) of bars and forging stock.

4.2.2 Periodic Tests: Tests to determine conformance to the following requirements are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser:

4.2.2.1 Stress-rupture properties (3.4.1.3) of bars, forgings, and flash welded rings.

4.2.2.2 Ability of stock for forging or flash welded rings to develop specified properties (3.4.2).

4.2.3 Preproduction Tests: Tests of forgings to determine conformance to all applicable technical requirements of this specification when AMS 2375 is specified are classified as preproduction tests and shall be performed on the first-article shipment of a forging to purchaser, when a change in material and/or processing requires reapproval as in 4.4, and when purchaser deems confirmatory testing to be required.

4.2.3.1 For direct U.S. Military procurement of forgings, substantiating test data and, when requested, preproduction forgings shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.