

AERONAUTICAL MATERIAL SPECIFICATIONS

AMS 5755

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

Issued 1-15-57
Revised

ALLOY, CORROSION AND HEAT RESISTANT
Nickel Base - 5Cr - 24.5Mo - 5.5Fe

1. ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. FORM: Bars, forgings, and forging stock.
3. APPLICATION: Primarily for parts and assemblies, such as turbine shrouds and seals, requiring oxidation resistance up to 1600 F, good strength up to 1200 F, and low coefficient of expansion.
4. COMPOSITION:

Check Analysis
Under Min or Over Max

Carbon	0.12 max	--	0.01
Manganese	1.00 max	--	0.03
Silicon	1.00 max	--	0.05
Phosphorus	0.050 max	--	0.005
Sulfur	0.050 max	--	0.005
Chromium	4.00 - 6.00	0.10	0.10
Molybdenum	23.00 - 26.00	0.10	0.10
Iron	4.00 - 7.00	--	--
Vanadium	0.60 max	--	0.01
Nickel + Cobalt	remainder	--	--
Cobalt, if determined	2.50 max	--	--

5. CONDITION:
 - 5.1 Bars: Hot rolled, solution heat treated, and descaled. Rounds 0.75 in. and over in diameter shall be centerless ground.
 - 5.2 Forgings: Solution heat treated and descaled.
 - 5.3 Forging Stock: As ordered by the forging manufacturer.
6. TECHNICAL REQUIREMENTS:
 - 6.1 Heat Treatment: Material shall be solution heat treated by heating to 2150 F \pm 25, holding at heat for not less than the time indicated below, and quenching in water or rapid air cooling.

Section 7C of the SAE Technical Board rules provides that: "All technical rules... see by anyone engaged in industry or trade is entirely voluntary. There is no... to conform to or be guided by any technical report, in formulating and approving... patents which may apply to the subject matter. Respective users of the report are responsible for protecting themselves against liability for infringement of patents."